

Commission Regulation (EU) No 10/2011 of 14 January 2011 on plastic materials and articles intended to come into contact with food (Text with EEA relevance)

COMMISSION REGULATION (EU) No 10/2011

of 14 January 2011

on plastic materials and articles intended to come into contact with food

(Text with EEA relevance)

THE EUROPEAN COMMISSION,

Having regard to the Treaty on the Functioning of the European Union,

Having regard to Regulation (EC) No 1935/2004 of the European Parliament and of the Council of 27 October 2004 on materials and articles intended to come into contact with food and repealing Directives 80/590/EEC and 89/109/EEC⁽¹⁾, and in particular Article 5(1)(a), (c), (d), (e), (f), (h), (i) and (j) thereof,

After consulting the European Food Safety Authority,

Whereas:

- (1) Regulation (EC) No 1935/2004 lays down the general principles for eliminating the differences between the laws of the Member States as regards food contact materials. Article 5(1) of that Regulation provides for the adoption of specific measures for groups of materials and articles and describes in detail the procedure for the authorisation of substances at EU level when a specific measure provides for a list of authorised substances.
- (2) This Regulation is a specific measure within the meaning of Article 5(1) of Regulation (EC) No 1935/2004. This Regulation should establish the specific rules for plastic materials and articles to be applied for their safe use and repeal Commission Directive 2002/72/EC of 6 August 2002 on plastic materials and articles intended to come into contact with foodstuffs⁽²⁾.
- (3) Directive 2002/72/EC sets out basic rules for the manufacture of plastic materials and articles. The Directive has been substantially amended 6 times. For reasons of clarity the text should be consolidated and redundant and obsolete parts removed.
- (4) In the past Directive 2002/72/EC and its amendments have been transposed into national legislation without any major adaptation. For transposition into national law usually a time period of 12 months is necessary. In case of amending the lists of monomers and additives in order to authorise new substances this transposition time leads to a retardation of the authorisation and thus slows down innovation. Therefore it seems appropriate to adopt rules on plastic materials and articles in form of a Regulation directly applicable in all Member States.

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

- (5) Directive 2002/72/EC applies to materials and articles purely made of plastics and to plastic gaskets in lids. In the past these were the main use of plastics on the market. However, in recent years, besides materials and articles purely made of plastics, plastics are also used in combination with other materials in so called multi-material multi-layers. Rules on the use of vinyl chloride monomer laid down in Council Directive 78/142/EEC of 30 January 1978 on the approximation of the laws of the Member States relating to materials and articles which contain vinyl chloride monomer and are intended to come into contact with foodstuffs⁽³⁾ already apply to all plastics. Therefore it seems appropriate to extend the scope of this Regulation to plastic layers in multi-material multi-layers.
- (6) Plastic materials and articles may be composed of different layers of plastics held together by adhesives. Plastic materials and articles may also be printed or coated with an organic or inorganic coating. Printed or coated plastic materials and articles as well as those held together by adhesives should be within the scope of the Regulation. Adhesives, coatings and printing inks are not necessarily composed of the same substances as plastics. Regulation (EC) No 1935/2004 foresees that for adhesives, coatings and printing inks specific measures can be adopted. Therefore plastic materials and articles that are printed, coated or held together by adhesives should be allowed to contain in the printing, coating or adhesive layer other substances than those authorised at EU level for plastics. Those layers may be subject to other EU or national rules.
- (7) Plastics as well as ion exchange resins, rubbers and silicones are macromolecular substances obtained by polymerisation processes. Regulation (EC) No 1935/2004 foresees that for ion exchange resins, rubbers and silicones specific measures can be adopted. As those materials are composed of different substances than plastics and have different physico-chemical properties specific rules for them need to apply and it should be made clear that they are not within the scope of this Regulation.
- (8) Plastics are made of monomers and other starting substances which are chemically reacted to a macromolecular structure, the polymer, which forms the main structural component of the plastics. To the polymer additives are added to achieve defined technological effects. The polymer as such is an inert high molecular weight structure. As substances with a molecular weight above 1 000 Da usually cannot be absorbed in the body the potential health risk from the polymer itself is minimal. Potential health risk may occur from non- or incompletely reacted monomers or other starting substances or from low molecular weight additives which are transferred into food via migration from the plastic food contact material. Therefore monomers, other starting substances and additives should be risk assessed and authorised before their use in the manufacture of plastic materials and articles.
- (9) The risk assessment of a substance to be performed by the European Food Safety Authority (hereinafter the Authority) should cover the substance itself, relevant impurities and foreseeable reaction and degradation products in the intended use. The risk assessment should cover the potential migration under worst foreseeable conditions of use and the toxicity. Based on the risk assessment the authorisation should if

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

necessary set out specifications for the substance and restrictions of use, quantitative restrictions or migration limits to ensure the safety of the final material or article.

- (10) No rules have yet been set out at EU level for the risk assessment and use of colorants in plastics. Therefore their use should remain subject to national law. That situation should be reassessed at a later stage.
- (11) Solvents used in the manufacture of plastics to create a suitable reaction environment are expected to be removed in the manufacturing process as they are usually volatile. No rules have yet been set out at EU level for the risk assessment and use of solvents in the manufacture of plastics. Therefore their use should remain subject to national law. That situation should be reassessed at a later stage.
- (12) Plastics can also be made of synthetic or natural occurring macromolecular structures which are chemically reacted with other starting substances to create a modified macromolecule. Synthetic macromolecules used are often intermediate structures which are not fully polymerised. Potential health risk may occur from the migration of non- or incompletely reacted other starting substances used to modify the macromolecule or an incompletely reacted macromolecule. Therefore the other starting substances as well as the macromolecules used in the manufacture of modified macromolecules should be risk assessed and authorised before their use in the manufacture of plastic materials and articles.
- (13) Plastics can also be made by micro-organisms that create macromolecular structures out of starting substances by fermentation processes. The macromolecule is then either released to a medium or extracted. Potential health risk may occur from the migration of non- or incompletely reacted starting substances, intermediates or by-products of the fermentation process. In this case the final product should be risk assessed and authorised before its use in the manufacture of plastic materials and articles.
- (14) Directive 2002/72/EC contains different lists for monomers or other starting substances and for additives authorised for the manufacture of plastic materials and articles. For monomers, other starting substances and additives the Union list is now complete, this means that only substances authorised at EU level may be used. Therefore a separation of monomers or other starting substances and of additives in separate lists due to their authorisation status is no longer necessary. As certain substances can be used both as monomer or other starting substances and as additive for reasons of clarity they should be published in one list of authorised substances indicating the authorised function.
- (15) Polymers can not only be used as main structural component of plastics but also as additives achieving defined technological effects in the plastic. If such a polymeric additive is identical to a polymer that can form the main structural component of a plastic material the risk from polymeric additive can be regarded as evaluated if the monomers have already been evaluated and authorised. In such a case it should not be necessary to authorise the polymeric additive but it could be used on the basis of the authorisation of its monomers and other starting substances. If such a polymeric additive is not identical to a polymer that can form the main structural component of a plastic material then the risk of the polymeric additive can not be regarded as evaluated by evaluation of the monomers. In such a case the polymeric additive should be risk

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

assessed as regards its low molecular weight fraction below 1 000 Da and authorised before its use in the manufacture of plastic materials and articles.

- (16) In the past no clear differentiation has been made between additives that have a function in the final polymer and polymer production aids (PPA) that only exhibit a function in the manufacturing process and are not intended to be present in the final article. Some substances acting as PPA had already been included in the incomplete list of additives in the past. These PPA should remain in the Union list of authorised substances. However, it should be made clear that the use of other PPA will remain possible, subject to national law. That situation should be reassessed at a later stage.
- (17) The Union list contains substances authorised to be used in the manufacture of plastics. Substances such as acids, alcohols and phenols can also occur in form of salts. As the salts usually are transformed in the stomach to acid, alcohol or phenol the use of salts with cations that have undergone a safety evaluation should in principle be authorised together with the acid, alcohol or phenol. In certain cases, where the safety assessment indicates concerns on the use of the free acids, only the salts should be authorised by indicating in the list the name as ‘... acid(s), salts’.
- (18) Substances used in the manufacture of plastic materials or articles may contain impurities originating from their manufacturing or extraction process. These impurities are non-intentionally added together with the substance in the manufacture of the plastic material (non-intentionally added substance – NIAS). As far as they are relevant for the risk assessment the main impurities of a substance should be considered and if necessary be included in the specifications of a substance. However it is not possible to list and consider all impurities in the authorisation. Therefore they may be present in the material or article but not included in the Union list.
- (19) In the manufacture of polymers substances are used to initiate the polymerisation reaction such as catalysts and to control the polymerisation reaction such as chain transfer, chain extending or chain stop reagents. These aids to polymerisation are used in minute amounts and are not intended to remain in the final polymer. Therefore they should at this point of time not be subject to the authorisation procedure at EU level. Any potential health risk in the final material or article arising from their use should be assessed by the manufacturer in accordance with internationally recognised scientific principles on risk assessment.
- (20) During the manufacture and use of plastic materials and articles reaction and degradation products can be formed. These reaction and degradation products are non-intentionally present in the plastic material (NIAS). As far as they are relevant for the risk assessment the main reaction and degradation products of the intended application of a substance should be considered and included in the restrictions of the substance. However it is not possible to list and consider all reaction and degradation products in the authorisation. Therefore they should not be listed as single entries in the Union list. Any potential health risk in the final material or article arising from reaction and degradation products should be assessed by the manufacturer in accordance with internationally recognised scientific principles on risk assessment.

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

- (21) Prior to the establishment of the Union list of additives, other additives than those authorised at EU level could be used in the manufacture of plastics. For those additives which were permitted in the Member States, the time limit for the submission of data for their safety evaluation by the Authority with a view to their inclusion in the Union list expired on 31 December 2006. Additives for which a valid application was submitted within this time limit were listed in a provisional list. For certain additives on the provisional list a decision on their authorisation at EU level has not yet been taken. For those additives, it should be possible to continue to be used in accordance with national law until their evaluation is completed and a decision is taken on their inclusion in the Union list.
- (22) When an additive included in the provisional list is inserted in the Union list or when it is decided not to include it in the Union list, that additive should be removed from the provisional list of additives.
- (23) New technologies engineer substances in particle size that exhibit chemical and physical properties that significantly differ from those at a larger scale, for example, nanoparticles. These different properties may lead to different toxicological properties and therefore these substances should be assessed on a case-by-case basis by the Authority as regards their risk until more information is known about such new technology. Therefore it should be made clear that authorisations which are based on the risk assessment of the conventional particle size of a substance do not cover engineered nanoparticles.
- (24) Based on the risk assessment the authorisation should if necessary set out specific migration limits to ensure the safety of the final material or article. If an additive that is authorised for the manufacture of plastic materials and articles is at the same time authorised as food additive or flavouring substance it should be ensured that the release of the substance does not change the composition of the food in an unacceptable way. Therefore the release of such a dual use additive or flavouring should not exhibit a technological function on the food unless such a function is intended and the food contact material complies with the requirements on active food contact materials set out in Regulation (EC) No 1935/2004 and Commission Regulation (EC) No 450/2009 of 29 May 2009 on active and intelligent materials and articles intended to come into contact with food⁽⁴⁾. The requirements of Regulations (EC) No 1333/2008 of the European Parliament and of the Council of 16 December 2008 on food additives⁽⁵⁾ or (EC) No 1334/2008 of the European Parliament and of the Council of 16 December 2008 on flavourings and certain food ingredients with flavouring properties for use in and on foods and amending Council Regulation (EEC) No 1601/91, Regulations (EC) No 2232/96 and (EC) No 110/2008 and Directive 2000/13/EC⁽⁶⁾ should be respected where applicable.
- (25) According to Article 3(1)(b) of Regulation (EC) No 1935/2004 the release of substances from food contact materials and articles should not bring about unacceptable changes in the composition of the food. According to good manufacturing practice it is feasible to manufacture plastic materials in such a way that they are not releasing more than 10 mg of substances per 1 dm² of surface area of the plastic material. If the risk

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

assessment of an individual substance is not indicating a lower level, this level should be set as a generic limit for the inertness of a plastic material, the overall migration limit. In order to achieve comparable results in the verification of compliance with the overall migration limit, testing should be performed under standardised test conditions including testing time, temperature and test medium (food simulant) representing worst foreseeable conditions of use of the plastic material or article.

- (26) The overall migration limit of 10 mg per 1 dm² results for a cubic packaging containing 1kg of food to a migration of 60 mg per kg food. For small packaging where the surface to volume ratio is higher the resulting migration into food is higher. For infants and small children which have a higher consumption of food per kilogram bodyweight than adults and do not yet have a diversified nutrition, special provisions should be set in order to limit the intake of substances migrating from food contact materials. In order to allow also for small volume packaging the same protection as for high volume packaging, the overall migration limit for food contact materials that are dedicated for packaging foods for infants and small children should be linked to the limit in food and not to the surface area of the packaging.
- (27) In recent years plastic food contact materials are being developed that do not only consist of one plastic but combine up to 15 different plastic layers to attain optimum functionality and protection of the food, while reducing packaging waste. In such a plastic multi-layer material or article, layers may be separated from the food by a functional barrier. This barrier is a layer within food contact materials or articles preventing the migration of substances from behind that barrier into the food. Behind a functional barrier, non-authorised substances may be used, provided they fulfil certain criteria and their migration remains below a given detection limit. Taking into account foods for infants and other particularly susceptible persons, as well as the large analytical tolerance of the migration analysis, a maximum level of 0,01 mg/kg in food should be established for the migration of a non-authorised substance through a functional barrier. Substances that are mutagenic, carcinogenic or toxic to reproduction should not be used in food contact materials or articles without previous authorisation and should therefore not be covered by the functional barrier concept. New technologies that engineer substances in particle size that exhibit chemical and physical properties that significantly differ from those at a larger scale, for example, nanoparticles, should be assessed on a case-by-case basis as regards their risk until more information is known about such new technology. Therefore, they should not be covered by the functional barrier concept.
- (28) In recent years food contact materials and articles are being developed that consist of a combination of several materials to achieve optimum functionality and protection of the food while reducing packaging waste. In these multi-material multi-layer materials and articles plastic layers should comply with the same compositional requirements as plastic layers which are not combined with other materials. For plastic layers in a multi-material multi-layer which are separated from the food by a functional barrier the functional barrier concept should apply. As other materials are combined with the plastic layers and for these other materials specific measures are not yet adopted at EU level it is not yet possible to set out requirements for the final multi-material multi-layer

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

materials and articles. Therefore specific migration limits and the overall migration limit should not be applicable except for vinyl chloride monomer for which such a restriction is already in place. In the absence of a specific measure at EU level covering the whole multi-material multi-layer material or article Member States may maintain or adopt national provisions for these materials and articles provided they comply with the rules of the Treaty.

- (29) Article 16(1) of Regulation (EC) No 1935/2004 provides that materials and articles covered by specific measures be accompanied by a written declaration of compliance stating that they comply with the rules applicable to them. To strengthen the coordination and responsibility of the suppliers at each stage of manufacture, including that of the starting substances, the responsible persons should document the compliance with the relevant rules in a declaration of compliance which is made available to their customers.
- (30) Coatings, printing inks and adhesives are not yet covered by a specific EU legislation and therefore not subject to the requirement of a declaration of compliance. However, for coatings, printing inks and adhesives to be used in plastic materials and articles adequate information should be provided to the manufacturer of the final plastic article that would enable him to ensure compliance for substances for which migration limits have been established in this Regulation.
- (31) Article 17(1) of Regulation (EC) No 178/2002 of the European Parliament and of the Council of 28 January 2002 laying down the general principles and requirements of food law, establishing the European Food Safety Authority and laying down procedures in matters of food safety⁽⁷⁾ requires the food business operator to verify that foods are compliant with the rules applicable to them. To this end and subject to the requirement of confidentiality, food business operators should be given access to the relevant information to enable them to ensure that the migration from the materials and articles to food complies with the specifications and restrictions laid down in food legislation.
- (32) At each stage of manufacture, supporting documentation, substantiating the declaration of compliance, should be kept available for the enforcement authorities. Such demonstration of compliance may be based on migration testing. As migration testing is complex, costly and time consuming it should be admissible that compliance can be demonstrated also by calculations, including modelling, other analysis, and scientific evidence or reasoning if these render results which are at least as severe as the migration testing. Test results should be regarded as valid as long as formulations and processing conditions remain constant as part of a quality assurance system.
- (33) When testing articles not yet in contact with food, for certain articles, such as films or lids, it is often not feasible to determine the surface area that is in contact with a defined volume of food. For these articles specific rules should be set out for verification of compliance.
- (34) The setting of migration limits takes into account a conventional assumption that 1kg of food is consumed daily by a person of 60 kg bodyweight and that the food is packaged in a cubic container of 6 dm² surface area releasing the substance. For very small and very large containers the real surface area to volume of packaged food is varying a lot

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

from the conventional assumption. Therefore, their surface area should be normalised before comparing testing results with migration limits. These rules should be reviewed when new data on food packaging uses become available.

- (35) The specific migration limit is a maximum permitted amount of a substance in food. This limit should ensure that the food contact material does not pose a risk to health. It should be ensured by the manufacturer that materials and articles not yet in contact with food will respect these limits when brought into contact with food under the worst foreseeable contact conditions. Therefore compliance of materials and articles not yet in contact with food should be assessed and the rules for this testing should be set out.
- (36) Food is a complex matrix and therefore the analysis of migrating substances in food may pose analytical difficulties. Therefore test media should be assigned that simulate the transfer of substances from the plastic material into food. They should represent the major physico-chemical properties exhibited by food. When using food simulants standard testing time and temperature should reproduce, as far as possible, the migration which may occur from the article into the food.
- (37) For determining the appropriate food simulant for certain foods the chemical composition and the physical properties of the food should be taken into account. Research results are available for certain representative foods comparing migration into food with migration into food simulants. On the basis of the results, food simulants should be assigned. In particular, for fat containing foods the result obtained with food simulant may in certain cases significantly overestimate migration into food. In these cases it should be foreseen that the result in food simulant is corrected by a reduction factor.
- (38) The exposure to substances migrating from food contact materials was based on the conventional assumption that a person consumes daily 1 kg of food. However, a person ingests at most 200 g of fat on a daily basis. For lipophilic substances that only migrate into fat this should be taken into consideration. Therefore a correction of the specific migration by a correction factor applicable to lipophilic substances in accordance with the opinion of the Scientific Committee on Food (SCF)⁽⁸⁾ and the opinion of the Authority⁽⁹⁾ should be foreseen.
- (39) Official control should establish testing strategies which allow the enforcement authorities to perform controls efficiently making best use of available resources. Therefore it should be admissible to use screening methods for checking compliance under certain conditions. Non-compliance of a material or article should be confirmed by a verification method.
- (40) Basic rules on migration testing should be set out in this Regulation. As migration testing is a very complex issue, these basic rules can, however, not cover all foreseeable cases and details necessary for performing the testing. Therefore a EU guidance document should be established, dealing with more detailed aspects of the implementation of the basic migration testing rules.
- (41) The updated rules on food simulants and migration testing provided by this Regulation will supersede those in Directive 78/142/EEC and the Annex to Council Directive

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

82/711/EEC of 18 October 1982 laying down the basic rules necessary for testing migration of the constituents of plastic materials and articles intended to come into contact with foodstuffs⁽¹⁰⁾.

- (42) Substances present in the plastic but not listed in Annex I to this Regulation have not necessarily been risk assessed as they had not been subject to an authorisation procedure. Compliance with Article 3 of Regulation (EC) No 1935/2004 for these substances should be assessed by the relevant business operator in accordance with internationally recognised scientific principles taking into account exposure from food contact materials and other sources.
- (43) Recently additional monomers, other starting substances and additives have received a favourable scientific evaluation by the Authority and should now be added to the Union list.
- (44) As new substances are added to the Union list the Regulation should apply as soon as possible to allow for manufacturers to adapt to technical progress and allow for innovation.
- (45) Certain migration testing rules should be updated in view of new scientific knowledge. Enforcement authorities and industry need to adapt their current testing regime to these updated rules. To allow for this adaptation it seems appropriate that the updated rules only apply 2 years after the adoption of the Regulation.
- (46) Business operators are currently basing their declaration of compliance on supporting documentation following the requirements set out in Directive 2002/72/EC. Declaration of compliance need, in principle, only to be updated when substantial changes in the production bring about changes in the migration or when new scientific data are available. In order to limit the burden to business operators, materials which have been lawfully placed on the market based on the requirements set out in Directive 2002/72/EC should be able to be placed on the market with a declaration of compliance based on supporting documentation in accordance with Directive 2002/72/EC until 5 years after the adoption of the Regulation.
- (47) Analytical methods for testing migration and residual content of vinyl chloride monomer as described in Commission Directives 80/766/EEC of 8 July 1980 laying down the Community method of analysis for the official control of the vinyl chloride monomer level in materials and articles which are intended to come into contact with foodstuffs⁽¹¹⁾ and 81/432/EEC of 29 April 1981 laying down the Community method of analysis for the official control of vinyl chloride released by materials and articles into foodstuffs⁽¹²⁾ are outdated. Analytical methods should comply with the criteria set out in Article 11 of Regulation (EC) No 882/2004⁽¹³⁾ of the European Parliament and of the Council on official controls performed to ensure the verification of compliance with feed and food law, animal health and animal welfare rules. Therefore Directives 80/766/EEC and 81/432/EEC should be repealed.
- (48) The measures provided for in this Regulation are in accordance with the opinion of the Standing Committee on the Food Chain and Animal Health,

HAS ADOPTED THIS REGULATION:

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

CHAPTER I

GENERAL PROVISIONS

Article 1

Subject matter

1 This Regulation is a specific measure within the meaning of Article 5 of Regulation (EC) No 1935/2004.

2 This Regulation establishes specific requirements for the manufacture and marketing of plastic materials and articles:

- a intended to come into contact with food; or
- b already in contact with food; or
- c which can reasonably be expected to come into contact with food.

Article 2

Scope

1 This Regulation shall apply to materials and articles which are placed on the EU market and fall under the following categories:

- a materials and articles and parts thereof consisting exclusively of plastics;
- b plastic multi-layer materials and articles held together by adhesives or by other means;
- c materials and articles referred to in points a) or b) that are printed and/or covered by a coating;
- d plastic layers or plastic coatings, forming gaskets in caps and closures, that together with those caps and closures compose a set of two or more layers of different types of materials;
- e plastic layers in multi-material multi-layer materials and articles.

2 This Regulation shall not apply to the following materials and articles which are placed on the EU market and are intended to be covered by other specific measures:

- a ion exchange resins;
- b rubber;
- c silicones.

3 This Regulation shall be without prejudice to the EU or national provisions applicable to printing inks, adhesives or coatings.

Article 3

Definitions

For the purpose of this Regulation, the following definitions shall apply:

(1) 'plastic materials and articles' means:

- (a) materials and articles referred to in points (a), (b) and (c) of Article 2(1); and

- (b) plastic layers referred to in Article 2(1)(d) and (e);
- (2) ‘plastic’ means polymer to which additives or other substances may have been added, which is capable of functioning as a main structural component of final materials and articles;
- (3) ‘polymer’ means any macromolecular substance obtained by:
 - (a) a polymerisation process such as polyaddition or polycondensation, or by any other similar process of monomers and other starting substances; or
 - (b) chemical modification of natural or synthetic macromolecules; or
 - (c) microbial fermentation;
- (4) ‘plastic multi-layer’ means a material or article composed of two or more layers of plastic;
- (5) ‘multi-material multi-layer’ means a material or article composed of two or more layers of different types of materials, at least one of them a plastic layer;
- (6) ‘monomer or other starting substance’ means:
 - (a) a substance undergoing any type of polymerisation process to manufacture polymers; or
 - (b) a natural or synthetic macromolecular substance used in the manufacture of modified macromolecules; or
 - (c) a substance used to modify existing natural or synthetic macromolecules;
- (7) ‘additive’ means a substance which is intentionally added to plastics to achieve a physical or chemical effect during processing of the plastic or in the final material or article; it is intended to be present in the final material or article;
- (8) ‘polymer production aid’ means any substance used to provide a suitable medium for polymer or plastic manufacturing; it may be present but is neither intended to be present in the final materials or articles nor has a physical or chemical effect in the final material or article;
- (9) ‘non-intentionally added substance’ means an impurity in the substances used or a reaction intermediate formed during the production process or a decomposition or reaction product;
- (10) ‘aid to polymerisation’ means a substance which initiates polymerisation and/or controls the formation of the macromolecular structure;
- (11) ‘overall migration limit’ (OML) means the maximum permitted amount of non-volatile substances released from a material or article into food simulants;
- (12) ‘food simulant’ means a test medium imitating food; in its behaviour the food simulant mimics migration from food contact materials;
- (13) ‘specific migration limit’ (SML) means the maximum permitted amount of a given substance released from a material or article into food or food simulants;

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

- (14) ‘total specific migration limit’ (SML(T)) means the maximum permitted sum of particular substances released in food or food simulants expressed as total of moiety of the substances indicated;
- (15) ‘functional barrier’ means a barrier consisting of one or more layers of any type of material which ensures that the final material or article complies with Article 3 of Regulation (EC) No 1935/2004 and with the provisions of this Regulation;
- (16) [^{F1}‘non-fatty food’ means a food for which in migration testing only food simulants other than food simulants D1 or D2 are laid down in Table 2 of Annex III to this Regulation;]
- (17) ‘restriction’ means limitation of use of a substance or migration limit or limit of content of the substance in the material or article;
- (18) [^{F1}‘specification’ means composition of a substance, purity criteria for a substance, physico-chemical characteristics of a substance, details concerning the manufacturing process of a substance or further information concerning the expression of migration limits;]
- (19) [^{F2}‘hot-fill’ means the filling of any article with a food with a temperature not exceeding 100 °C at the moment of filling, after which the food cools down to 50 °C or below within 60 minutes, or to 30 °C or below within 150 minutes.]

Textual Amendments

- F1** Substituted by [Commission Regulation \(EU\) 2016/1416 of 24 August 2016 amending and correcting Regulation \(EU\) No 10/2011 on plastic materials and articles intended to come into contact with food \(Text with EEA relevance\).](#)
- F2** Inserted by [Commission Regulation \(EU\) 2016/1416 of 24 August 2016 amending and correcting Regulation \(EU\) No 10/2011 on plastic materials and articles intended to come into contact with food \(Text with EEA relevance\).](#)

Article 4

Placing on the market of plastic materials and articles

Plastic materials and articles may only be placed on the market if they:

- (a) comply with the relevant requirements set out in Article 3 of Regulation (EC) No 1935/2004 under intended and foreseeable use; and
- (b) comply with the labelling requirements set out in Article 15 of Regulation (EC) No 1935/2004; and
- (c) comply with the traceability requirements set out in Article 17 of Regulation (EC) No 1935/2004; and
- (d) are manufactured according to good manufacturing practice as set out in Commission Regulation (EC) No 2023/2006⁽¹⁴⁾; and
- (e) comply with the compositional and declaration requirements set out in Chapters II, III and IV of this Regulation.

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

CHAPTER II

COMPOSITIONAL REQUIREMENTS

SECTION 1

Authorised substances

Article 5

Union list of authorised substances

- 1 Only the substances included in the Union list of authorised substances (hereinafter referred to as the Union list) set out in Annex I may be intentionally used in the manufacture of plastic layers in plastic materials and articles.
- 2 The Union list shall contain:
 - a monomers or other starting substances;
 - b additives excluding colorants;
 - c polymer production aids excluding solvents;
 - d macromolecules obtained from microbial fermentation.
- 3 The Union list may be amended in accordance with the procedure established by Articles 8 to 12 of Regulation (EC) No 1935/2004.

Article 6

Derogations for substances not included in the Union list

- 1 By way of derogation from Article 5, substances other than those included in the Union list may be used as polymer production aids in the manufacture of plastic layers in plastic materials and articles subject to national law.
- 2 By way of derogation from Article 5, colorants and solvents may be used in the manufacture of plastic layers in plastic materials and articles subject to national law.
- 3 The following substances not included in the Union list are authorised subject to the rules set out in Articles 8, 9, 10, 11 and 12:
 - [^{F3}a all salts of substances for which ‘yes’ is indicated in column 2 in Table 1 of Annex II of authorised acids, phenols or alcohols, and subject to the restrictions set out in column 3 and 4 of that table;]
 - b mixtures obtained by mixing authorised substances without a chemical reaction of the components;
 - c when used as additives, natural or synthetic polymeric substances of a molecular weight of at least 1 000 Da, except macromolecules obtained from microbial fermentation, complying with the requirements of this Regulation, if they are capable of functioning as the main structural component of final materials or articles;
 - d when used as monomer or other starting substance, pre-polymers and natural or synthetic macromolecular substances, as well as their mixtures, except macromolecules obtained from microbial fermentation, if the monomers or starting substances required to synthesise them are included in the Union list.

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

4 The following substances not included in the Union list may be present in the plastic layers of plastic materials or articles:

- a non-intentionally added substances;
- b aids to polymerisation.

5 By derogation from Article 5, additives not included in the Union list may continue to be used subject to national law after 1 January 2010 until a decision is taken to include or not to include them in the Union list provided they are included in the provisional list referred to in Article 7.

Textual Amendments

- F3** Substituted by [Commission Regulation \(EU\) 2020/1245 of 2 September 2020 amending and correcting Regulation \(EU\) No 10/2011 on plastic materials and articles intended to come into contact with food \(Text with EEA relevance\)](#).

Article 7

Establishment and management of the provisional list

1 The provisional list of additives that are under evaluation by the European Food Safety Authority (hereinafter referred to as the Authority) that was made public by the Commission in 2008 shall be regularly updated.

- 2 An additive shall be removed from the provisional list:
- a when it is included in the Union list set out in Annex I; or
 - b when a decision is taken by the Commission not to include it in the Union list; or
 - c if during the examination of the data, the Authority calls for supplementary information and that information is not submitted within the time limits specified by the Authority.

SECTION 2

General requirements, restrictions and specifications

Article 8

General requirement on substances

Substances used in the manufacture of plastic layers in plastic materials and articles shall be of a technical quality and a purity suitable for the intended and foreseeable use of the materials or articles. The composition shall be known to the manufacturer of the substance and made available to the competent authorities on request.

Article 9

Specific requirements on substances

1 Substances used in the manufacture of plastic layers in plastic materials and articles shall be subject to the following restrictions and specifications:

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

- a the specific migration limit set out in Article 11;
 - b the overall migration limit set out in Article 12;
 - c the restrictions and specifications set out in column 10 of Table 1 of point 1 of Annex I;
 - d the detailed specifications set out in point 4 of Annex I.
- 2 Substances in nanoform shall only be used if explicitly authorised and mentioned in the specifications in Annex I.

Article 10

General restrictions on plastic materials and articles

General restrictions related to plastic materials and articles are laid down in Annex II.

Article 11

Specific migration limits

1 Plastic materials and articles shall not transfer their constituents to foods in quantities exceeding the specific migration limits (SML) set out in Annex I. Those specific migration limits (SML) are expressed in mg of substance per kg of food (mg/kg).

^{F4}2

[^{F13} By derogation from paragraph 1, additives which are also authorised as food additives by Regulation (EC) No 1333/2008 or as flavourings by Regulation (EC) No 1334/2008 shall not migrate into foods in quantities having a technical effect in the final foods and shall not:

- a exceed the restrictions provided for in Regulation (EC) No 1333/2008 or in Regulation (EC) No 1334/2008 or in Annex I to this Regulation for foods for which their use is authorised as food additive or flavouring substances; or
- b exceed the restrictions set out in Annex I to this Regulation in foods for which their use is not authorised as food additive or flavouring substances.]

[^{F24} Where it is specified that no migration of a particular substance is permitted, compliance shall be established using appropriate migration test methods selected in accordance with Article 11 of Regulation (EC) No 882/2004 that can confirm the absence of migration above a specified limit of detection.

For the purposes of the first subparagraph, unless specific detection limits have been set for particular substances or groups of substances, a detection limit of 0,01 mg/kg shall apply.]

Textual Amendments

- F1** Substituted by [Commission Regulation \(EU\) 2016/1416 of 24 August 2016 amending and correcting Regulation \(EU\) No 10/2011 on plastic materials and articles intended to come into contact with food \(Text with EEA relevance\).](#)
- F2** Inserted by [Commission Regulation \(EU\) 2016/1416 of 24 August 2016 amending and correcting Regulation \(EU\) No 10/2011 on plastic materials and articles intended to come into contact with food \(Text with EEA relevance\).](#)

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

F4 Deleted by Commission Regulation (EU) 2016/1416 of 24 August 2016 amending and correcting Regulation (EU) No 10/2011 on plastic materials and articles intended to come into contact with food (Text with EEA relevance).

Article 12

Overall migration limit

1 Plastic materials and articles shall not transfer their constituents to food simulants in quantities exceeding 10 milligrams of total constituents released per dm² of food contact surface (mg/dm²).

2 By derogation from paragraph 1, plastic materials and articles intended to be brought into contact with food intended for infants and young children, as defined by Commission Directives 2006/141/EC⁽¹⁵⁾ and 2006/125/EC⁽¹⁶⁾, shall not transfer their constituents to food simulants in quantities exceeding 60 milligrams of total of constituents released per kg of food simulant.

CHAPTER III

SPECIFIC PROVISIONS FOR CERTAIN MATERIALS AND ARTICLES

Article 13

Plastic multi-layer materials and articles

1 In a plastic multi-layer material or article, the composition of each plastic layer shall comply with this Regulation.

2 By derogation from paragraph 1, a plastic layer which is not in direct contact with food and is separated from the food by a functional barrier, may:

- a not comply with the restrictions and specifications set out in this Regulation except for vinyl chloride monomer as provided in Annex I; and/or
- b be manufactured with substances not listed in the Union list or in the provisional list.

[^{F13} Substances under paragraph 2(b) shall not migrate into food or food simulant, in accordance with Article 11(4). The detection limit set out in the second subparagraph of Article 11(4) shall apply to groups of substances if they are structurally and toxicologically related, including isomers or substances with the same relevant functional group, or to individual substances that are not related, and shall include possible set-off transfer.]

4 The substances not listed in the Union list or provisional list referred to in paragraph 2(b) shall not belong to either of the following categories:

- a substances classified as ‘mutagenic’, ‘carcinogenic’ or ‘toxic to reproduction’ in accordance with the criteria set out in sections 3.5, 3.6. and 3.7 of Annex I to Regulation (EC) No 1272/2008 of the European Parliament and the Council⁽¹⁷⁾;
- b substances in nanof orm.

5 The final plastic multi-layer material or article shall comply with the specific migration limits set out in Article 11 and the overall migration limit set out in Article 12 of this Regulation.

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

Textual Amendments

- F1** Substituted by [Commission Regulation \(EU\) 2016/1416 of 24 August 2016 amending and correcting Regulation \(EU\) No 10/2011 on plastic materials and articles intended to come into contact with food \(Text with EEA relevance\).](#)

Article 14

Multi-material multi-layer materials and articles

- 1 In a multi-material multi-layer material or article, the composition of each plastic layer shall comply with this Regulation.
- 2 By derogation from paragraph 1, in a multi-material multi-layer material or article a plastic layer which is not in direct contact with food and is separated from the food by a functional barrier, may be manufactured with substances not listed in the Union list or the provisional list.
- 3 The substances not listed in the Union list or provisional list referred to in paragraph 2 shall not belong to either of the following categories:
 - a substances classified as ‘mutagenic’, ‘carcinogenic’ or ‘toxic to reproduction’ in accordance with the criteria set out in sections 3.5, 3.6. and 3.7 of Annex I to Regulation (EC) No 1272/2008;
 - b substances in nanoform.
- 4 By derogation from paragraph 1, Articles 11 and 12 of this Regulation do not apply to plastic layers in multi-material multi-layer materials and articles.
- 5 The plastic layers in a multi-material multi-layer material or article shall always comply with the restrictions for vinyl chloride monomer laid down in Annex I to this Regulation.
- 6 In a multi-material multi-layer material or article, specific and overall migration limits for plastic layers and for the final material or article may be established by national law.

CHAPTER IV

DECLARATION OF COMPLIANCE AND DOCUMENTATION

Article 15

Declaration of compliance

- 1 At the marketing stages other than at the retail stage, a written declaration in accordance with Article 16 of Regulation (EC) No 1935/2004 shall be available for plastic materials and articles, products from intermediate stages of their manufacturing as well as for the substances intended for the manufacturing of those materials and articles.
- 2 The written declaration referred to in paragraph 1 shall be issued by the business operator and shall contain the information laid down in Annex IV.
- 3 The written declaration shall permit an easy identification of the materials, articles or products from intermediate stages of manufacture or substances for which it is issued. It shall

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

be renewed when substantial changes in the composition or production occur that bring about changes in the migration from the materials or articles or when new scientific data becomes available.

Article 16

Supporting documents

1 Appropriate documentation to demonstrate that the materials and articles, products from intermediate stages of their manufacturing as well as the substances intended for the manufacturing of those materials and articles comply with the requirements of this Regulation shall be made available by the business operator to the national competent authorities on request.

2 That documentation shall contain the conditions and results of testing, calculations, including modelling, other analysis, and evidence on the safety or reasoning demonstrating compliance. Rules for experimental demonstration of compliance are set out in Chapter V.

CHAPTER V

COMPLIANCE

Article 17

Expression of migration test results

1 To check the compliance, the specific migration values shall be expressed in mg/kg applying the real surface to volume ratio in actual or foreseen use.

2 By derogation from paragraph 1 for:

- a containers and other articles, containing or intended to contain, less than 500 millilitres or grams or more than 10 litres,
- b materials and articles for which, due to their form it is impracticable to estimate the relationship between the surface area of such materials or articles and the quantity of food in contact therewith,
- c sheets and films that are not yet in contact with food,
- d sheets and films containing less than 500 millilitres or grams or more than 10 litres,

the value of migration shall be expressed in mg/kg applying a surface to volume ratio of 6 dm² per kg of food.

This paragraph does not apply to plastic materials and articles intended to be brought into contact with or already in contact with food for infants and young children, as defined by Directives 2006/141/EC and 2006/125/EC.

3 By derogation from paragraph 1, for caps, gaskets, stoppers and similar sealing articles the specific migration value shall be expressed in:

- [^{F1}a mg/kg using the actual content of the container for which the closure is intended applying the total contact surface of sealing article and sealed container if the intended use of the article is known, while taking into account the provisions of paragraph 2;]
- b mg/article if the intended use of the article is unknown.

4 For caps, gaskets, stoppers and similar sealing articles the overall migration value shall be expressed in:

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

- a mg/dm² applying the total contact surface of sealing article and sealed container if the intended use of the article is known;
- b mg/article if the intended use of the article is unknown.

Textual Amendments

- F1** Substituted by [Commission Regulation \(EU\) 2016/1416 of 24 August 2016 amending and correcting Regulation \(EU\) No 10/2011 on plastic materials and articles intended to come into contact with food](#) (Text with EEA relevance).

Article 18

Rules for assessing compliance with migration limits

1 For materials and articles already in contact with food verification of compliance with specific migration limits shall be carried out in accordance with the rules set out in Chapter 1 of Annex V.

2 For materials and articles not yet in contact with food verification of compliance with specific migration limits shall be carried out in food or in food simulants set out in Annex III in accordance with the rules set out in Chapter 2, Section 2.1 of Annex V.

3 For materials and articles not yet in contact with food screening of compliance with the specific migration limit can be performed applying screening approaches in accordance with the rules set out in Chapter 2, Section 2.2 of Annex V. If a material or article fails to comply with the migration limits in the screening approach a conclusion of non-compliance has to be confirmed by verification of compliance in accordance with paragraph 2.

[^{F14} For materials and articles not yet in contact with food verification of compliance with the overall migration limit shall be carried out in food simulants as set out in Annex III in accordance with the rules set out in Chapter 3 of Annex V.]

5 For materials and articles not yet in contact with food screening of compliance with the overall migration limit can be performed applying screening approaches in accordance with the rules set out in Chapter 3, Section 3.4 of Annex V. If a material or article fails to comply with the migration limit in the screening approach a conclusion of non-compliance has to be confirmed by verification of compliance in accordance with paragraph 4.

6 The results of specific migration testing obtained in food shall prevail over the results obtained in food simulant. The results of specific migration testing obtained in food simulant shall prevail over the results obtained by screening approaches.

[^{F17} Before comparing specific and overall migration test results with the migration limits the correction factors set out in point 3 of Annex III and Chapter 4 of Annex V shall be applied in accordance with the rules set out therein.]

Textual Amendments

- F1** Substituted by [Commission Regulation \(EU\) 2016/1416 of 24 August 2016 amending and correcting Regulation \(EU\) No 10/2011 on plastic materials and articles intended to come into contact with food](#) (Text with EEA relevance).

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

Article 19

Assessment of substances not included in the Union list

Compliance with Article 3 of Regulation (EC) No 1935/2004 of substances referred to in Articles 6(1), 6(2), 6(4), 6(5) and 14(2) of this Regulation which are not covered by an inclusion in Annex I to this Regulation shall be assessed in accordance with internationally recognised scientific principles on risk assessment.

CHAPTER VI

FINAL PROVISIONS

Article 20

Amendments of EU acts

The Annex to Council Directive 85/572/EEC⁽¹⁸⁾ is replaced by the following:

‘The food simulants to be used for testing migration of constituents of plastic materials and articles intended to come into contact with a single food or specific groups of foods are set out in point 3 of Annex III to Commission Regulation (EU) No 10/2011.’

Article 21

Repeal of EU acts

Directives 80/766/EEC, 81/432/EEC, and 2002/72/EC are hereby repealed with effect from 1 May 2011.

References to the repealed Directives shall be construed as references to this Regulation and shall be read in accordance with the correlation tables in Annex VI.

Article 22

Transitional provisions

1 Until 31 December 2012 the supporting documents referred to in Article 16 shall be based on the basic rules for overall and specific migration testing set out in the Annex to Directive 82/711/EEC.

2 As from 1 January 2013 the supporting documents referred to in Article 16 for materials, articles and substances placed on the market until 31 December 2015, may be based on:

- a the rules for migration testing set out in Article 18 of this Regulation; or
- b the basic rules for overall and specific migration testing set out in the Annex to Directive 82/711/EEC.

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

3 As from 1 January 2016, the supporting documents referred to in Article 16 shall be based on the rules for migration testing set out in Article 18, without prejudice to paragraph 2 of this Article.

4 Until 31 December 2015 additives used in glass fibre sizing for glass fibre reinforced plastics which are not listed in Annex I have to comply with the risk assessment provisions set out in Article 19.

5 Materials and articles that have been lawfully placed on the market before 1 May 2011 may be placed on the market until 31 December 2012.

Article 23

Entry into force and application

This Regulation shall enter into force on the 20th day following its publication in the *Official Journal of the European Union*.

It shall apply from 1 May 2011.

The provision of Article 5 as regards the use of additives, others than plasticisers, shall apply for plastic layers or plastic coatings in caps and closures referred to in Article 2(1) (d), as from 31 December 2015.

The provision of Article 5 as regards the use of additives used in glass fibre sizing for glass fibre reinforced plastics, shall apply from 31 December 2015.

The provisions of Articles 18(2), 18(4) and 20 shall apply from 31 December 2012.

This Regulation shall be binding in its entirety and directly applicable in the Member States in accordance with the Treaties.

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

ANNEX I

Substances

1. Union list of authorised monomers, other starting substances, macromolecules obtained from microbial fermentation, additives and polymer production aids

Table 1 contains the following information:

Column 1 (FCM substance No): the unique identification number of the substance

Column 2 (Ref. No): the EEC packaging material reference number

Column 3 (CAS No): the Chemical Abstracts Service (CAS) registry number

Column 4 (Substance Name): the chemical name

Column 5 (Use as additive or polymer production aid (PPA) (yes/no)): an indication if the substance is authorised to be used as additive or polymer production aid (yes) or if the substance is not authorised to be used as additive or polymer production aid (no). If the substance is only authorised as PPA it is indicated (yes) and in the specifications the use is restricted to PPA.

Column 6 (Use as monomer or other starting substance or macromolecule obtained from microbial fermentation (yes/no)): an indication if the substance is authorised to be used as monomer or other starting substance or macromolecule obtained from microbial fermentation (yes) or if the substance is not authorised to be used as monomer or other starting substance or macromolecule obtained from microbial fermentation (no). If the substance is authorised as macromolecule obtained from microbial fermentation it is indicated (yes) and in the specifications it is indicated that the substance is a macromolecule obtained from microbial fermentation.

Column 7 (FRF applicable (yes/no)): an indication if for the substance the migration results can be corrected by the Fat Consumption Reduction Factor (FRF) (yes) or if they cannot be corrected by the FRF (no).

[^{F1}Column 8 (SML [mg/kg]): the specific migration limit applicable for the substance. It is expressed in mg substance per kg food. It is marked as ND ('not-detectable') if the substance is one in respect of which no migration is permitted, to be determined in accordance with Article 11(4).]

Column 9 (SML(T) [mg/kg] (group restriction No)): contains the identification number of the group of substances for which the group restriction in Column 1 in Table 2 of this Annex applies.

Column 10 (Restrictions and specifications): contains other restrictions than the specific migration limit specifically mentioned and it contains specifications related to the substance. In case detailed specifications are set out a reference to Table 4 is included.

Column 11 (Notes on verification of compliance): contains the Notes number which refers to the detailed rules applicable for verification of compliance for this substance included in Column 1 in Table 3 of this Annex.

If a substance appearing on the list as an individual compound is also covered by a generic term, the restrictions applying to this substance shall be those indicated for the individual compound.

[^{F4}.....]

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

TABLE 1

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
FCM substance No	Ref. No	CAS No	Substance name	Use as additive or polymer product aid (yes/no)	Use as monomer or other starting substance or macromolecule obtained from microbial fermentation (yes/no)	FRF applicable (no)	SML [mg/kg] (yes/no)	SML (T) [mg/kg] (Group restriction No)	Restrictions and specifications	Notes on certification of compliance
1	12310	0266309	albumin	no	yes	no				
2	12340	—	albumin coagulated by formaldehyde	no	yes	no				
3	12375	—	alcohols, aliphatic, monohydric, saturated, linear, primary (C ₄ -C ₂₂)	no	yes	no				
4	22332	—	mixture of (40 % w/w) 2,2,4-trimethylhexane-1,6-diisocyanate and (60 % w/w) 2,4,4-trimethylhexane-1,6-diisocyanate	no	yes	no		(17)	1 mg/kg in final product expressed as isocyanate moiety.	(10)
5	25360	—	trialkyl (C ₁₅) acetic acid, 2,3-epoxypropyl ester	no	yes	no	ND		1 mg/kg in final product expressed as epoxy group.	

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

									Molecular weight is 43 Da.	
6	25380	—	trialkyl acetic acid (C ₇ -C ₁₇), vinyl esters	no	yes	no	0,05			(1)
7	30370	—	acetylated acids, salts	yes	no	no				
8	30401	—	acetylated mono- and diglycerides of fatty acids	yes	no	no		(32)		
9	30610	—	acids, C ₂ -C ₂₄ , aliphatic, linear, monocarboxylic from natural oils and fats, and their mono-, di- and triglycerol esters (branched fatty acids at naturally occurring levels are included)	yes	no	no				
10	30612	—	acids, C ₂ -C ₂₄ ,	yes	no	no				

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

			aliphatic, linear, monocarboxylic, synthetic and their mono-, di- and triglycerol esters						
11	30960	—	acids, yes aliphatic, monocarboxylic (C ₆ - C ₂₂), esters with polyglycerol	no	no				
12	31328	—	acids, yes fatty, from animal or vegetable food fats and oils	no	no				
13	33120	—	alcohols, yes aliphatic, monohydric, saturated, linear, primary (C ₄ - C ₂₄)	no	no				
14	33801	—	n- alkyl(C ₁₀ - C ₁₃)benzenesulphonic acid	yes	no	no	30		
15	34130	—	alkyl, linear with even number of carbon atoms (C ₁₂ -	yes	no	yes	30		

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

			C ₂₀) dimethylamines						
16	34230	—	alkyl(C ₈ - C ₂₂)sulphonic acids	yes no	no	no	6		
17	34281	—	alkyl(C ₈ - C ₂₂)sulphuric acids, linear, primary with an even number of carbon atoms	yes no	no	no			
18	34475	—	aluminium calcium hydroxide phosphite, hydrate	yes no	no	no			
19	39090	—	N,N- bis(2- hydroxyethyl) alkyl(C ₈ - C ₁₈)amine	yes no	no	no		(7)	
20	39120	—	N,N- bis(2- hydroxyethyl) alkyl(C ₈ - C ₁₈)amine hydrochlorides	yes no	no	no		(7)	SML(T) expressed excluding HCl
21	42500	—	carbonic acid, salts	yes no	no	no			
22	43200	—	castor oil, mono- and diglycerides	yes no	no	no			
23	43515	—	chlorides of choline esters of coconut oil	yes no	no	no	0,9		(1)

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

			fatty acids							
24	45280	—	cotton fibers	yes	no	no				
25	45440	—	cresols, butylated, styrenated	yes	no	no	12			
26	46700	—	5,7-di-tert-butyl-3-(3,4- and 2,3-dimethylphenyl)-3H-benzofuran-2-one containing: a) 5,7-di-tert-butyl-3-(3,4-dimethylphenyl)-3H-benzofuran-2-one (80 to 100 % w/w) and b) 5,7-di-tert-butyl-3-(2,3-dimethylphenyl)-3H-benzofuran-2-one (0 to 20 % w/w)	yes	no	no	5			
27	48960	—	9,10-dihydroxy stearic acid and its oligomers	yes	no	no	5			
28	50160	—	di-n-octyltin bis(n-alkyl(C ₁₀ -C ₁₆) mercaptoacetate)	yes	no	no		(10)		

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

29	50360	—	di-n-octyltin bis(ethyl maleate)	yes	no	no		(10)		
30	50560	—	di-n-octyltin 1,4-butanediol bis(mercaptoacetate)	yes	no	no		(10)		
31	50800	—	di-n-octyltin dimaleate, esterified	yes	no	no		(10)		
32	50880	—	di-n-octyltin dimaleate, polymers (n = 2-4)	yes	no	no		(10)		
33	51120	—	di-n-octyltin thiobenzoate 2-ethylhexyl mercaptoacetate	yes	no	no		(10)		
34	54270	—	ethylhydroxyethylcellulose	yes	no	no				
35	54280	—	ethylhydroxypropylcellulose	yes	no	no				
36	54450	—	fats and oils, from animal or vegetable food sources	yes	no	no				
37	54480	—	fats and oils, hydrogenated, from animal or vegetable food sources	yes	no	no				

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

38	55520	—	glass fibers	yes	no	no				
39	55600	—	glass microballs	yes	no	no				
40	56360	—	glycerol esters with acetic acid	yes	no	no				
41	56486	—	glycerol esters with acids, aliphatic, saturated, linear, with an even number of carbon atoms (C ₁₄ -C ₁₈) and with acids, aliphatic, unsaturated, linear, with an even number of carbon atoms (C ₁₆ -C ₁₈)	yes	no	no				
42	56487	—	glycerol esters with butyric acid	yes	no	no				
43	56490	—	glycerol esters with	yes	no	no				

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

			erucic acid						
44	56495	—	glycerol esters with 12-hydroxystearic acid	yes	no	no			
45	56500	—	glycerol esters with lauric acid	yes	no	no			
46	56510	—	glycerol esters with linoleic acid	yes	no	no			
47	56520	—	glycerol esters with myristic acid	yes	no	no			
48	56535	—	glycerol esters with nonanoic acid	yes	no	no			
49	56540	—	glycerol esters with oleic acid	yes	no	no			
50	56550	—	glycerol esters with palmitic acid	yes	no	no			
51	56570	—	glycerol esters with propionic acid	yes	no	no			
52	56580	—	glycerol esters with ricinoleic acid	yes	no	no			

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

53	56585	—	glycerol esters with stearic acid	yes	no	no				
54	57040	—	glycerol monooleate, ester with ascorbic acid	yes	no	no				
55	57120	—	glycerol monooleate, ester with citric acid	yes	no	no				
56	57200	—	glycerol monopalmitate, ester with ascorbic acid	yes	no	no				
57	57280	—	glycerol monopalmitate, ester with citric acid	yes	no	no				
58	57600	—	glycerol monostearate, ester with ascorbic acid	yes	no	no				
59	57680	—	glycerol monostearate, ester with citric acid	yes	no	no				
60	58300	—	glycine, salts	yes	no	no				
62	64500	—	lysine, salts	yes	no	no				
63	65440	—	manganese pyrophosphate	yes	no	no				

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

64	66695	—	methylcellulose	yes	no	no			
65	67155	—	mixture of 4-(2-benzoxazolyl)-4-(5-methyl-2-benzoxazolyl)stilbene, 4,4'-bis(2-benzoxazolyl)stilbene and 4,4'-bis(5-methyl-2-benzoxazolyl)stilbene	yes	no	no			Not more than 0,05 % (w/w) (quantity of substance used/ quantity of the formulation). Mixture obtained from the manufacturing process in the typical ratio of (58-62 %): (23-27 %): (13-17 %).
66	67600	—	mono-n-octyltin tris(alkyl(C ₁₀ -C ₁₆) mercaptoacetate)	yes	no	no		(11)	
67	67840	—	montanic acids and/or their esters with ethyleneglycol and/or with 1,3-butanediol and/or with glycerol	yes	no	no			
68	73160	—	phosphoric acid, mono- and di-	yes	no	yes	0,05		

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

			n-alkyl (C ₁₆ and C ₁₈) esters						
69	74400	—	phosphoric acid, tris(nonyl- and/or dinonylphenyl) ester	yes	no	yes	30		
70	76463	—	polyacrylic acid, salts	yes	no	no		(22)	
71	76730	—	polydimethylsiloxane, γ- hydroxypropylated	yes	no	no	6		
72	76815	—	polyesters of adipic acid with glycerol or pentaerythritol, esters with even numbered, unbranched C ₁₂ - C ₂₂ fatty acids	yes	no	no		(32)	The fraction with molecular weight below 1 000 Da [^{F1} shall] not exceed 5 % (w/w)
73	76866	—	polyesters of 1,2- propanediol and/ or 1,3- and/ or 1,4- butanediol and/or polypropyleneglycol with adipic acid, which may be	yes	no	yes		(31) (32)	

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

			end-capped with acetic acid or fatty acids C ₁₂ -C ₁₈ or n-octanol and/or n-decanol						
74	77440	—	polyethylene glycol diricinoleate	yes	no	yes	42		
75	77702	—	polyethylene glycol esters of aliph. monocarb. acids (C ₆ -C ₂₂) and their ammonium and sodium sulphates	yes	no	no			
76	77732	—	polyethylene glycol (EO = 1-30, typically 5) ether of butyl 2-cyano 3-(4-hydroxy-3-methoxyphenyl) acrylate	yes	no	no	0,05		Only for use in PET
77	77733	—	polyethylene glycol (EO = 1-30, typically 5)	yes	no	no	0,05		Only for use in PET

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

			ether of butyl-2- cyano-3- (4- hydroxyphenyl) acrylate						
78	77897	—	polyethylene glycol (EO = 1-50) monoalkylether (linear and branched, C ₈ - C ₂₀) sulphate, salts	yes	no	5			
79	80640	—	polyoxyalkyl (C ₂ - C ₄) dimethylpolysiloxane	no	no				
80	81760	—	powders, flakes and fibres of brass, bronze, copper, stainless steel, tin, iron and alloys of copper, tin and iron	yes	no	no			
81	83320	—	propylhydroxyethylcellulose	yes	no				
82	83325	—	propylhydroxyethylcellulose	yes	no				
83	83330	—	propylhydroxypropylcellulose	yes	no				
84	85601	—	silicates, natural (with the exception	yes	no	no			

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

			of asbestos)						
85	85610	—	silicates, yes natural, silanated (with the exception of asbestos)	no	no				
86	86000	—	silicic acid, silylated	yes	no	no			
[^{F1} 87	86285		Silicon dioxide, silanated	yes	no	no			For synthetic amorphous silicon dioxide, silanated: primary particles of 1–100 nm which are aggregated to a size of 0,1–1 µm and may form agglomerates within the size distribution of 0,3 µm to the mm size.
88	86880	—	sodium monoalkyl dialkylphenoxybenzenedisulphonate	yes	no	no	9		
89	89440	—	stearic acid, esters	yes	no	no		(2)	

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

			with ethyleneglycol						
90	92195	—	taurine, salts	yes	no	no			
91	92320	—	tetradecyl polyethyleneglycol ether of glycolic acid	yes	no	yes	15		
92	93970	—	tricyclohexane bis(hexahydrophthalate)	yes	no	no	0,05		
93	95858	—	waxes, paraffinic, refined, derived from petroleum based or synthetic hydrocarbon feedstocks, low viscosity	yes	no	no	0,05		Not to be used for articles in contact with fatty foods for which [F1simulant D1 and/ or D2] is laid down. Average molecular weight not less than 350 Da. Viscosity at 100 °C not less than 2,5 cSt (2,5 × 10 ⁻⁶ m ² /s).

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

									Content of hydrocarbons with Carbon number less than 25, not more than 40 % (w/w).
94	95859	—	waxes, refined, derived from petroleum based or synthetic hydrocarbon feedstocks, high viscosity	yes	no	no			Average molecular weight not less than 500 Da. Viscosity at 100 °C not less than 11 cSt ($11 \times 10^{-6} \text{ m}^2/\text{s}$). Content of mineral hydrocarbons with Carbon number less than 25, not more than 5 % (w/w).
95	95883	—	white mineral oils, paraffinic, derived from	yes	no	no			Average molecular weight not less than

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

			petroleum based hydrocarbon feedstocks						480 Da. Viscosity at 100 °C not less than 8,5 cSt ($8,5 \times 10^{-6} \text{ m}^2/\text{s}$). Content of mineral hydrocarbons with Carbon number less than 25, not more than 5 % (w/w).
96	95920	—	wood flour and fibers, untreated	yes	no	no			
97	72081/10	—	petroleum hydrocarbon resins (hydrogenated)	yes	no	no			Petroleum hydrocarbon resins, hydrogenated are produced by the catalytic or thermal polymerisation of dienes and olefins of the aliphatic, alicyclic and/or monobenzenoidarylalkene types

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

								from distillates of cracked petroleum stocks with a boiling range not greater than 220 °C, as well as the pure monomers found in these distillation streams, subsequently followed by distillation, hydrogenation and additional processing. Properties: — Viscosity at 120 °C: > 3 Pa.s, — Softening point: > 95 °C as determined by ASTM Method E 28-67, — Bromine number: < 40
--	--	--	--	--	--	--	--	---

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

110	93520	0000059e02-9 00101914e0pherol	yes	no	no				
111	53600	0000060e04-benediaminetetraacetic acid	no	no	no				
112	64015	0000060133-13 acid	yes	no	no				
113	16780	0000064e17-5ol	yes	yes	no				
	52800								
114	55040	0000064f18-6c acid	yes	no	no				
115	10090	0000064a09-7 acid	yes	yes	no				
	30000								
116	13090	0000065b81-0 acid	yes	yes	no				
	37600								
117	21550	0000067e61-1 nol	no	yes	no				
118	23830	0000067263-0 propanol	yes	yes	no				
	81882								
119	30295	0000067a64-1 ne	yes	no	no				
120	49540	0000067d68-2 ethylsulphoxide	yes	no	no				
121	24270	0000069a7e-7 acid	yes	yes	no				
	84640								
122	23800	0000071123-8 propanol	no	yes	no				
123	13840	0000071136-3 butanol	no	yes	no				
124	22870	0000071141-0 pentanol	no	yes	no				
125	16950	0000074e85-1 lene	no	yes	no				
126	10210	0000074a86-2 lene	no	yes	no				
127	26050	0000075v01-4 chloride	no	yes	no	ND			1 mg/ kg in final product
128	10060	0000075a07-0 aldehyde	yes	no	no		(1)		
129	17020	0000075e21-2 oxide	no	yes	no	ND			1 mg/ kg in final product (10)

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

130	26110	0000075354	1,1-dichloroethane	yes	no	ND			(1)
131	48460	0000075137-6	1,1-difluoroethane	yes	no	no			
132	26140	0000075387	1,1-difluoroethane	yes	no	5			
133	14380	0000075446	1,1-dichloroethane	yes	no	ND		1 mg/kg in final product	(10)
	23155								
134	43680	0000075456	1,1-difluoroethane	no	no	6		Content of chlorofluoromethane less than 1 mg/kg of the substance	
135	24010	0000075569	propylene oxide	yes	no	ND		1 mg/kg in final product	
136	41680	0000076222	phosphoric acid	yes	no	no			(3)
137	66580	0000077262-3	2,2-bis[4-(1-methyl-6-(1-methylcyclohexyl)phenyl)phenyl]propane	yes	no	yes			(5)
138	93760	0000077407	butyl acetyl citrate	yes	no	no			(32)
139	14680	0000077929	citric acid	yes	yes	no			
	44160								
140	44640	0000077930	citric acid, triethyl ester	yes	no	no			(32)
141	13380	0000077499-6	1,1,1-trimethylolpropane	yes	yes	no	6		
	25600								
	94960								
142	26305	0000078087	triethoxysilane	yes	no	0,05		Only to be	[F ¹⁰ (1)]

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

									used as a surface treatment agent
143	62450	000007815-7	hexane	yes	no	no			
144	19243	0000078279-5	methyl-1,3-butadiene	no	yes	no	ND		1 mg/kg in final product
	21640								
145	10630	000007906	acrylamide	no	yes	no	ND		
146	23890	000007909	acrylic acid	no	yes	no			
	82000								
147	10690	000007909	acrylic acid	no	yes	no		(22)	
148	14650	000007918	perfluorohydrocarbon	no	yes	no	ND		(1)
149	19990	000007930	methacrylamide	no	yes	no	ND		
150	20020	000007944	methacrylic acid	no	yes	no		(23)	
[^{F7} 151]	13480	000008025	bis(4-hydroxyphenyl)propane	no	yes	no	0,05		Not to be used for the manufacture of polycarbonate infant feeding bottles ^g . Not to be used for the manufacture of polycarbonate drinking cups or bottles which, due to their spill proof characteristics, are
	13607]								

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

										final product.
158	23380	0000085	phthalic anhydride	yes	yes	no				
	76320									
159	74560	0000085	phthalic acid, benzyl butyl ester	yes	no	no	30	(32)	Only to be used as: (a) (b)	(7) plasticiser in repeated use materials and articles; plasticiser in single-use materials and articles contacting non-fatty foods except for infant formulae and follow-on formulae as defined by Directive 2006/141/EC or processed cereal-based foods and baby foods for infants and

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

									(c)	young children as defined by Directive 2006/125/EC; technical support agent in concentrations up to 0,1 % in the final product.
160	84800	0000087	salicylic acid, 4-tert-butylphenyl ester	yes	no	yes	12			
[^{F11} 161	92160	000087	(4)-tartaric acid	yes	no	no]
162	65520	0000087	nitro	yes	no	no				
163	66400	0000088	2,2'-methylene bis(4-ethyl-6-tert-butylphenol)	yes	no	yes	(13)			
164	34895	0000088	2,6-aminobenzamide	yes	no	no	0,05			Only for use in PET for water and beverages
165	23200 74480	0000088	99-3 phthalic acid	yes	yes	no				
166	24057	0000089	3,7-phthalic anhydride	yes	yes	no	0,05			

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

167	25240	000009	1208-7 toluene diisocyanate	no	yes	no		(17)	1 mg/ kg in final product expressed as isocyanate moiety	(10)
168	13075 15310	000009	1274-9 diamino-6- phenyl-1,3,5- triazine	no	yes	no	5			[^{F10} (1)]
169	16240	000009	1397-4 dimethyl-4,4'- diisocyanatobiphenyl	no	yes	no		(17)	1 mg/ kg in final product expressed as isocyanate moiety	(10)
170	16000	000009	2488-6 dihydroxybiphenyl	no	yes	no	6			
171	38080	000009	3588-3 benzoic acid, methyl ester	yes	no	no				
172	37840	000009	3589-0 benzoic acid, ethyl ester	yes	no	no				
173	60240	000009	4413-3 hydroxybenzoic acid, propyl ester	yes	no	no				
174	14740	000009	5648-7 cresol	no	yes	no				
175	20050	000009	60516 methacrylic acid, allyl ester	no	yes	no	0,05			
176	11710	000009	60516 acrylic acid, methyl ester	no	yes	no		(22)		
177	16955	000009	60516 ethylene carbonate	no	yes	no	30		SML expressed	

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

									as ethyleneglycol. Residual content of 5 mg ethylene carbonate per kg of hydrogel with max 10 g of hydrogel in contact with 1 kg of food.
178	92800	000009	649-5 thiobis(6-tert-butyl-3-methylphenol)	yes	no	yes	0,48		
179	48800	000009	722-4 dihydroxy-5,5'-dichlorodiphenylmethane	yes	no	yes	12		
[^{F12} 180	17160	000009	753-0 phenol	no	yes	no		(33)	I
181	20890	000009	763-2 acrylic acid, ethyl ester	no	yes	no		(23)	
182	19270	000009	765-4 acrylic acid	no	yes	no			
183	21010	000009	784-9 acrylic acid, isobutyl ester	no	yes	no		(23)	
184	20110	000009	788-1 acrylic acid, butyl ester	no	yes	no		(23)	
185	20440	000009	790-5 acrylic acid, diester	no	yes	no	0,05		

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

			with ethyleneglycol						
186	14020	00000984564	4-butylphenol	no	yes	no	0,05		
187	22210	0000098683-9	methylstyrene	no	yes	no	0,05		
188	19180	00000991608	phthalic acid dichloride	no	yes	no		(27)	
189	60200	0000099476-3	hydroxybenzoic acid, methyl ester	yes	no	no			
190	18880	0000099996-7	hydroxybenzoic acid	no	yes	no			
191	24940	00001001009	phthalic acid dichloride	no	yes	no		(28)	
192	23187	—	phthalic acid	no	yes	no		(28)	
193	24610	0000100542-5	styrene	no	yes	no			
194	13150	0000100517-6	benzyl alcohol	no	yes	no			
195	37360	0000100552-7	benzaldehyde	no	no	no			(3)
196	18670	0000100607-0	hexamethylene tetramine	no	no	no		(15)	
	59280								
197	20260	00001014319	methacrylic acid, cyclohexyl ester	no	yes	no	0,05		
198	16630	00001014688	4,4'-methylenediphenyl diisocyanate	no	no	no		(17)	1 mg/kg in final product expressed as isocyanate moiety (10)
199	24073	00001019006	1,6-hexanediol diglycidyl ether	no	yes	no	ND		Not to be used for articles (8)

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

									in contact with fatty foods for which [F ¹ simulant D1 and/or D2] is laid down. For indirect food contact only, behind a PET layer.
200	51680	000010220819	diphenylthiourea	yes	no	yes	3		
201	16540	000010220910	diphenyl carbonate	no	yes	no	0,05		
202	23070	000010221316	phenylenedioxydiacetic acid	no	yes	no	0,05		[F ¹⁰ (1)]
203	13323	000010221419	bis(2-hydroxyethoxy)benzene	no	yes	no	0,05		
204	25180	000010226013	'N'-tetrakis(2-hydroxypropyl)ethylenediamine	yes	yes	no			
	92640								
205	25385	000010227015	ethylamine	yes	no				40 mg/kg hydrogel at a ratio of 1 kg food to a maximum of 1,5 grams of hydrogel.

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

									Only to be used in hydrogels intended for non-direct food contact use.
206	11500	0000103	adipic acid, 2-ethylhexyl ester	no	yes	no	0,05		
207	31920	0000103	adipic acid, bis(2-ethylhexyl) ester	yes	no	yes	18	(32)	(2)
208	18898	0000103	4-(4-hydroxyphenyl) acetamide	no	yes	no	0,05		
209	17050	0000104	276-7 ethyl-1-hexanol	no	yes	no	30		
210	13390 14880	0000105	408-8 bis(hydroxymethyl)cyclohexane	no	yes	no			
211	23920	0000105	384-1 acrylic acid, vinyl ester	no	yes	no		(1)	
212	14200 41840	0000105	602-1 lactam	yes	yes	no		(4)	
213	82400	0000105	162-4 propyleneglycol dioleate	yes	no	no			
214	61840	0000106	124-9 hydroxystearic acid	yes	no	no			
215	14170	0000106	adipic anhydride	no	yes	no			
216	14770	0000106	44-5 cresol	no	yes	no			

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

217	15565	0000106144-7	no dichlorobenzene	yes	no	12			
218	11590	000010663-8	no acetic acid, isobutyl ester	yes	no		(22)		
219	14570	000010680-8	no ethylene glycol	yes	no	ND		1 mg/ kg in final product	(10)
	16750								
220	20590	000010691-2	no acrylic acid, 2,3-epoxypropyl ester	yes	no	0,02			(10)
221	40570	000010697-8	no toluene	yes	no	no			
222	13870	0000106198-9	no butene	yes	no				
223	13630	000010699-1	no butadiene	yes	no	ND		1 mg/ kg in final product	
224	13900	0000107201-7	no butene	yes	no				
225	12100	000010721-1	no acrylonitrile	yes	no	ND			
226	15272	000010725-2	no ethylbenzene	yes	no	12			
	16960								
227	16990	000010727-4	no ethylene glycol	yes	no		(2)		
	53650								
228	13690	0000107183-0	no butanediol	yes	no				
229	14140	0000107502-6	no cyclohexane	yes	no				
230	16150	000010840-1	no ethylenediamine	yes	no	18			
231	10120	000010805-4	no acetic acid, vinyl ester	yes	no	12			
232	10150	000010824-7	yes anhydride	yes	no				
	30280								
233	24850	000010830-5	no anhydride	yes	no				

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

234	19960	00001083166	maleic anhydride	no	yes	no		(3)		
235	14710	00001083794	2,4-cresol	no	yes	no				
[^{F3} 236]	23050	00001084452	4,4'-phenylenediamine	no	yes	no	ND			(28)]
237	15910	00001084463	2,4-dihydroxybenzene	no	yes	no	2,4			
	24072									
238	18070	00001085544	glutaric anhydride	no	yes	no				
[^{F13} 239]	19975	00001082746	2,4,6-triamino-1,3,5-triazine	yes	yes	no	2,5			
	25420									
	93720]									
240	45760	00001089118	hexamethylenediamine	no	no	no				
[^{F11} 241]	22960	00001089521	phenol	no	yes	no	3]
242	85360	00001094948	sebacic acid, dibutyl ester	yes	no	no		(32)		
243	19060	00001095357	isobutyl vinyl ether	no	yes	no	0,05			(10)
244	71720	00001096610	pentane	yes	no	no				
245	22900	00001094671	1-pentene	no	yes	no	5			
246	25150	00001094909	2,5-dihydrofuran	yes	yes	no	0,6			
247	24820	00001105566	suberic acid	yes	yes	no				
	90960									
248	19540	00001104167	maleic acid	yes	yes	no		(3)		
	64800									
249	17290	00001104178	fumaric acid	yes	yes	no				
	55120									
250	53520	00001103305	N,N'-ethylenebisstearamide	yes	no	no				
251	53360	00001103306	N,N'-ethylenebisoleamide	yes	no	no				
252	87200	00001104416	sebacic acid	yes	no	no				

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

253	15250	0000110160-1	no	yes	no				
			diaminobutane						
254	13720	0000110164-4	yes	yes	no		(30)		
	40580		butanediol						
255	25900	0000110188-3	no	yes	no	5			
			hexane						
256	18010	0000110194-1	yes	yes	no				
	55680		glutaric acid						
[^{F12} 257	13550	0000110198-5	yes	yes	no				
	16660	0025265-71-8							
	51760	I							
			propylene glycol						
258	70480	0000111008-1	yes	no	no				
			palmitic acid, butyl ester						
259	58720	0000111018-1	yes	no	no				
			heptanoic acid						
260	24280	0000111020-1	no	yes	no				
			sebacic acid						
261	15790	0000111040-1	yes	yes	no	5			
			dodecyltrimethylamine						
262	35284	0000111042-1	yes	no	no	0,05			
			N-(2-aminoethyl)ethanolamine						Not to be used for articles in contact with fatty foods for which [^{F1} simulant D1 and/or D2] is laid down. For indirect food contact only, behind a PET layer.

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

263	13326	0000111466-0	1466-0 ethylene glycol	yes	yes	no		(2)		
	15760									
	47680									
264	22660	0000111466-0	1466-0 octene	no	yes	no	15			
265	22600	0000111487-5	1487-5 octanol	no	yes	no				
266	25510	0000112477-6	1477-6 ethylene glycol	yes	yes	no				
	94320									
267	15100	0000112430-1	1430-1 decanol	no	yes	no				
268	16704	0000112441-4	1441-4 dodecene	no	yes	no	0,05			
269	25090	0000112607-7	1607-7 ethylene glycol	yes	yes	no				
	92350									
270	22763	0000112861-8	1861-8 acid	yes	yes	no				
	69040									
271	52720	0000112845-5	1845-5 amides	no	yes	no				
272	37040	0000112856-6	1856-6 acid	yes	yes	no				
273	52730	0000112867-7	1867-7 acid	yes	yes	no				
274	22570	0000112069-9	1069-9 cycloisocyanate	yes	yes	no		(17)	1 mg/ kg in final product expressed as isocyanate moiety	(10)
275	23980	0000115007-7	1507-7 polyene	no	yes	no				
276	19000	0000115147-7	1547-7 isobutene	no	yes	no				
277	18280	0000115127-7	1527-7 chloroendomethylenetetrahydrophthalic anhydride	yes	yes	no				
278	18250	0000115128-8	1528-8 chloroendomethylenetetrahydrophthalic acid	yes	yes	no				
279	22840	0000115077-7	1577-7 acrylonitril	yes	yes	no				
	71600									
280	73720	0000115968-8	1968-8 phosphonic acid,	no	yes	no	ND			

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

			trichloroethyl ester						
281	25120	000011644-1	hexafluoromethylene	yes	no	0,05			
282	18430	000011645-1	hexafluoropropylene	yes	no	ND			
283	74640	000011731-1	phthalic acid, bis(2-ethylhexyl) ester	yes	no	1,5	(32)	Only to be used as: (a) (b)	(7) plasticiser in repeated use materials and articles contacting non-fatty foods; technical support agent in concentrations up to 0,1 % in the final product.
284	84880	000011935-1	salicylic acid, methyl ester	yes	no	30			
285	66480	000011947-1	methylene bis(4-methyl-6-tert-butylphenol)	yes	no	yes	(13)		
286	38240	000011962-1	benzophenone	no	yes	0,6			
287	60160	000012044-8	hydroxybenzoic acid, ethyl ester	yes	no	no			

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

288	24970	00001206	terephthalic acid, dimethyl ester	yes	no				
289	15880 24051	00001204	1,2-dihydroxybenzene	no	yes	no	6		
290	55360	00001219	terephthalic acid, propyl ester	yes	no	no		(20)	
291	19150	00001215	isophthalic acid	yes	no			(27)	
292	94560	00001224	2,2,4,4-tetrahydro-3H-pyridin-3-one	no	yes	no	5		
293	23175	00001225	phosphonic acid, triethyl ester	yes	no	no	ND		1 mg/kg in final product (1)
294	93120	00001234	2,2-dipropionic acid, didodecyl ester	no	yes			(14)	
295	15940 18867 48620	00001234	1,2-dihydroxybenzene	yes	yes	no	0,6		
296	23860	00001233	propanal	yes	no				
297	23950	00001236	propanoic anhydride	no	yes	no			
298	14110	00001235	2-oxopropanal	yes	no				
299	63840	00001235	butyric acid	yes	no	no			
300	30045	00001238	butyric acid, butyl ester	yes	no	no			
301	89120	00001235	butyric acid, butyl ester	yes	no	no			
302	12820	00001239	acetic acid	no	yes	no			
303	12130 31730	00001241	acetic acid	yes	yes	no			

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

304	14320	0000124007-2	407-2 polylic acid	yes	yes	no			
	41960								
305	15274	0000124004-4	409-4 methylenediamine	yes	no	no	2,4		
	18460								
306	88960	0000124006-5	406-5 amides	yes	no	no			
307	42160	0000124010-0	410-0 carbon dioxide	yes	no	no			
308	91200	0000126013-6	613-6 sucrose acetate isobutyrate	yes	no	no			
309	91360	0000126017-7	617-7 sucrose octaacetate	yes	no	no			
310	16390	0000126232-7	623-7 dimethyl-1,3-propanediol	no	yes	no	0,05		
	22437								
311	16480	0000126050-9	650-9 D-glucitol	yes	yes	no			
	51200								
312	21490	0000126081-7	681-7 acrylonitrile	yes	yes	no	ND		
313	16650	0000127063-0	763-0 phenylsulphone	yes	yes	no	3		
	51570								
314	23500	0000127091-3	791-3 pinene	no	yes	no			
315	46640	0000128236-0	823-0 tert-butyl-p-cresol	yes	no	no	3		
316	23230	0000131017-0	117-0 phthalic acid, diallyl ester	no	yes	no	ND		
317	48880	0000131253-3	125-3 dihydroxy-4-methoxybenzophenone	yes	no	yes	(8)		
318	48640	0000131256-6	125-6 dihydroxybenzophenone	yes	no	no	(8)		
319	61360	0000131257-7	125-7 hydroxy-4-methoxybenzophenone	yes	no	yes	(8)		
320	37680	0000136007-0	607-0 benzoic acid,	yes	no	no			

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

			butyl ester						
321	36080	0000137	666-6 butyl palmitate	yes	no	no			
322	63040	0000138	22-7 lauric acid, butyl ester	yes	no	no			
323	11470	0000140	88-5 lauric acid, ethyl ester	no	yes	no		(22)	
324	83700	0000141	22-0 lauric acid	yes	no	yes	42		
325	10780	0000141	32-1 lauric acid, n-butyl ester	no	yes	no		(22)	
326	12763 35170	0000141	243-5 aminoethanol	yes	yes	no	0,05		Not to be used for articles in contact with fatty foods for which [F1simulant D1 and/ or D2] is laid down. For indirect food contact only, behind a PET layer.
327	30140	0000141	78-6 lauric acid, ethyl ester	yes	no	no			

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

328	65040	000014182-2	phenolic acid	yes	no	no			
329	59360	000014262-2	salicylic acid	yes	no	no			
330	19470	000014310-7	acetic acid	yes	yes	no			
	63280								
331	22480	000014310-8	nonanol	no	yes	no			
332	69760	000014328-2	ethyl alcohol	yes	no	no			
333	22775	000014462-7	acetic acid	yes	yes	no	6		
	69920								
334	17005	000015164-4	benzoin	yes	no	no	ND		
335	68960	000030102-0	amide	yes	no	no			
336	15095	000033448-5	decanoic acid	yes	yes	no			
	45940								
337	15820	000034549-6	difluorobenzophenone	no	yes	no	0,05		
338	71020	000037340-3	salicylic acid	yes	no	no			
339	86160	000040951-2	silicon carbide	yes	no	no			
[^{F14} 340	47440	000046158-5	diacrylamide	no	no	no	60]
341	13180	000049866-8	hept-2-ene	no	yes	no	0,05		
	22550								
342	14260	000050249-3	lactone	yes	no	no	(29)		
343	23770	000050413-2	propanediol	no	yes	no	0,05		
[^{F11} 344	13810	000050516-7	butanediol formal	no	yes	no	0,05	15 30	(21)
	21821]								
345	35840	000050630-9	acetic acid	yes	no	no			
346	10030	000051440-6	acetic acid	no	yes	no			
347	13050	000052844-0	lactic acid	no	yes	no	(21)		
	25540								

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

348	22350	0000544	163-8 phthalic acid	yes	yes	no			
	67891								
349	25550	0000552	10-7 phthalic anhydride	no	yes	no		(21)	
350	63920	0000557	159-5 phthalic acid	yes	no	no			
351	21730	0000563	345-1 methyl-1- butene	no	yes	no	ND		Only to be used in polypropylene (1)
352	16360	0000576	226-1 dimethylphenol	no	yes	no	0,05		
353	42480	0000584	101-8 phthalic acid, rubidium salt	yes	no	no	12		
354	25210	0000584	284-9 toluene diisocyanate	no	yes	no		(17)	1 mg/kg in final product expressed as isocyanate moiety (10)
355	20170	0000585	0716 acrylic acid, tert- butyl ester	yes	yes	no		(23)	
356	18820	0000592	141-6 hexene	no	yes	no	3		
357	13932	0000598	332-3 buten-2- ol	no	yes	no	ND		Only to be used as a co-monomer for the preparation of polymeric additive (1)
358	14841	0000599	464-4 cumylphenol	no	yes	no	0,05		

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

359	15970	000061149-4	yes	yes	no	(8)		
	48720		dihydroxybenzophenone					
360	57920	000062057-7	yes	no	no			
			glycerol triheptanoate					
361	18700	000062911-8	no	yes	no	0,05		
			hexanediol					
362	14350	000063048-0	no	yes	no			
			carbon monoxide					
363	16450	000064610-0	no	yes	no	5		
			dioxolane					
[^{F11} 364	15404	000065217-3,6-	no	yes	no	5		Only to be used as: (a) a co-monomer in poly(ethylene-co-isorbide terephthalate); (b) a co-monomer at levels of up to 40 mole % of the diol component in combination with ethylene glycol and/or 1,4-bis(hydroxymethyl)cyclohexane for the production
			dianhydrosorbitol					

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

									final product expressed as isocyanate moiety
373	22390	0000840265-3	naphthalenedicarboxylic acid, dimethyl ester	no	yes	no	0,05		
374	21190	0000868771-6	acrylic acid, monoester with ethyleneglycol	no	yes	no		(23)	
375	15130	0000872405-9	decene	no	yes	no	0,05		
[^{F13} 376]	66905	0000872450-4	methylpyrrolidone	yes	no	no	60]
377	12786	0000919330-2	aminopropyltriethoxysilane	no	yes	no	0,05		Residual extractable content of 3-aminopropyltriethoxysilane to be less than 3 mg/kg filler when used for the reactive surface treatment of inorganic fillers. SML = 0,05 mg/kg when used for the surface treatment of

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

									materials and articles.
378	21970	0000923	202-4 methylmethacrylamide	no	yes	no	0,05		
379	21940	0000924	442-5 methylolacrylamide	no	yes	no	ND		
380	11980	0000925	601-6 acrylic acid, propyl ester	no	yes	no		(22)	
381	15030	0000931	881-4 decane	yes	no	no	0,05		Only to be used in polymers contacting foods for which simulant A is laid down
382	19490	0000947	104-6 lactam	yes	no	no	5		
383	72160	0000948	265-2 phenylindole	yes	no	yes	15		
384	40000	0000991	1284-4 bis(octylmercapto)-6-(4-hydroxy-3,5-di-tert-butylanilino)-1,3,5-triazine	yes	no	yes	30		
385	11530	0000999	601-6 acrylic acid, 2-hydroxypropyl ester	no	yes	no	0,05		SML (1) expressed as the sum of acrylic acid, 2-hydroxypropyl ester and acrylic acid, 2-

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

									hydroxyisopropyl ester. It may contain up to 25 % (m/m) of acrylic acid, 2-hydroxyisopropyl ester (CAS No 0002918-23-2).	
386	55280	0001034	4011-4 allilic acid, octyl ester	yes	no	no		(20)		
387	26155	0001072	163-5 vinylimidazole	no	yes	no	0,05			[^{F10} (1)]
388	25080	0001120	436-1 tetradecene	no	yes	no	0,05			
389	22360	0001141	238-4 naphthalenedicarboxylic acid	no	yes	no	5			
390	55200	0001166	5215 acid, dodecyl ester	yes	no	no		(20)		
[^{F1} 391	22932	0001187	035 perfluoromethyl perfluorovinyl ether	yes	no	no	0,05		Only to be used in: — —] anti-stick coatings; fluoro- and perfluoropolymers intended for repeated use applications where the contact ratio

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

									is 1 dm ² surface in contact with at least 150 kg food.
392	72800	0001241	Phosphoric acid, diphenyl 2-ethylhexyl ester	no	yes	2,4			
393	37280	0001302	2,2,4,4-tetranitroethane	yes	no	no			
394	41280	0001305	5,6-Di- <i>n</i> -butyl-2,2,4,4-tetrahydroxide	yes	no	no			
395	41520	0001305	5,6-Di- <i>n</i> -butyl-2,2,4,4-tetrahydroxide	yes	no	no			
396	64640	0001309	4,8-Di- <i>n</i> -butyl-2,2,4,4-tetrahydroxide	yes	no	no			
397	64720	0001309	4,8-Di- <i>n</i> -butyl-2,2,4,4-tetrahydroxide	yes	no	no			
[^{F3} 398	35760	0001309	antimony trioxide	yes	no	no			(6)]
399	81600	0001310	5,8-Di- <i>n</i> -butyl-2,2,4,4-tetrahydroxide	yes	no	no			
400	86720	0001310	5,8-Di- <i>n</i> -butyl-2,2,4,4-tetrahydroxide	yes	no	no			
401	24475	0001313	8,8-Di- <i>n</i> -butyl-2,2,4,4-tetrahydroxide	no	yes	no			
402	96240	0001314	zinc oxide	yes	no	no			
403	96320	0001314	zinc sulphide	yes	no	no			
404	67200	0001317	1,3,5-Tricyanodisulphide	yes	no	no			
405	16690	0001321	divinylbenzene	yes	no	ND		SML (1) expressed as the sum of divinylbenzene	

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

										and ethylvinylbenzene. It may contain up to 45 % (m/m) of ethylvinylbenzene.
406	83300	0001323432-3	propyleneglycol monostearate	yes	no	no				
407	87040	0001330561-4	sodium tetraborate	yes	no	no	(16)			
408	82960	0001330482-9	propyleneglycol monooleate	yes	no	no				
409	62240	0001332137-2	zinc oxide	yes	no	no				
[F11]410	62720	0001332158-7	zinc oxide	yes	no	no				Particles] can be thinner than 100 nm only if incorporated at a quantity of less than 12 % w/w in an ethylene vinyl alcohol copolymer (EVOH) inner layer of a multi-layer structure, in which the layer in direct

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

								contact with the food provides a functional barrier preventing migration of particles into the food.
411	42080	0001333	carbon black	yes	no	no		Primary particles of 10 – 300 nm which are aggregated to a size of 100 – 1 200 nm which may form agglomerates within the size distribution of 300 nm – mm. Toluene extractables: maximum 0,1 %, determined according to ISO method 6209. UV absorption of cyclohexane extract

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

									at 386 nm: < 0,02 AU for a 1 cm cell or < 0,1 AU for a 5 cm cell, determined according to a generally recognised method of analysis. Benzo(a)pyrene content: max 0,25 mg/ kg carbon black. Maximum use level of carbon black in the polymer: 2,5 % w/w.
412	45200	0001335	2350 copper iodide	yes	no	no	(6)		
413	35600	0001336	2116 antimony hydroxide	yes	no	no			
414	87600	0001338	0512 sorbitan monolaurate	yes	no	no			
415	87840	0001338	0118 sorbitan monostearate	yes	no	no			
416	87680	0001338	0118 sorbitan monooleate	yes	no	no			
417	85680	0001343	1812 sulfuric acid	yes	no	no			

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

418	34720	00013444	28-11-1990	Aluminium oxide	yes	no	no			
419	92150	00014016	15-11-1990	Formic acids	yes	no	no			According to the JECFA specifications
420	19210	00014591	03-11-1990	Phthalic acid, dimethyl ester	no	yes	no	0,05		
[F14]421	13000	00014774	15-11-1990	benzenedimethanamine	no	yes	no		(34)	I
422	38515	00015334	15-11-1990	bis(2-benzoxazolyl)stilbene	yes	no	yes	0,05		(2)
423	22937	00016233	05-11-1990	Fluoropropylperfluorovinyl ether	no	yes	no	0,05		
424	15070	00016471	16-11-1990	decadiene	no	yes	no	0,05		
425	10840	00016633	16-11-1990	Acrylic acid, tert-butyl ester	no	yes	no		(22)	
426	13510	00016752	17-11-1990	bis(4-hydroxyphenyl)propane	no	yes	no			In compliance with Commission Regulation (EC) No 1895/2005 ^a
	13610			bis(2,3-epoxypropyl) ether						
427	18896	00016794	15-11-1990	(hydroxymethyl)-1-cyclohexene	no	yes	no	0,05		
428	95200	00017091	17-11-1990	2,4,6-trimethyl-2,4,6-tris(3,5-di-tert-butyl-4-hydroxybenzyl)benzene	yes	no	no			
429	13210	00017615	15-11-1990	(4-aminocyclohexyl)methane	no	yes	no	0,05		
430	95600	00018431	08-11-1990	tris(2-methyl-4-	yes	no	yes	5		

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

			hydroxy-5-tert-butylphenyl)butane						
431	61600	0001843205-6	hydroxy-4-n-octyloxybenzophenone	yes	no	yes		(8)	
432	12280	0002035475-8	anhydride	no	yes	no			
433	68320	0002082670-1	3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate	yes	no	yes	6		
434	20410	0002082841-7	acrylic acid, diester with 1,4-butanediol	yes	yes	no	0,05		
435	14230	0002123641-0	lactam, sodium salt	yes	yes	no		(4)	
436	19480	0002146471-6	acid, vinyl ester	no	yes	no			
437	11245	0002156607-1	acid, dodecyl ester	no	yes	no	0,05		(2)
[^{F13} 438	13303	0002162574-5	diisopropylphenyl)carbodiimide	no	yes	no	0,05		Expressed as the sum of bis(2,6-diisopropylphenyl)carbodiimide and its hydrolysis product 2,6-diisopropylaniline
439	21280	0002177761-0	acrylic acid, phenyl ester	yes	yes	no		(23)	

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

440	21340	00022102818	methacrylic acid, propyl ester	yes	no		(23)		
441	38160	00023156876	benzoic acid, propyl ester	yes	no	no			
442	13780	0002425174-8	butanediol bis(2,3-epoxypropyl)ether	no	yes	no	ND	Residual content = 1 mg/kg in final product expressed as epoxygroup. Molecular weight is 43 Da.	(10)
443	12788	0002432199-7	aminoundecanoic acid	no	yes	no	5		
444	61440	00024402224	hydroxy-5'-methylphenyl)benzotriazole	yes	no	no		(12)	
445	83440	0002466093	phosphoric acid	yes	no	no			
446	10750	0002495254	acrylic acid, benzyl ester	no	yes	no		(22)	
447	20080	00024952716	methacrylic acid, benzyl ester	yes	no			(23)	
448	11890	00024992504	acrylic acid, n-octyl ester	no	yes	no		(22)	
[^{F12} 449	49840	0002500488	thiobis(2-ethyl)disulphide	no	yes	0,05			1
450	24430	0002561888	basic anhydride	no	yes	no			

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

451	66755	0002682	220-4	yes	no	no	0,5		Only to be used in aqueous polymer dispersions and emulsions	
[^{F13} 452	38885	0002725	224-6	yes	no	no	5]
			bis(2,4-dimethylphenyl)-6-(2-hydroxy-4-n-octyloxyphenyl)-1,3,5-triazine							
453	26320	0002768	027	no	yes	no	0,05			(10)
			trimethylsilane							
454	12670	0002855	113-2	no	yes	no	6			
			amino-3-aminomethyl-3,5,5-trimethylcyclohexane							
455	20530	0002867	4512	no	yes	no	ND			
			methacrylic acid, 2-(dimethylamino)-ethyl ester							
456	10810	0002998	087	no	yes	no		(22)		
			acetic acid, sec-butyl ester							
457	20140	0002998	1817	no	yes	no		(23)		
			methacrylic acid, sec-butyl ester							
458	36960	0003061	754	no	yes	no				
			benzamide							
459	46870	0003135	315-01	yes	no	no				
			tert-butyl-4-hydroxybenzylphosphonic acid, dioctadecyl ester							
460	14950	0003173	513	no	yes	no		(17)	1 mg/kg in	(10)
			hexyl isocyanate							

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

									final product expressed as isocyanate moiety	
461	22420	0003173472-6	naphthalene diisocyanate	no	yes	no		(17)	1 mg/kg in final product expressed as isocyanate moiety	(10)
462	26170	0003195178-6	vinyl-N-methylacetamide	no	yes	no	0,02			[^{F10} (1)]
463	25840	0003290492-4	trimethylolpropane trimethacrylate	no	yes	no	0,05			
464	61280	0003293297-8	hydroxy-4-n-hexyloxybenzophenone	yes	no	yes		(8)		
465	68040	0003333762-8	naphtho-(1,2-D)triazol-2-yl]-3-phenylcoumarin	yes	no	no				
466	50640	0003648118-8	octyltin dilaurate	yes	no	no		(10)		
[^{F15} 467	14800	3724-6540	otonic acid	yes	yes	no		(35)		
	45600]									
468	71960	0003825261	fluorocortic acid, ammonium salt	yes	no	no			Only to be used in repeated use articles, sintered at high temperatures	

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

469	60480	000386429021	hydroxy-3,5'-di-tert-butylphenyl)-5-chlorobenzotriazole	yes	no	yes		(12)		
470	60400	000389621025	hydroxy-3'-tert-butyl-5'-methylphenyl)-5-chlorobenzotriazole	yes	no	yes		(12)		
471	24888	0003965555-7	sulphoisophthalic acid, monosodium salt, dimethyl ester	no	yes	no	0,05			
472	66560	0004066202-8	methylenebis(4-methyl-6-cyclohexylphenol)	yes	no	yes		(5)		
473	12265	00040744002	acid, divinyl ester	no	yes	no	ND		5 mg/kg in final product. Only to be used as co-monomer.	(1)
474	43600	000408013033	chloroallyl)-3,5,7-triaza-1-azoniaadamantane chloride	yes	no	no	0,3			
475	19110	0004098171-9	isocyanato-3-isocyanatomethyl-3,5,5-trimethylcyclohexane	no	yes	no		(17)	1 mg/kg in final product expressed as isocyanate moiety	(10)
476	16570	00041281738	phenyl ether-4,4'-diisocyanate	yes	yes	no		(17)	1 mg/kg in final product expressed	(10)

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

486	54005	0005136	644-1	yes	no	no			
			N-palmitamide-N'-stearamide						
487	45640	0005232	299-5	yes	no	no	0,05		
			cyano-3,3-diphenylacrylic acid, ethyl ester						
488	53440	0005518	813	yes	no	no			
			ethylenebispalmitamide						
489	41040	0005743	362	yes	no	no			
			butyrate						
490	16600	0005873	45	no	no	no		(17)	1 mg/kg in final product expressed as isocyanate moiety (10)
			diphenylmethane,2,4'-diisocyanate						
491	82720	0006182	11-2	yes	no	no			
			propyleneglycol distearate						
492	45650	0006197	230-4	yes	no	no	0,05		
			cyano-3,3-diphenylacrylic acid, 2-ethylhexyl ester						
493	39200	0006200	41(2)	yes	no	no	1,8		
			hydroxyethyl)-2-hydroxypropyl-3-(dodecyloxy)methylammonium chloride						
494	62140	0006303	215	no	no	no			
			hypophosphorous acid						
495	35160	0006642	631-5	yes	no	no	5		
			amino-1,3-dimethyluracil						
496	71680	0006683	118	no	no	no			
			erythritol tetrakis[3-(3,5-di-tert-						

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

			butyl-4-hydroxyphenyl)-propionate]							
497	95020	0006846250-4	trimethyl-1,3-pentenediol diisobutyrate	yes	no	no	5		Only to be used in single-use gloves	
498	16210	0006864337-5	dimethyl-4,4'-diaminodicyclohexylmethane	no	yes	no	0,05		Only to be used in polyamides	(5)
499	19965 65020	0006915117	acid	yes	yes	no			In case of use as a monomer only to be used as a co-monomer in aliphatic polyesters up to maximum level of 1 % on a molar basis	
500	38560	0007128261-5	bis(5-tert-butyl-2-benzoxazolyl)thiophene	yes	no	yes	0,6			
501	34480	—	aluminium fibers, flakes and powders	yes	no	no				
502	22778	0007456468-0	oxybis(benzenesulphonyl azide)	no	yes	no	0,05			[F ¹⁰ (1)]

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

503	46080	0007585	β-D-39-9 dextrin	yes	no	no				
504	86240	0007631	SiO ₂ silicon dioxide	yes	no	no			For synthetic amorphous silicon dioxide: primary particles of 1 – 100 nm which are aggregated to a size of 0,1 – 1 µm which may form agglomerates within the size distribution of 0,3 µm to the mm size.	
505	86480	0007631	SO ₂ bisulphite	yes	no	no		(19)		
506	86920	0007632	NO ₂ nitrite	yes	no	no	0,6			
507	59990	0007647	HCl hydrochloric acid	yes	no	no				
508	86560	0007647	NaBr sodium bromide	yes	no	no				
509	23170	0007664	H ₃ PO ₄ phosphoric acid	yes	yes	no				
	72640									
510	12789	0007664	NH ₃ ammonia	yes	yes	no				
	35320									
511	91920	0007664	H ₂ SO ₄ sulphuric acid	yes	no	no				

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

512	81680	0007681	potassium iodide	yes	no	no		(6)		
513	86800	0007681	potassium iodide	yes	no	no		(6)		
514	91840	0007704	silicic acid	yes	no	no				
515	26360	0007732	water	yes	yes	no			In compliance with Directive 98/83/EC ^b	
	95855									
516	86960	0007757	sodium sulphite	yes	no	no		(19)		
517	81520	0007758	potassium bromide	yes	no	no				
518	35845	0007771	lactic acid	yes	no	no				
519	87120	0007772	sodium thiosulphate	yes	no	no		(19)		
520	65120	0007773	manganese chloride	yes	no	no				
521	58320	0007782	zinc white	yes	no	no				
522	14530	0007782	zinc white	no	yes	no				
523	45195	0007787	potassium bromide	yes	no	no				
524	24520	0008001	soybean oil	no	yes	no				
525	62640	0008001	japan wax	yes	no	no				
526	43440	0008001	lecithin	yes	no	no				
527	14411	0008001	leather oil	yes	yes	no				
	42880									
528	63760	0008002	lecithin	yes	no	no				
529	67850	0008002	montan wax	yes	no	no				
530	41760	0008006	beeswax	yes	no	no				
531	36880	0008012	beeswax	yes	no	no				
532	88640	0008013	soybean oil, epoxidised	yes	no	no	60 30(*)	(32)	(*)	In the

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

									case of PVC gaskets used to seal glass jars containing infant formulae and follow-on formulae as defined by Directive 2006/141/EC or processed cereal-based foods and baby foods for infants and young children as defined by Directive 2006/125/EC, the SML is lowered to mg/30 kg.
									Oxirane < 8 %, iodine number < 6.

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

533	42720	0008015869	Sebacic wax	yes	no	no			
534	80720	0008017166	phosphoric acids	yes	no	no			
535	24100	0008050097	Olefin	yes	yes	no			
	24130								
	24190								
	83840								
536	84320	0008050155	hydrogenated, ester with methanol	yes	no	no			
537	84080	0008050268	ester with pentaerythritol	yes	no	no			
538	84000	0008050315	ester with glycerol	yes	no	no			
539	24160	0008052166	tall oil	no	yes	no			
540	63940	0008062156	High sulphonic acid	yes	no	no	0,24		Only to be used as dispersant for plastics dispersions
541	58480	0009000015	arabic	yes	no	no			
542	42640	0009000117	cellulose	yes	no	no			
543	45920	0009000162	gum	yes	no	no			
544	58400	0009000300	gum	yes	no	no			
545	93680	0009000165	gum	yes	no	no			
546	71440	0009000607	gum	yes	no	no			
547	55440	0009000708	gum	yes	no	no			
548	42800	0009000712	gum	yes	no	no			

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

549	80000	00090022884	polyethylene wax	yes	no	no			
550	81060	0009003070	polypropylene wax	yes	no	no			
551	79920	00090030106392	poly(ethylene terephthalate) glycol	yes	no	no			
552	81500	0009003309	polyvinylpyrrolidone	yes	no	no			The substance shall meet the purity criteria as laid down in Commission Directive 2008/84/EC ^c
553	14500	0009004311	cellulose	yes	yes	no			
	43280								
554	43300	0009004318	cellulose acetate butyrate	yes	no	no			
555	53280	0009004517	cellulose	yes	no	no			
556	54260	0009004518	hydroxyethylcellulose	yes	no	no			
557	66640	0009004515	ethylcellulose	yes	no	no			
558	60560	0009004620	hydroxyethylcellulose	yes	no	no			
559	61680	0009004642	propylcellulose	yes	no	no			
560	66700	0009004653	hydroxypropylcellulose	yes	no	no			
561	66240	0009004655	cellulose	yes	no	no			
562	22450	0009004700	cellulose	yes	yes	no			
563	78320	0009004907	polyethylene glycol monoricinoleate	yes	no	yes	42		
564	24540	0009005258	starch, edible	yes	yes	no			
	88800								
565	61120	0009005270	hydroxyethyl starch	yes	no	no			
566	33350	0009005327	lactic acid	yes	no	no			

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

567	82080	0009005137-2	propyleneglycol alginate	yes	no	no				
568	79040	0009005615	poly(5-ethylsorbitan monolaurate)	yes	no	no				
569	79120	0009005616	poly(6-ethylsorbitan monooleate)	yes	no	no				
570	79200	0009005617	poly(7-ethylsorbitan monopalmitate)	yes	no	no				
571	79280	0009005618	poly(8-ethylsorbitan monostearate)	yes	no	no				
572	79360	0009005619	poly(9-ethylsorbitan trioleate)	yes	no	no				
573	79440	0009005620	poly(10-ethylsorbitan tristearate)	yes	no	no				
574	24250 84560	0009006016	cellulose, natural	yes	yes	no				
575	76721	0063148601	polydimethylsiloxane (Mw > 6 800 Da)	no	no	no				Viscosity at 25 °C not less than 100 cSt (100 × 10 ⁻⁶ m ² /s)
576	60880	0009032422	hydroxyethylcellulose	yes	no	no				
577	62280	0009044157	isobutylene-butene copolymer	yes	no	no				
578	79600	0009046119	poly(9-tridecyl ether phosphate)	yes	no	no	5			For materials and articles intended for contact with

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

									aqueous foods only. Polyethyleneglycol (EO ≤ 11) tridecyl ether phosphate (mono- and dialkyl ester) with a maximum 10 % content of polyethyleneglycol (EO ≤ 11) tridecylether.
579	61800	00090491747	hydroxypropyl starch	yes	no	no			
580	46070	0010016203	dextrin	yes	no	no			
581	36800	00100226118	nitrate	yes	no	no			
582	50240	0010039335	octyltin bis(2-ethylhexyl maleate)	yes	no	no	(10)		
583	40400	0010043665	nitride	yes	no	no	(16)		
584	13620 40320	0010043663	acid	yes	yes	no	(16)		
585	41120	0010043614	chloride	yes	no	no			
586	65280	0010043842	hypophosphite	yes	no	no			
587	68400	0010094458	ecylsuccinamide	yes	no	yes	5		
588	64320	0010377512	iodide	yes	no	no	(6)		
589	52645	0010436081	eicosenamide	yes	no	no			

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

590	21370	0010595	8019 acrylic acid, 2- sulphoethyl ester	yes	no	ND			(1)
591	36160	0010605	0017 stearyl stearate	no	no				
592	34690	0011097	5019 magnesium carbonate hydroxide	no	no				
593	44960	0011104	4017 cobalt oxide	yes	no	no			
594	65360	0011129	6015 manganese oxide	no	no				
595	19510	0011132	1723 high cell ulose	yes	no				
596	95935	0011138	6611 gum	yes	no				
597	67120	0012001	1262 zinc	yes	no	no			
598	41600	0012004 0037293	4117 aluminum silicate	yes	no	no			
599	36840	0012007	5115 tetraborate	yes	no	no	(16)		
600	60030	0012072	9011 magnesium oxide	no	no				
601	35440	0012124	0719 bromide	yes	no	no			
602	70240	0012198	9215 cerium oxide	yes	no	no			
603	83460	0012269	7821 phenyl oxide	yes	no	no			
604	60080	0012304	6513 hydroxy benzene	yes	no	no			
605	11005	0012542	3011 acid, dicyclopentenyl ester	no	yes	no	0,05		(1)
606	65200	0012626	8819 manganese hydroxide	no	no				
607	62245	0012751	2213 phosphide	yes	no	no			Only to be used in PET polymers and copolymers

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

608	40800	0013003414-8	butylidene-bis(6-tert-butyl-3-methylphenyl-ditridecyl phosphite)	yes	no	yes	6		
609	83455	0013445562	pyrophosphoric acid	yes	no	no			
610	93440	0013463667	titanium dioxide	yes	no	no			
611	35120	0013560349-1	aminocrotonic acid, diester with thiobis (2-hydroxyethyl) ether	yes	no	no			
612	16694	0013811502	divinyl-2-imidazolidinone	no	yes	no	0,05		(10)
613	95905	0013983710	histonins	yes	no	no			
614	45560	0014464450	distalite	yes	no	no			
615	92080	0014807116-6	leuc	yes	no	no			
616	83470	0014808607z	separz	yes	no	no			
617	10660	0015214289-8	acrylamido-2-methylpropanesulphonic acid	no	yes	no	0,05		
618	51040	0015535479-2	octyltin mercaptoacetate	yes	no	no		(10)	
619	50320	0015571458-1	octyltin bis(2-ethylhexyl mercaptoacetate)	yes	no	no		(10)	
620	50720	0015571460-5	octyltin dimaleate	yes	no	no		(10)	

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

621	17110	0016219575-3	no	yes	no	0,05			(9)
			ethylidenebicyclo[2,2,1]hept-2-ene						
622	69840	0016260009-6	no	yes	no	5			
			ethylmetacrylamide						
623	52640	0016389488-1	yes	no	no				
			zinc stearate						
624	18897	0016712664-4	no	yes	no	0,05			
			hydroxy-2-naphthalenecarboxylic acid						
625	36720	0017194400-2	yes	no	no				
			zinc hydroxide						
626	57800	0018641574-1	yes	no	no				
			glycerol tribehenate						
627	59760	0019569411-2	yes	no	no				
			zinc stearate						
628	96190	0020427388-1	yes	no	no				
			zinc hydroxide						
629	34560	0021645411-1	yes	no	no				
			zinc hydroxide						
630	82240	0022788412-8	yes	no	no				
			propyleneglycol dilaurate						
631	59120	0023128176-7	yes	no	yes	45			
			hexamethylene-bis(3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionamide)						
632	52880	0023676409-7	yes	no	no	3,6			
			ethoxybenzoic acid, ethyl ester						
633	53200	0023949266-8	yes	no	yes	30			
			ethoxy-2'-ethyloxanilide						
634	25910	0024800440-0	yes	no	no				
			propyleneglycol						
635	40720	0025013416-5	yes	no	no	30			
			tert-butyl-4-hydroxyanisole						
636	31500	0025134514-4	yes	no	no	0,05	(22)	SML expressed as acrylic	
			acrylic acid, acrylic acid,						

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

			2-ethylhexyl ester, copolymer					acid, 2-ethylhexyl ester	
637	71635	002515	polybutylene terephthalate	no	no	0,05		Not to be used for articles in contact with fatty foods for which [F1 simulant D1 and/or D2] is laid down	
638	23590	002532	polyethylene glycols		no				
	76960								
639	23651	002532	polypropyleneglycol		no				
	80800								
640	54930	002535	formaldehyde-1-naphthol, copolymer	no	no	0,05			
[F1] 641	22331	002551	3648 of (35-45 % w/w) 1,6-diamino-2,2,4-trimethylhexane and (55-65 % w/w) 1,6-diamino-2,4,4-trimethylhexane	no	yes	no	0,05		I
642	64990	002573	maleic anhydride-styrene, copolymer, sodium salt	yes	no	no		The fraction with molecular weight below	

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

									1 000 Da [^{F1} shall] not exceed 0,05 % (w/w)	
643	87760	00262665709	6709-9 monopalmitate	yes	no	no				
644	88080	00262665800	6800-0 trioleate	yes	no	no				
645	67760	00264018615	18615- n- octyltin tris(isooctyl mercaptoacetate)	yes	no	no	(11)			
646	50480	00264018718	18718- octyltin bis(isooctyl mercaptoacetate)	yes	no	no	(10)			
647	56720	00264022303	22303- monohexanoate	yes	no	no				
648	56880	00264022366	22366- monooctanoate	yes	no	no				
649	47210	00264274076	4076-6 acid polymer	yes	no	no			Molecular unit = (C ₈ H ₁₈ S ₃ Sn ₂) _n (n = 1,5-2)	
650	49600	00266364017	64017- bis(isooctyl mercaptoacetate)	yes	no	no	(9)			
651	88240	00266580505	80505- tristearate	yes	no	no				
652	38820	00267415327	15327- di-tert- butylphenyl) pentaerythritol diphosphite	yes	no	yes	0,6			
653	25270	00267472900	72900- toluene diisocyanate dimer	no	yes	no	(17)	1 mg/ kg in final product expressed as	(10)	

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

									isocyanate moiety
654	88600	0026836	47-101	yes	no	no			
			monostearate						
655	25450	0026896	48-010	no	no	no	0,05		
			1,4-bis(2-chlorophenyl)ethane						
656	24760	0026914	43-201	yes	no	no	0,05		
			4-sulphonic acid						
657	67680	0027107	80-7	yes	no	no		(11)	
			n-octyltin tris(2-ethylhexyl mercaptoacetate)						
658	52000	0027176	87-401	no	no	no	30		
			4-ethylbenzenesulphonic acid						
659	82800	0027194	72-7	yes	no	no			
			propyleneglycol monolaurate						
660	47540	0027458	90-8	yes	no	yes	0,05		
			dodecyl disulphide						
661	95360	0027676	62-5	yes	no	yes	5		
			tris(3,5-di-tert-butyl-4-hydroxybenzyl)-1,3,5-triazine-2,4,6(1H,3H,5H)-trione						
662	25927	0027955	14-8	no	yes	no	0,005		Only to be used in polycarbonates
			tris(4-hydroxyphenyl)ethane						[F ¹⁰ (1)]
663	64150	0028290	70-11	yes	no	no			
			7-phenic acid						
664	95000	0028931	67-6	no	no	no			
			1,6-hexylpropylene trimethacrylate-methyl methacrylate copolymer						
665	83120	0029013	28-3	yes	no	no			
			propyleneglycol monopalmitate						
666	87280	0029116	98-11	yes	no	no			
			sebitan dioleate						

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

667	55190	0029204001	adipic acid	yes	no	no			
668	80240	0029894035	glycerol ricinoleate	yes	no	no			
669	56610	0030233054	8-oxo-9-oxoheptanoic acid monobenzenate	yes	no	no			
670	56800	0030899052	8-oxo-9-oxoheptanoic acid monolaurate diacetate	yes	no	no	(32)		
671	74240	0031570004	phosphoric acid, tris(2,4-di-tert-butylphenyl)ester	yes	no	no			
672	76845	0031831051	polyester of 1,4-butanediol with caprolactone	yes	no	no	(29) (30)	The fraction with molecular weight below 1 000 Da [F1 shall] not exceed 0,5 % (w/w)	
673	53670	0032509066	ethylene glycol bis[3,3-bis(3-tert-butyl-4-hydroxyphenyl)butyrate]	yes	no	yes	6		
674	46480	0032647067	azulene sorbitol	yes	no	no			
675	38800	0032687078	N,N-bis(3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionyl)hydrazide	yes	no	yes	15		
676	50400	0033568099	tin octyltin bis(isooctyl maleate)	yes	no	no	(10)		

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

677	82560	0033587420-1	propyleneglycol dipalmitate	yes	no	no				
678	59200	0035074176-2	hexamethylene-bis(3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate)	yes	no	yes	6			
679	39060	0035958130-6	bis(2-hydroxy-3,5-di-tert-butylphenyl)ethane	yes	no	yes	5			
680	94400	0036443682-2	bis[3-(3-tert-butyl-4-hydroxy-5-methylphenyl)propionate]	yes	no	no	9			
681	18310	0036653182-4	hexadecanol	no	yes	no				
682	53270	003720599-2	ethylcarboxymethylcellulose	yes	no	no				
683	66200	0037206041-2	butylcarboxymethylcellulose	yes	no	no				
684	68125	0037244261-5	ephaline syenite	yes	no	no				
685	85950	0037296517-2	acid, magnesium-sodium-fluoride salt	yes	no	no	0,15			SML expressed as fluoride. Only to be used in layers of multi-layer materials not coming into direct contact with food.

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

686	61390	0037353	506	hydroxy-methylcellulose	no				
687	13530	0038103	206-9	bis(4-hydroxyphenyl)propane bis(phthalic anhydride)	no	yes	no	0,05	
	13614								
688	92560	0038613	77	Bis(3,4-di-tert-butyl-phenyl)-4,4'-biphenylene diphosphonite	no	yes	yes	18	
689	95280	0040601	175-5	tris(4-tert-butyl-3-hydroxy-2,6-dimethylbenzyl)-1,3,5-triazine-2,4,6(1H,3H,5H)-trione	yes	no	yes	6	
690	92880	0041484	415-0	Bis-Diethylol bis(3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate)	no	yes	yes	2,4	
691	13600	0047465	397-4	bis(3-methyl-4-hydroxyphenyl)2-indolinone	no	yes	no	1,8	
692	52320	0052047	250-3	dodecyl(phenyl)indole	yes	no	yes	0,06	
693	88160	0054140	507-1	sorbitan tripalmitate	yes	yes	no		
694	21400	0054276	251-6	methacrylic acid, sulphopropyl ester	yes	no	no	0,05	(1)
695	67520	0054849	386	non-methyl tin tris(isooctyl mercaptoacetate)	no	no	no		(9)
696	92205	0057569	401	terephthalic acid, diester	no	no	no		

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

			with 2,2'- methylenebis(4- methyl-6- tert- butylphenol)						
697	67515	0057583	3,4,4'-methyltin tris(ethylhexyl mercaptoacetate)	no	no		(9)		
698	49595	0057583	3,5-dithyltin bis(ethylhexyl mercaptoacetate)	no	no		(9)		
699	90720	0058446	6,6'-dibenzoylmethane		no				
700	31520	0061167	asfific acid, 2-tert- butyl-6- (3-tert- butyl-2- hydroxy-5- methylbenzyl)-4- methylphenyl ester	yes	no	yes	6		
701	40160	0061269	N,N'- bis(2,2,6,6- tetramethyl-4- piperidyl)hexamethylenediamine-1,2- dibromoethane, copolymer	yes	no	no	2,4		
702	87920	0061752	6,6'-dian tetrastearate	yes	no	no			
703	17170	0061788	fatty acids, coco	no	yes	no			
704	77600	0061788	polyethyl ester of hydrogenated castor oil	yes	no	no			
705	10599/90 10599/91	0061788	8014 fatty, unsaturated (C ₁₈), dimers, non hydrogenated, distilled	no	yes	no	(18)		(1)

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

			and non-distilled							
706	17230	0061790	Fatty acids, tall oil	no	yes	no				
707	46375	0061790	Diatomaceous earth	no	no	no				
708	77520	0061790	Diethylsebacate ester of castor oil	no	no	no	42			
709	87520	0062568	Sorbitan monobehenate	yes	no	no				
710	38700	0063397	Di-(2-carbobutoxyethyl)tin-bis(isooctyl mercaptoacetate)	yes	no	yes	18			
711	42000	0063438	Di-(2-carbobutoxyethyl)tin-tris(isooctyl mercaptoacetate)	yes	no	yes	30			
712	42960	0064147	Castor oil, dehydrated	yes	no	no				
[F11]713	43480	0064365	Charcoal, activated	yes	no	no				Only for use in PET at maximum 10 mg/kg of polymer. Same purity requirements as for Vegetable Carbon (E 153) set out by Commission Regulation (EU) No
		0007440	[44-0]							

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

									231/2012 ^d with exception of ash content which can be up to 10 % (w/w).
714	84400	0064365	F0510 hydrogenated, ester with pentaerythritol	yes	no	no			
715	46880	0065140	391-01 tert- butyl-4- hydroxybenzylphosphonic acid, monoethyl ester, calcium salt	yes	no	no	6		
716	60800	0065447	717(20) hydroxyethyl)-4- hydroxy-2,2,6,6- tetramethyl piperidine- succinic acid, dimethyl ester, copolymer	yes	no	no	30		
717	84210	0065997	F0610 hydrogenated	yes	no	no			
718	84240	0065997	F0310 hydrogenated, ester with glycerol	yes	no	no			
719	65920	0066822	N60-4 methacryloyloxyethyl- N,N- dimethyl- N- carboxymethylammonium chloride, sodium	yes	no	no			

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

			salt - octadecyl methacrylate-ethyl methacrylate-cyclohexyl methacrylate-N-vinyl-2-pyrrolidone, copolymers						
720	67360	0067649	n-654- n-dodecyltin tris(isooctyl mercaptoacetate)	yes	no	no		(25)	
721	46800	0067845	395-6- tert-butyl-4-hydroxybenzoic acid, hexadecyl ester	yes	no	no			
722	17200	0068308	551-2 fatty acids, soya	no	yes	no			
723	88880	0068412	202-3 starch, hydrolysed	yes	no	no			
724	24903	0068425	577-3 syrups, hydrolysed starch, hydrogenated	no	yes	no			In compliance with the purity criteria for maltitol syrup E 965(ii) as laid down in Commission Directive 2008/60/EC ^e
[^{F16}]									
726	83599	0068442	2-12-6 reaction products	yes	no	yes		(9)	

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

			of oleic acid, 2-mercaptoethyl ester, with dichlorodimethyltin, sodium sulphide and trichloromethyltin						
727	43360	0068442	Stilbene regenerated	no	no				
728	75100	0068515 0028553	Aliphatic diesters with primary, saturated C ₈ -C ₁₀ branched alcohols, more than 60 % C ₉	no	no	(26) (32)	Only to be used as: (a) (b)	(7) plasticiser in repeated use materials and articles; plasticiser in single-use materials and articles contacting non-fatty foods except for infant formulae and follow-on formulae as defined by Directive 2006/141/EC or processed	

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

										cereal-based foods and baby foods for infants and young children as defined by Directive 2006/125/EC; technical support agent in concentrations up to 0,1 % in the final product.
729	75105	0068515 0026761	phthalic acid diesters with primary, saturated C ₉ -C ₁₁ alcohols more than 90 % C ₁₀	yes	no	no	(26) (32)	Only to be used as: (a) (b)	(7) plasticiser in repeated use materials and articles; plasticiser in single-use materials and articles contacting non-fatty foods except	

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

									for infant formulae and follow-on formulae as defined by Directive 2006/141/EC or processed cereal-based foods and baby foods for infants and young children as defined by Directive 2006/125/EC; technical support agent in concentrations up to 0,1 % in the final product.
730	66930	0068554	4-methylsilsesquioxane			no			Residual monomer in methylsilsesquioxane: < 1 mg methyltrimethoxysilane/kg of methylsilsesquioxane

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

731	18220	0068564	488-5 heptylamino undecanoic acid	no	yes	no	0,05			(2)
732	45450	0068610	51-5 cresol- dicyclopentadiene- isobutylene, copolymer	yes	no	yes	5			
733	10599/92 10599/93	0068783	415 fatty, unsaturated (C ₁₈), dimers, hydrogenated, distilled and non- distilled	no	yes	no		(18)		(1)
734	46380	0068855	410 silica earth, soda ash flux- calcined	no	no	no				
735	40120	0068951	518 polyethylene glycol hydroxymethylphosphonate	no	no	no				
736	50960	0069226	44-4 octyltin ethyleneglycol bis(mercaptoacetate)	yes	no	no		(10)		
737	77370	0070142	216 polyethylene glycol-30 dipolyhydroxystearate	yes	no	no				
738	60320	0070321	287 hydroxy-3,5- bis(1,1- dimethylbenzyl)phenyl]benzotriazole	yes	no	yes	1,5			
739	70000	0070331	291 oxamidobis[ethyl-3- (3,5- di-tert- butyl-4- hydroxyphenyl)- propionate]	yes	no	no				
740	81200	0071878	096 [(1,1,3,3- tetramethylbutyl)amino]-1,3,5- triazine-2,4- diyl]- [(2,2,6,6-	yes	no	yes	3			

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

			tetramethyl-4-piperidyl)-imino]hexamethylene[(2,2,6,6-tetramethyl-4-piperidyl)imino]							
741	24070 83610	0073138-83610	acids and rosin acids	yes	yes	no				
742	92700	007830124,64	tetramethyl-20-(2,3-epoxypropyl)-7-oxa-3,20-diazadispiro-[5.1.11.2]-heneicosan-21-one, polymer	yes	no	yes	5			
743	38950	007907259(4)	ethylbenzylidene)sorbitol	yes	no	no				
[^{F15} 744	18888	080181-31-3	hydroxybutanoic acid-3-hydroxypentanoic acid, copolymer	no	yes	no		(35)	The substance is used as product obtained by bacterial fermentation. In compliance with the specifications mentioned in the Table 4 of Annex I.	
745	68145	0080410232,9'	nitri(triethyl tris(3,3',5,5'-tert-butyl-1,1'-bi-	yes	no	yes	5		SML expressed as sum of phosphite and phosphate	

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

			phenyl-2,2'-diyl)phosphite)						
746	38810	0080693500	(2,6-di-tert-butyl-4-methylphenyl)pentacerythritol diphosphite	yes	no	yes	5		SML expressed as sum of phosphite and phosphate
747	47600	008403061	5-dodecyltin bis(isooctyl mercaptoacetate)	yes	no	yes		(25)	
748	12765	008443412	28-N-(2-aminoethyl)-β-alanine, sodium salt	no	yes	no	0,05		
749	66360	008520922	2'-2-methylene bis(4,6-di-tert-butylphenyl) sodium phosphate	yes	no	yes	5		
750	66350	008520923	4-methylenebis(4,6-di-tert-butylphenyl) lithium phosphate	yes	no	no	5		
751	81515	008718925	25-zinc glycerolate)	yes	no	no			
[^{F1} 752	39890	008782641 0069158-41-4 0054686-97-4 0081541-12-0	41-(methylbenzylidene)sorbitol	yes	no	no]
753	62800	009270440	40-lin, calcined	yes	no	no			
754	56020	009988064	64-6-dibehenate	yes	no	no			
755	21765	010624643	3-7-methylenebis(3-chloro-2,6-diethylaniline)	no	yes	no	0,05		(1)

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

756	40020	0110553224-0	yes	no	yes	(24)		
			bis(octylthiomethyl)-6-methylphenol					
757	95725	0110638716-0	no	no	no			
			reaction product with citric acid, lithium salt					
758	38940	0110675224-8	yes	no	yes	(24)		
			bis(dodecylthiomethyl)-6-methylphenol					
759	54300	0118337209-0	yes	no	yes	6		
			ethylidenebis(4,6-di-tert-butylphenyl) fluorophosphonite					
760	83595	0119345116-0	yes	no	no	18		Composition: — 4,4'-biphenylene-bis[0,0-bis(2,4-di-tert-butylphenyl)phosphonite] (CAS No 0038613-77-3) (36-46 % w/w (*)), — 4,3'-biphenylene-bis[0,0-bis(2,4-di-tert-butylphenyl)phosphonite] (CAS No 0118421-00-4) (17-23 % w/w (*)), — 3,3'-biphenylene-

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

763	39925	0129228321-3	yes	no	yes	0,05			
			bis(methoxymethyl)-2,5-dimethylhexane						
764	13317	0132459542	no	yes	no	0,05		Purity > 98,1 % (w/w). Only to be used as co-monomer (max 4 %) for polyesters (PET, PBT).	
			bis[4-(ethoxycarbonyl)phenyl]-1,4,5,8-naphthalenetetracarboxydiimide						
765	49485	0134701220-5	yes	no	yes	1			
			dimethyl-6-(1-methylpentadecyl)phenol						
766	38879	0135861563-2	yes	no	no				
			dimethylbenzylidene)sorbitol						
767	38510	0136504196-6	yes	no	no	5			
			bis(3-aminopropyl)ethylenediamine, polymer with N-butyl-2,2,6,6-tetramethyl-4-piperidinamine and 2,4,6-trichloro-1,3,5-triazine						
768	34850	0143925002-2	yes	no	no			Not to be used for articles in contact with fatty foods for which [F1] simulant	(1)
			bis(hydrogenated tallow alkyl) oxidised						

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

									D1 and/or D2] is laid down. Only to be used in: (a) polyolefins at 0,1 % (w/w) concentration and in PET at 0,25 % (w/w) concentration. (b)
769	74010	0145650	Phosphoric acid, bis(2,4-di-tert-butyl-6-methylphenyl) ethyl ester	yes	no	yes	5		SML expressed as sum of phosphite and phosphate
770	51700	0147315	2,4-bis(diphenyl-1,3,5-triazin-2-yl)-5-(hexyloxy)phenol	yes	no	no	0,05		
771	34650	0151841	5,5'-bis(hydroxybis[2,2'-methylenebis(4,6-di-tert-butylphenyl) phosphate])	yes	no	no	5		
772	47500	0153250	2,2',3,3'-bis(dicyclohexyl-2,6-naphthalene dicarboxamide)	yes	no	no	5		

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

773	38840	015486264324	2,4-bis(2,4-dicumylphenyl)pentacerythritol-diphosphite	yes	no	yes	5		SML expressed as sum of the substance itself, its oxidised form bis(2,4-dicumylphenyl)pentacerythritol-phosphate and its hydrolysis product (2,4-dicumylphenol)	
774	95270	016171723464	tris(tert-butylphenyl-2-butyl-2-ethyl-1,3-propanediol phosphite	yes	no	yes	2		SML expressed as sum of phosphite, phosphate and the hydrolysis product = TTBP	
775	45705	0166412178	cyclohexanedicarboxylic acid, diisononyl ester	yes	no	no		(32)		
776	76723	0167883164	polydimethylsiloxane, 3-aminopropyl terminated, polymer with dicyclohexylmethane-4,4'-diisocyanate	yes	no	no			The fraction with molecular weight below 1 000 Da [F1 shall] not exceed 1,5 % (w/w)	
777	31542	017425423	acrylic acid, methyl	yes	no	no			0,5 % in	(1)

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

			ester, telomer with 1- dodecanethiol, C ₁₆ - C ₁₈ alkyl esters						final product
778	71670	0178671	pentacerythritol tetrakis (2-cyano-3,3-diphenylacrylate)	no	yes	0,05			
[^{F1} 779]	39815	0182121	bis(methoxymethyl)fluorene	yes	no	yes	0,05		[^{F10} (2)]
780	81220	0192268	[[6-[N-(2,2,6,6-tetramethyl-4-piperidinyl)-n-butylamino]-1,3,5-triazine-2,4-diyl][(2,2,6,6-tetramethyl-4-piperidinyl)imino]-1,6-hexanediyl[(2,2,6,6-tetramethyl-4-piperidinyl)imino]]-α-[N,N,N',N'-tetrabutyl-N''-(2,2,6,6-tetramethyl-4-piperidinyl)-N''-[6-(2,2,6,6-tetramethyl-4-piperidinylamino)-hexyl]-[1,3,5-triazine-2,4,6-triamine]-ω-N,N,N',N'-	yes	no	no	5		

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

			tetrabutyl-1,3,5-triazine-2,4-diamine]						
781	95265	0227099160-57	tris(4-benzoylphenyl)benzene	yes	no	no	0,05		
782	76725	06614760-11	polydimethylsiloxane, 3-aminopropyl terminated, polymer with 1-isocyanato-3-isocyanatomethyl-3,5,5-trimethylcyclohexane			no			The fraction with molecular weight below 1 000 Da [F ¹ shall] not exceed 1 % (w/w)
783	55910	07361506-33	castor-oil mono-, hydrogenated, acetates	yes	no	no		(32)	
[F ¹¹ 784	95420	0745070161-57	tris(2,2-dimethylpropanamido)benzene	yes	no	no	5]
785	24910	00001000-10	terephthalic acid	yes	no	no		(28)	
786	14627	0000117321-5	3-chlorophthalic anhydride	no	yes	no	0,05		SML expressed as 3-chlorophthalic acid
787	14628	0000118445-6	4-chlorophthalic anhydride	no	yes	no	0,05		SML expressed as 4-chlorophthalic acid
788	21498	0002530135-0	(methacryloxy)propyl]trimethoxysilane	no	yes	no	0,05		Only to be used as a (1) (11)

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

								surface treatment agent of inorganic fillers
789	60027	—	hydrogenated homopolymers and/or copolymers made of 1-hexene and/or 1-octene and/or 1-decene and/or 1-dodecene and/or 1-tetradecene (Mw: 440–12 000)	yes	no	no		Average (2) molecular weight not less than 440 Da. Viscosity at 100 °C not less than 3,8 cSt ($3,8 \times 10^{-6} \text{ m}^2/\text{s}$).
790	80480	009075 008245	poly(1,3,5-triazine-2,4-diyl)-[(2,2,6,6-tetramethyl-4-piperidyl)imino] hexamethylene-[(2,2,6,6-tetramethyl-4-piperidyl)imino]	yes	no	no	5	Average (16) molecular weight not less than 2 400 Da. Residual content of morpholine $\leq 30 \text{ mg/kg}$, of N,N'-bis(2,2,6,6-tetramethylpiperidin-4-yl)hexane-1,6-diamine $< 15 000 \text{ mg/kg}$,

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

									and of 2,4-dichloro-6-morpholino-1,3,5-triazine
									≤ 20 mg/kg.
791	92470	0106990	N,N',N'',N'''-tetrakis(4,6-bis(N-butyl-(N-methyl-2,2,6,6-tetramethylpiperidin-4-yl)amino)triazin-2-yl)-4,7-diazadecane-1,10-diamine	yes	no	no	0,05		
792	92475	0203255	3,3',5,5'-tetrakis(tert-butyl)-2,2'-dihydroxybiphenyl, cyclic ester with [3-(3-tert-butyl-4-hydroxy-5-methylphenyl)propyl]oxyphosphonous acid	yes	no	yes	5		SML expressed as the sum of phosphite and phosphate form of the substance and the hydrolysis products
793	94000	0000102	triethanolamine	yes	no	no	0,05		SML expressed as the sum of triethanolamine and the hydrochloride adduct expressed as triethanolamine
[^{F13} 794	18117	0000079	glycolic acid	no	yes	no			Only to be used for]

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

									manufacture of polyglycolic acid (PGA) for (i) indirect food contact behind polyesters such as polyethylene terephthalate (PET) or polylactic acid (PLA); and (ii) direct food contact of a blend of PGA up to 3 % w/w in PET or PLA.	
795	40155	0124172	N,N-bis(2,2,6,6-tetramethyl-4-piperidyl)-N,N'-diformylhexamethylenediamine	yes	no	no	0,05			(2) (12)
796	72141	0018600	(1,4-phenylene)bis[4H-3,1-benzoxazin-4-one]	yes	no	yes	0,05		SML including the sum of its hydrolysis products	
[^{F13} 797	76807	0073018	Diesters of adipic	yes	no	yes		(31) (32)		I

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

			acid with 1,3-butanediol, 1,2-propanediol and 2-ethyl-1-hexanol						
798	92200	0006422	terephthalic acid, bis(2-ethylhexyl)ester	no	no	60	(32)		
799	77708		polyethyleneglycol (EO = 1-50) ethers of linear and branched primary (C ₈ -C ₂₂) alcohols	no	no	1,8		In compliance with the maximum ethylene oxide content as laid down in the purity criteria for food additives in Commission Regulation (EU) No 231/2012.	
800	94425	0000867	ethyl phosphonoacetate	yes	no	no		Only for use in PET	
801	30607	—	acids, C ₂ -C ₂₄ , aliphatic, linear, monocarboxylic, from natural oils and fats,	yes	no	no			

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

			lithium salt						
802	33105	0146340	alcohols, C ₁₂ -C ₁₄ secondary, β-(2-hydroxyethoxy), ethoxylated	yes	no	no	5		(12)
803	33535	0152261	3-1 alkenes (C ₂₀ -C ₂₄) copolymer with maleic anhydride, reaction product with 4-amino-2,2,6,6-tetramethylpiperidine	yes	no	no		Not to be used for articles in contact with fatty foods for which [F1 simulant D1 and/or D2] is laid down. Not to be used in contact with alcoholic foods.	(13)
804	80510	1010121	80-73-nonyl-1,1-dioxo-1-thiopropyl-diyl)-block-poly(x-oleyl-7-hydroxy-1,5-diiminooctane-1,8-diyl), process mixture with x = 1 and/	yes	no	no		Only to be used as polymer production aid in polyethylene (PE), polypropylene (PP) and polystyrene (PS)	

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

			or 5, neutralised with dodecylbenzenesulfonic acid						
805	93450	—	titanium dioxide, coated with a copolymer of n- octyltrichlorosilane and [aminotris(methylenephosphonic acid), penta sodium salt]	yes	no	no			The content of the surface treatment copolymer of the coated titanium dioxide is less than 1 % w/ w
806	14876	0001076197-7	cyclohexanedicarboxylic acid	no	yes	no	5		Only to be used for manufacture of polyesters
[^{F12} 807	93485	—	titanium nitride, nanoparticles	yes	no	no			No migration of titanium nitride nanoparticles. Only to be used in polyethylene terephthalate (PET) up to 20 mg/ kg. In the PET, the agglomerates have a diameter of 100-500 nm consisting

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

									of primary titanium nitride nanoparticles; primary particles have a diameter of approximately 20 nm.	
808	38550	088207344-4	polypropylene	yes	no	no	5		SML including the sum of its hydrolysis products	
809	49080	085228289-4	(2,6-diisopropylphenyl)-6-[4-(1,1,3,3-tetramethylbutyl)phenoxy]-1H-benzo[de]isoquinolin-1,3-dione	yes	no	yes	0,05		Only for use in PET	(6) (14) (15)
810	68119		neopentyl glycol, diesters and monoesters with benzoic acid and 2-ethylhexanoic acid	yes	no	no	5	(32)	Not to be used for articles in contact with fatty foods for which [F1 simulant D1 and/or D2] is laid down.	
811	80077	006844161-4	polyethylene waxes, oxidised	yes	no	no	60			
[F13] 812	80350	012457861-4	polyhydroxystearic	yes	no	no			Only to be]

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

			acid)- polyethyleneimine copolymer						used in plastics up to 0,1 % w/w. Prepared by the reaction of poly(12- hydroxystearic acid) with polyethyleneimine.
813	91530	—	acid)- sulphosulphonic acid alkyl (C ₄ - C ₂₀) or cyclohexyl diesters, salts	no	no	5			
814	91815	—	acid)- sulphosulphonic acid monoalkyl (C ₁₀ - C ₁₆) polyethyleneglycol esters, salts	no	no	2			
815	94985	—	acid)- trimethylpropyl mixed triesters and diesters with benzoic acid and 2- ethylhexanoic acid	no	no	5	(32)	Not to be used for articles in contact with fatty foods for which [^{F1} simulant D1 and/ or D2] is laid down	

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

816	45704	—	cis-1,2-cyclohexanedicarboxylic acid, salts	yes	no	no	5		
817	38507	—	cis-endo-bicyclo[2.2.1]heptane-2,3-dicarboxylic acid, salts	yes	no	no	5		Not to be used with polyethylene in contact with acidic foods. Purity \geq 96 %.
818	21530	—	methallylsulphonic acid, salts	yes	no	no	5		
819	68110	—	neodecanoic acid, salts	yes	no	no	0,05		Not to be used in polymers contacting fatty foods. Not to be used for articles in contact with fatty foods for which [F1 simulant D1 and/ or D2] is laid down. SML expressed as neodecanoic acid.

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

820	76420	—	pimelic acid, salts	yes	no	no				
821	90810	—	stearoyl-lactylic acid, salts	yes	no	no				
[^{F17} 822]	71938		Perchloric acid, salts	yes	no	no	0,002			(4)]
823	24889	—	5-Sulphoisophthalic acid, salts	no	yes	no	5			
854	71943	0329238-246	perfluoroacetic acid, α -substituted with the copolymer of perfluoro-1,2-propylene glycol and perfluoro-1,1-ethylene glycol, terminated with chlorohexafluoropropoxy groups	yes	no	no				Only to be used in concentrations up to 0,5 % w/w in the polymerisation of fluoropolymers that are processed at temperatures at or above 340 °C and are intended for use in repeated use articles
[^{F18} 855]	40560		(butadiene, styrene, methyl methacrylate) copolymer cross-linked with	yes	no	no				Only to be used in rigid poly(vinyl chloride) (PVC)

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

			1,3-butanediol dimethacrylate					at a maximum level of 12 % at room temperature or below.	
[F19]	856	40563	25101-28	Butadienes, styrene, methyl methacrylate, butyl acrylate) copolymer cross-linked with divinylbenzene or 1,3-butanediol dimethacrylate	no	no		Only to be used in: —	rigid poly(vinyl chloride) (PVC) at a maximum level of 12 % at room temperature or below; or at up to 40 % w/w in blends of styrene acrylonitrile copolymer (SAN)/ poly(methyl methacrylate) (PMMA) repeat-use articles at room temperature or below,

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

										and when either in contact only with aqueous, acidic and/or low alcoholic (< 20 %) foodstuffs for less than 1 day, or when in contact only with dry foodstuffs for any duration of time.	
857	66765	0037953	(methyl methacrylate, butyl acrylate, styrene, glycidyl methacrylate) copolymer	yes	no	no				Only to be used in rigid poly(vinyl chloride) (PVC) at a maximum level of 2 % at room temperature or below.	I
[F8] [X1] 858	38565	0090498	390-1 bis[2-(3-(3-	yes	no	yes	0,05			SML expressed as the	(2)]

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

		tert-butyl-4-hydroxy-5-methylphenylpropionyloxy)-1,1-dimethylethyl]-2,4,8,10-tetraoxaspiro[5,5]undecane					sum of the substance and its oxidation product 3-[(3-(3-tert-butyl-4-hydroxy-5-methylphenyl)prop-2-enoyloxy)-1,1-dimethylethyl]-9-[(3-(3-tert-butyl-4-hydroxy-5-methylphenyl)propionyloxy)-1,1-dimethylethyl]-2,4,8,10-tetraoxaspiro[5,5]-undecane in equilibrium with its para quinone methid tautomer.
[F ⁵ 859		(butadiene, ethyl acrylate, methyl methacrylate, styrene) copolymer crosslinked with divinylbenzene, in nanoform	yes	no	no		Only to be used as particles in non-plasticised PVC up to 10 % w/w in contact with all food types at room temperature or below including

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

									long-term storage. When used together with the substance with FCM No 998 and/ or the substance with FCM No 1043, the restriction of 10 % w/w applies to the sum of those substances. The diameter of particles shall be > 20 nm, and for at least 95 % by number it shall be > 40 nm.
860	71980	0051798	perfluoropolyethylenes (poly(n-propoxy)propanoic acid]	no	no				Only to be used in the polymerisation of

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

									fluoropolymers that are processed at temperatures at or above 265 °C and are intended for use in repeated use articles
861	71990	0013252	21336 [2-(n-propoxy)propanoic acid]	yes	no	no			Only to be used in the polymerisation of fluoropolymers that are processed at temperatures at or above 265 °C and are intended for use in repeated use articles
[^{F13} 862	15180	0018085	302-4 diacetoxy-1-butene	no	yes	no	0,05		SML (17) including (19)] the hydrolysis product 3,4-dihydroxy-1-butene Only to be used as a

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

									co-monomer for ethylvinylalcohol (EVOH) and polyvinylalcohol (PVOH) copolymers.
[^{F18} 863	15260	000064642503	no decanediamine	no	yes	no	0,05		Only to be used as a co-monomer for manufacturing polyamide articles for repeated use in contact with aqueous, acidic and dairy foodstuffs at room temperature or for short term contact up to 150 °C.
864	46330	0000056206-4	yes diamino-6-hydroxypyrimidine	yes	no	no	5		Only to be used in rigid poly(vinyl chloride) (PVC) in contact with non-acidic and

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

									non-alcoholic aqueous food	
[F12] 865	40619	0025322(00-01	(butyl acrylate, methyl methacrylate, butyl methacrylate) copolymer	yes	no	no			Only to be used in: (a) rigid poly(vinyl chloride) (PVC) at a maximum level of 1 % w/w; (b) polylactic acid (PLA) at a maximum level of 5 % w/w.]
866	40620	—	(butyl acrylate, methyl methacrylate) copolymer, cross-linked with allyl methacrylate	yes	no	no			Only to be used in rigid poly(vinyl chloride) (PVC) at a maximum level of 7 %	
867	40815	0040471(00-01	(butyl methacrylate, ethyl acrylate, methyl methacrylate) copolymer	yes	no	no			Only to be used in rigid poly(vinyl chloride) (PVC)	

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

									at a maximum level of 2 %	
[F12]868	53245	0009010	(88-2 acrylate, methyl methacrylate) copolymer	yes	no	no			Only to be used in: (a) rigid poly(vinyl chloride) (PVC) at a maximum level of 2 % w/w; (b) polylactic acid (PLA) at a maximum level of 5 % w/w; (c) polyethylene terephthalate (PET) at a maximum level of 5 % w/w.	I
869	66763	0027136	(85-8 acrylate, methyl methacrylate, styrene) copolymer	yes	no	no			Only to be used in rigid poly(vinyl chloride) (PVC) at a maximum	

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

									level of 3 %
870	95500	0160535	54416 ,N"- tris(2- methylcyclohexyl)-1,2,3- propane- tricarboxamide	yes	no	no	5		
[^{F2} 871		0287916	8613 acetic acid, 12- amino-, polymer with ethene, 2,5- furandione, α - hydro- ω - hydroxypoly (oxy-1,2- ethanediy)l and 1- propene	yes	no	no			Only (23)] to be used in polyolefins at levels of up to 20 weight %. These polyolefins shall only be used in contact with foods for which Table 2 of Annex III assigns food simulant E, at ambient temperature or below, and when migration of the total oligomeric fraction of less than

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

									1 000 Da does not exceed 50 µg/kg food.	
[^{F20} 872]		0006607	241-6 phenyl-3,3- bis(4- hydroxyphenyl)phthalimidine	no	yes	no	0,05		To be used only as a co-monomer in polycarbonate copolymers	(20)]
[^{F18} 873]	93460		titanium dioxide reacted with octyltriethoxysilane	yes	no	no			Reaction product of titanium dioxide with up to 2 % w/w surface treatment substance octyltriethoxysilane, processed at high temperatures.	
[^{F8} 874]	16265	0156065	600-8 dimethyl-3-(4'-hydroxy-3'-methoxyphenyl)propylsilyloxy, ω-3-dimethyl-3-(4'-hydroxy-3'-methoxyphenyl)propylsilyl polydimethylsiloxane	no	yes	no	0,05	(33)	Only to be used as comonomer in siloxane modified polycarbonate. The oligomeric mixture shall be characterised by the formula]

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

										$C_{24}H_{38}Si_2O_5(SiOC_2H_6)_n$ ($50 > n \geq 26$).
875	80345	0058128p01	poly(12-hydroxystearic acid) stearate	yes	no	yes	5			
878	31335	—	acids, fatty (C_8 - C_{22}) from animal or vegetable fats and oils, esters with branched alcohols, aliphatic, monohydric, saturated, primary (C_3 - C_{22})	yes	no	no				
879	31336	—	acids, fatty (C_8 - C_{22}) from animal or vegetable fats and oils, esters with alcohols, linear, aliphatic, monohydric, saturated, primary (C_1 - C_{22})	yes	no	no				

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

[^{FI} 880	31348		acids, fatty (C ₈ -C ₂₂), esters with pentaerythritol'	yes	no	no				
881	25187	000301029644-	tetramethylcyclobutane-1,3-diol	no	yes	no	5		Only for: (a) (b)	I repeated use articles for long term storage at room temperature or below and hotfill; single use materials and articles as a co-monomer at a maximum use level of 35 mole % of the diol component of polyesters, and if such materials and

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

										articles are for long term storage at room temperature or below of food types which have an alcohol content of up to 10 % and for which Table 2 of Annex III does not assign simulant D2. Hot fill conditions are allowed for such single use materials and articles.
882	25872	00024162936	no trimethylphenol	no	yes	no	0,05			

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

883	22074	0004457	371-0 methyl-1,5-pentanediol	no	yes	no	0,05		Only to be used in materials in contact with food at a surface to mass ratio up to 0,5 dm ² /kg
884	34240	0091082	alkyl(C ₂₁)sulphonic acid, esters with phenol	yes	no	no	0,05		Not to be used for articles in contact with fatty foods for which [F ¹ simulant D1 and/or D2] is laid down.
885	45676	0263244	548 oligomers of (butylene terephthalate)	yes	no	no			Only to be used in poly(ethylene terephthalate) (PET), poly(butylene terephthalate) (PBT), polycarbonate (PC), polystyrene (PS) and

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

									rigid poly(vinyl chloride) (PVC) plastics in concentrations up to 1 % w/w, in contact with aqueous, acidic and alcoholic foods, for long term storage at room temperature.
[^{F18} 894	93360	0016545	5516-8 di-propionic acid, ditetradecyl ester	no	no		(14)		
895	47060	0171090	3963-5 di-tert-butyl-4-hydroxyphenyl)propanoic acid, esters with C13-C15 branched and linear alcohols	yes	no	no	0,05		Only to be used in polyolefins in contact with foods other than fatty/high-alcoholic and dairy products.
896	71958	0958445	341-8 perfluoro-3-[(3-methoxypropoxy)propanoic acid],	yes	no	no			Only to be used in the polymerisation of

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

			ammonium salt					fluoropolymers when: — processed at temperatures higher than 280 °C for at least 10 minutes, — processed at temperatures higher than 190 °C up to 30 % w/w for use in blends with polyoxymethylene polymers and intended for repeated use articles.
[FR]902	000012842-9	2-9	benzothiazol-3-one 1,1-dioxide, sodium salt	yes	no (2H)-	no		The substance shall comply with the specific purity criteria as set out in Commission Regulation (EU)

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

								No 231/2012 ^a .
[^{F5} 903	37486-624-	perfluoro- [(5,8,11,14-tetramethyl)- tetraethyleneglycol ethyl propyl ether]	yes	no	no			Only to be used as a polymer production aid in the polymerisation of fluoropolymers intended for: (a) repeated and single use materials and articles when sintered or processed (non-sintered) at temperatures at or above 360 °C for at least 10 minutes or at higher temperatures for equivalent shorter times; (b) repeated use materials and articles

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

									when processed (non-sintered) at temperatures from 300 °C and up to 360 °C for at least 10 minutes.
923	39150	0000120404	N,N-bis(2-hydroxyethyl)dodecanamide	yes	no	no	5		(18) The residual amount of diethanolamine in plastics, as an impurity and decomposition product of the substance, [F1 shall] not result in a migration of diethanolamine higher than 0,3 mg/kg food.
924	94987		trimethylpropyl mixed triesters and diesters with n-octanoic and n-	yes	no	no	0,05		Only for use in PET in contact with all types of

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

			decanoic acids					foods other than fatty, high-alcoholic and dairy products.
926	71955	0908020	05200 [(2-ethoxyethoxy)acetic acid], ammonium salt	no	no			Only to be used in the polymerisation of fluoropolymers that are processed at temperatures higher than 300 °C for at least 10 minutes.
[^{F5} 969		24937-78	styleneyes vinyl acetate copolymer wax	no	no			Only to be used as a polymeric additive up to 2 % w/w in polyolefins. The migration of low molecular weight oligomeric fraction below 1 000 Da shall not exceed 5 mg/

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

								kg food.	
971	25885	0002459	trifluoromethyl trimellitate	yes	no			Only to be used as a co-monomer up to 0,35 % w/w to produce modified polyesters intended to be used in contact with aqueous and dry foodstuffs containing no free fat at the surface.	(17)
972	45197	0012158	zinc hydroxide phosphate	yes	no	no			
973	22931	0019430	(per-fluorobutyl)ethylene	no	no	no		Only to be used as a co-monomer up to 0,1 % w/w in the polymerisation of fluoropolymers, sintered at high temperatures.	
[^{F17} 974	74050	939402-	phosphoric acid, mixed	yes	no	yes	10	SML expressed as the]]

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

			2,4-bis(1,1-dimethylpropyl)phenyl and 4-(1,1-dimethylpropyl)phenyl triesters					sum of the phosphite and phosphate forms of the substance, 4-tert-amylphenol and 2,4-di-tert-amylphenol. The migration of 2,4-di-tert-amylphenol shall not exceed 1 mg/kg food.
[^{F8} 979	79987	—	(polyethylene terephthalate, hydroxylated polybutadiene, pyromellitic anhydride) copolymer	no	no			Only to be used in polyethylene terephthalate (PET) at a maximum level of 5 % w/w.
[^{F20} 988		3634-83	1,3-bis(isocyanatomethyl)benzene	no	yes	no	(34)	SML(T)] applies to the migration of its hydrolysis product, 1,3-benzenedimethanamine. To be used only as co-monomer in the

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

								manufacture of a middle layer coating on a poly(ethylene terephthalate) polymer film in a multilayer film
[^{FS} 998			(butadiene, ethyl acrylate, methyl methacrylate, styrene) copolymer not cross-linked, in nanoform	yes	no	no		Only to be used as particles in non-plasticised PVC up to 10 % w/w in contact with all food types at room temperature or below including long-term storage. When used together with the substance with FCM No 859 and/ or the substance

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

									with FCM No 1043, the restriction of 10 % w/w applies to the sum of those substances. The diameter of particles shall be > 20 nm, and for at least 95 % by number it shall be > 40 nm.
[^{F21} 1007	976-56-	diethyl[1,5-bis(1,1-dimethylethyl)-4-hydroxyphenyl]methyl]phosphonate	yes	no					Only to be used up to 0,2 % w/w based on the final polymer weight in the polymerisation process to manufacture poly(ethylene terephthalate) (PET).
1016		(methacrylic acid, ethyl	no	no					Only to be

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

			acrylate, n- butyl acrylate, methyl methacrylate and butadiene) copolymer in nanoform					used up to: (a) 10 % w/ w in non- plasticised PVC; (b) 15 % w/ w in non- plasticised PLA.
								The final material shall be used at room temperature or below.
1017		25618-55-7	polyglycerol	no	no			To be processed under conditions preventing the decomposition of the substance and up to a maximum temperature of 275 °C.
[^{F21} 1030			montmorillonite clay modified by dimethyldialkyl(C16- C18)ammonium chloride	no	no			Only to be used up to 12 % (w/ w) in polyolefins in contact with

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

									dry foods to which simulant E is assigned in table 2 of Annex III at room temperature or below. The sum of the specific migration of 1-chlorohexadecane and 1-chlorooctadecane shall not exceed 0,05 mg/kg food. Can contain platelets in the nanoform that are only in one dimension thinner than 100 nm. Such platelets shall be oriented parallel to the polymer surface
--	--	--	--	--	--	--	--	--	---

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

								and shall be fully embedded in the polymer.	
[F ² 1031		3238-40-2	furan-2,5-dicarboxylic acid	no	yes	no	5	Only to be used as a monomer in the production of polyethylene furanoate. The migration of the oligomeric fraction of less than 1 000 Da shall not exceed 50 µg/kg food (expressed as furan-2,5-dicarboxylic acid).	(22) (23)
1034		3710-30-3	7-octadiene	no	yes	no	0,05	Only to be used as a crosslinking co-monomer in the manufacture of polyolefins for contact with any]

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

								type of foods for long term storage at room temperature, including when packaged under hot-fill conditions.
1043			(butadiene, ethyl acrylate, methyl methacrylate, styrene) copolymer crosslinked with 1,3-butanediol dimethacrylate, in nanoform	yes	no	no		Only to be used as particles in non-plasticised PVC up to 10 % w/w in contact with all food types at room temperature or below including long-term storage. When used together with the substance with FCM No 859 and/

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

								or the substance with FCM No 998, the restriction of 10 % w/w applies to the sum of those substances. The diameter of particles shall be > 20 nm, and for at least 95 % by number it shall be > 40 nm.
[F ² 1045	119093	1271	perfluoroacetic acid, 2-[(5-methoxy-1,3-dioxolan-4-yl)oxy]}, ammonium salt	no	no			Only to be used as a polymer production aid during the manufacture of fluoropolymers under high temperature conditions of at least 370 °C.

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

1046			zinc oxide, nanoparticles, coated with [3-(methacryloxy)propyl]trimethoxysilane (FCM No 788)	yes	no	no			Only to be used in unplasticised polymers. The restrictions and specifications specified for FCM substance No 788 shall be respected.	
1048		624-03-3	ethylene glycol dipalmitate	yes	no	no		(2)	Only to be used when produced from a fatty acid precursor that is obtained from edible fats or oils.	
1050			zinc oxide, nanoparticles, uncoated	yes	no	no			Only to be used in unplasticised polymers.	
1051		42774-1	N,N'-bis(2,2,6,6-tetramethyl-4-piperidinyl)isophthalamide	yes	no	no	5			
1052		1455-42	2,4,8,10-tetraoxaspiro[5,5]undecane-3,9-diethanol,β3,β3,β9,β9-tetramethyl- ('SPG')	no	yes	no	5		Only to be used as a monomer	(22) (23)

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

									in the production of polyesters. The migration of oligomers of less than 1 000 Da shall not exceed 50 µg/kg food (expressed as SPG).	
1053			fatty acids, C16–18 saturated, esters with dipentaerythritol	yes	no	no			Only to be used when produced from a fatty acid precursor that is obtained from edible fats or oils	1
[^{F21} 1055	7695-91-6 58-95-7	tocopherol acetate	yes	no	no				Only to be used as antioxidant in polyolefins.	(24)
[^{F22} 1059	147398-10-3	poly((R)-3-hydroxybutyrate-co-(R)-3-hydroxyhexanoate)	no	yes	no		(35)		Only to be used either alone or blended with	(23)]

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

								other polymers in contact with all foods under contact conditions of up to 6 months and/or 6 months and more, at room temperature or below, including hot fill or a short heating up phase. The migration of all oligomers with a molecular weight below 1 000 Da shall not exceed 5,0 mg/kg food.
1060			ground sunflower seed hulls	yes	no	no		Only to be used at room temperature or below

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

								in contact with foods for which Table 2 of Annex III assigns food simulant E. The seed hulls shall be obtained from sunflower seeds that are fit for human consumption. The processing temperature of the plastic containing the additive shall not exceed 240 °C.	
[^{F23} 1061	80512-44-3,4'-	2,3,4'-	no	yes	no			Only to be used as a co-monomer in the manufacture of polyether ether ketone plastics up to	I
		trifluorobenzophenone							

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

								0,3 % w/w of the final material.	
1062			mixture no composed of 97 % tetraethyl orthosilicate (TEOS) with CAS No 78-10-4 and 3 % hexamethyldisilazane (HMDS) with CAS No 999-97-3	yes	no			Only to be used for the production of recycled PET and at up to 0,12 % (w/w).]
[^{F23} 1063	1547-26-2	2,3,3,4,4,5-heptafluoro-1-pentene		yes	no			Only to be used together with tetrafluoroethylene and/or ethylene co-monomers to manufacture fluorocopolymers for application as polymer processing aid at up to 0,2 % w/w of the food contact material, and when the low-molecular mass	

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

									fraction below 1 500 Da in the fluorocopolymer does not exceed 30 mg/kg.
1064		39318-18	Subst. yes oxide	no	no	0,05			Stoichiometry: WO_n , $n = 2,72-2,90$ (25)
1065		85711-28	Mixture of methyl-branched and linear C_{14} - C_{18} alkanamides, derived from fatty acids	yes	no	no	5		Only to be used in the manufacture of articles made of polyolefins, and which do not come into contact with foods for which food simulant D2 is assigned in Table 2 of Annex III. (26)]
[^{F15} 1066		23985-73	1,2,3,4-tetrahydronaphthalene-2,6-dicarboxylic acid, dimethyl ester	no	yes	no	0,05		Only to be used as a co-monomer in the manufacture of a]

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

									polyester non-food contact layer in a plastic multilayer material, which is to be used only in contact with foods for which food simulants A, B, C and/or D1 are assigned in Table 2 of Annex III. The specific migration limit in column 8 refers to the sum of the substance and of its dimers (cyclic and open chain).
--	--	--	--	--	--	--	--	--	---

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

[^{F24} 1067]	616-38-	dimethylno carbonate	yes	no			Only to be used: a)	(27)] with 1,6- hexanediol in the manufacture of polycarbonate pre- polymers that are used at up to 30 % to manufacture thermoplastic polyurethanes with 4,4'- methylenediphenyldiisocya and diols, such as polypropylene glycol and 1,4- butanediol. The resulting material shall only be applied in repeated use articles intended to come into short- term
------------------------	---------	-------------------------	-----	----	--	--	------------------------------	---

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

										b)	contact (≤ 30 min at room temperature) with food for which simulants A and/ or B are assigned in Table 2 of Annex III; or for the production of other polycarbonates and/ or under other conditions provided that the migration of dimethyl carbonate does not exceed 0,05 mg/ kg food and that the migration of all
--	--	--	--	--	--	--	--	--	--	----	--

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

									polycarbonate oligomers with a molecular weight below 1 000 Da together does not exceed 0,05 mg/kg food.
[^{F15} 1068	2530-83	18-(2,3-epoxypropoxy)propyl]trimethoxy silane	no	yes	no			Only to be used as a component of a sizing agent to treat glass fibres to be embedded in glass-fibre-reinforced low diffusivity plastics (polyethylene terephthalate (PET), polycarbonate (PC), polybutylene terephthalate (PBT), thermoset polyesters and epoxy bisphenol vinylester) in]

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

								contact with all foodstuffs. In treated glass fibres, residues of the substance must not be detectable at 0,01 mg/kg for the substance and 0,06 mg/kg for each of the reaction products (hydrolysed monomers and epoxy-containing cyclic dimer, trimer and tetramer).
[^{F24} 1069	75-28-5	isobutanes	yes	no	no			Only to be used as a blowing agent.
[^{F25} 1075		Montmorillonite clay modified with hexadecyltrimethylammonium bromide	no	no	no			Only to be used as additive at up to 4,0 % w/w in polylactic

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

								acid plastics intended for long-term storage of water at ambient temperature or below. Can form platelets in the nanoform that are in one or two dimensions thinner than 100 nm. Such platelets shall be oriented parallel to the polymer surface and shall be fully embedded in the polymer.
1076		1227937	Phosphoric acid, triphenyl ester, polymer with alpha-hydro-	no	no	0,05		Only to be used as an additive at up to 0,2 % w/w

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

			omega-hydroxypoly[oxy(methyl-1,2-ethanediyl)], C10-16 alkyl ester					in high impact polystyrene materials and articles intended contact with food at room temperature and below, including hot-fill and/or heating up to 100 °C for up to 2 hours. It shall not be used in contact with foods for which simulant C and/or D1 is assigned in Annex III.	
1077			Titanium dioxide surface-treated with fluoride-modified alumina	yes	no	no		Only to be used at up to 25,0 % w/w, including in the nanoform.	29]

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

- c [OJ L 253, 20.9.2008, p. 1.](#)
- d [^{F5}Commission Regulation (EU) No 231/2012 of 9 March 2012 laying down specifications of food additives listed in Annexes II and III to Regulation (EC) No 1333/2008 of the European Parliament and of the Council ([OJ L 83, 22.3.2012, p. 1.](#))]
- e [OJ L 158, 18.6.2008, p. 17.](#)
- f [^{F6}^{F7}Infant as defined in Article 2(2)(a) of Regulation (EU) No 609/2013 of the European Parliament and of the Council of 12 June 2013 on food intended for infants and young children, food for special medical purposes, and total diet replacement for weight control and repealing Council Directive 92/52/EEC, Commission Directives 96/8/EC, 1999/21/EC, 2006/125/EC and 2006/141/EC, Directive 2009/39/EC of the European Parliament and of the Council and Commission Regulations (EC) No 41/2009 and (EC) No 953/2009 ([OJ L 181, 29.6.2013, p. 35.](#))]
- g This restriction is applicable from 1 May 2011 as regards the manufacture and from 1 June 2011 as regards the placing on the market and importation into the Union.]
- h [^{F8}[OJ L 83, 22.3.2012, p. 1.](#)]
- i [^{F9}Infant as defined in Article 2(2)(a) of Regulation (EU) No 609/2013.
- j Young children as defined in Article 2(2)(b) of Regulation (EU) No 609/2013.]

Editorial Information

- X1** Substituted by [Corrigendum to Commission Regulation \(EU\) No 1183/2012 of 30 November 2012 amending and correcting Regulation \(EU\) No 10/2011 on plastic materials and articles intended to come into contact with food \(Official Journal of the European Union L 338 of 12 December 2012\).](#)

Textual Amendments

- F5** Inserted by [Commission Regulation \(EU\) 2015/174 of 5 February 2015 amending and correcting Regulation \(EU\) No 10/2011 on plastic materials and articles intended to come into contact with food \(Text with EEA relevance\).](#)
- F6** Inserted by [Commission Implementing Regulation \(EU\) No 321/2011 of 1 April 2011 amending Regulation \(EU\) No 10/2011 as regards the restriction of use of Bisphenol A in plastic infant feeding bottles \(Text with EEA relevance\).](#)
- F7** Substituted by [Commission Regulation \(EU\) 2018/213 of 12 February 2018 on the use of bisphenol A in varnishes and coatings intended to come into contact with food and amending Regulation \(EU\) No 10/2011 as regards the use of that substance in plastic food contact materials \(Text with EEA relevance\).](#)
- F8** Inserted by [Commission Regulation \(EU\) No 1183/2012 of 30 November 2012 amending and correcting Regulation \(EU\) No 10/2011 on plastic materials and articles intended to come into contact with food \(Text with EEA relevance\).](#)
- F9** Inserted by [Commission Regulation \(EU\) 2018/213 of 12 February 2018 on the use of bisphenol A in varnishes and coatings intended to come into contact with food and amending Regulation \(EU\) No 10/2011 as regards the use of that substance in plastic food contact materials \(Text with EEA relevance\).](#)
- F10** Deleted by [Commission Regulation \(EU\) 2017/752 of 28 April 2017 amending and correcting Regulation \(EU\) No 10/2011 on plastic materials and articles intended to come into contact with food \(Text with EEA relevance\).](#)
- F11** Substituted by [Commission Regulation \(EU\) 2015/174 of 5 February 2015 amending and correcting Regulation \(EU\) No 10/2011 on plastic materials and articles intended to come into contact with food \(Text with EEA relevance\).](#)
- F12** Substituted by [Commission Regulation \(EU\) No 1183/2012 of 30 November 2012 amending and correcting Regulation \(EU\) No 10/2011 on plastic materials and articles intended to come into contact with food \(Text with EEA relevance\).](#)
- F13** Substituted by [Commission Regulation \(EU\) No 1282/2011 of 28 November 2011 amending and correcting Commission Regulation \(EU\) No 10/2011 on plastic materials and articles intended to come into contact with food \(Text with EEA relevance\).](#)

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

- F14** Substituted by Commission Regulation (EU) No 202/2014 of 3 March 2014 amending Regulation (EU) No 10/2011 on plastic materials and articles intended to come into contact with food (Text with EEA relevance).
- F15** Substituted by Commission Regulation (EU) 2019/37 of 10 January 2019 amending and correcting Regulation (EU) No 10/2011 on plastic materials and articles intended to come into contact with food (Text with EEA relevance).
- F16** Deleted by Commission Regulation (EU) 2015/174 of 5 February 2015 amending and correcting Regulation (EU) No 10/2011 on plastic materials and articles intended to come into contact with food (Text with EEA relevance).
- F17** Substituted by Commission Regulation (EU) 2018/831 of 5 June 2018 amending Regulation (EU) No 10/2011 on plastic materials and articles intended to come into contact with food (Text with EEA relevance).
- F18** Inserted by Commission Regulation (EU) No 1282/2011 of 28 November 2011 amending and correcting Commission Regulation (EU) No 10/2011 on plastic materials and articles intended to come into contact with food (Text with EEA relevance).
- F19** Substituted by Commission Regulation (EU) 2018/79 of 18 January 2018 amending Regulation (EU) No 10/2011 on plastic materials and articles intended to come into contact with food (Text with EEA relevance).
- F20** Inserted by Commission Regulation (EU) No 202/2014 of 3 March 2014 amending Regulation (EU) No 10/2011 on plastic materials and articles intended to come into contact with food (Text with EEA relevance).
- F21** Inserted by Commission Regulation (EU) 2017/752 of 28 April 2017 amending and correcting Regulation (EU) No 10/2011 on plastic materials and articles intended to come into contact with food (Text with EEA relevance).
- F22** Substituted by Commission Regulation (EU) 2019/1338 of 8 August 2019 amending Regulation (EU) No 10/2011 on plastic materials and articles intended to come into contact with food (Text with EEA relevance).
- F23** Inserted by Commission Regulation (EU) 2018/79 of 18 January 2018 amending Regulation (EU) No 10/2011 on plastic materials and articles intended to come into contact with food (Text with EEA relevance).
- F24** Inserted by Commission Regulation (EU) 2019/37 of 10 January 2019 amending and correcting Regulation (EU) No 10/2011 on plastic materials and articles intended to come into contact with food (Text with EEA relevance).
- F25** Inserted by Commission Regulation (EU) 2020/1245 of 2 September 2020 amending and correcting Regulation (EU) No 10/2011 on plastic materials and articles intended to come into contact with food (Text with EEA relevance).

2. Group restriction of substances

Table 2 on Group restrictions contains the following information:

Column 1 (Group restriction No): contains the identification number of the group of substances for which the group restriction applies. It is the number referred to in Column 9 in Table 1 of this Annex.

Column 2 (FCM substance No): contains the unique identification numbers of the substances for which the group restriction applies. It is the number referred to in Column 1 in Table 1 of this Annex.

Column 3 (SML (T) [mg/kg]): contains the total specific migration limit for the sum of substances applicable to this group. It is expressed in mg substance per kg food. It is indicated ND if the substance shall not migrate in detectable quantities.

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

Column 4 (Group restriction specification): contains an indication of the substance whose molecular weight forms the basis for expression of the result.

TABLE 2

(1) Group Restriction No	(2) FCM substance No	(3) SML (T)[mg/kg]	(4) Group restriction specification
1	128 211	6	expressed as acetaldehyde
[^{F1} 2	89 227 263 1048	30	expressed as ethyleneglycol]
3	234 248	30	expressed as maleic acid
4	212 435	15	expressed as caprolactam
5	137 472	3	expressed as the sum of the substances
6	412 512 513 588	1	expressed as iodine
7	19 20	1,2	expressed as tertiary amine
8	317 318 319 359 431 464	6	expressed as the sum of the substances
9	650 695 697 698 726	0,18	expressed as tin
10	28 29 30 31 32 33 466 582 618 619	0,006	expressed as tin

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

	620 646 676 736		
11	66 645 657	1,2	expressed as tin
12	444 469 470	30	expressed as the sum of the substances
13	163 285	1,5	expressed as the sum of the substances
[^{F13} 14	294	5	expressed as the sum of the substances and their oxidation products
	368		
	894]		
[^{F11} 15	98 196 344	15	expressed as formaldehyde]
16	407 583 584 599	6	expressed as boron Without prejudice to the provisions of Directive 98/83/EC
17	4 167 169 198 274 354 372 460 461 475 476 485 490 653	ND	expressed as isocyanate moiety
18	705 733	0,05	expressed as the sum of the substances
19	505 516 519	10	expressed as SO ₂
20	290 386 390	30	expressed as the sum of the substances
21	347 349	5	expressed as trimellitic acid

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

22	70 147 176 218 323 325 365 371 380 425 446 448 456 636	6	expressed as acrylic acid
23	150 156 181 183 184 355 370 374 439 440 447 457 482	6	expressed as methacrylic acid
24	756 758	5	expressed as the sum of the substances
25	720 747	0,05	sum of mono-n-dodecyltin tris(isooctylmercaptoacetate), di-n-dodecyltin bis(isooctylmercaptoacetate), mono-dodecyltin trichloride and di-dodecyltin dichloride) expressed as the sum of mono- and di-dodecyltin chloride
26	728 729	9	expressed as the sum of the substances
27	188 291	5	expressed as isophthalic acid
28	191 192 785	7,5	expressed as terephthalic acid

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

29	342 672	0,05	expressed as the sum of 6-hydroxyhexanoic acid and caprolactone
[^{F11} 30	254 344 672	5	expressed as 1,4-butanediol]
31	73 797	30	expressed as the sum of the substances
32	8 72 73 138 140 157 159 207 242 283 532 670 728 729 775 783 797 798 810 815	60	expressed as the sum of the substances
[^{F8} 33	180 874	ND	expressed as eugenol]
[^{F20} 34	421 988	0,05	Expressed as 1,3-benzenedimethanamine]
[^{F24} 35	467 744 1059	0,05	expressed as crotonic acid]

3. Notes on verification of compliance

Table 3 on notes on verification of compliance contains the following information:

Column 1 (Note No): contains the identification number of the Note. It is the number referred to in Column 11 in Table 1 of this Annex.

Column 2 (Notes on verification of compliance): contains rules that shall be respected when testing for compliance of the substance with specific migration limits or other restrictions or it contains remarks on situations where there is a risk of non-compliance.

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

TABLE 3

(1) Note No	(2) Notes on verification of compliance
(1)	Verification of compliance by residual content per food contact surface area (QMA) pending the availability of an analytical method.
(2)	There is a risk that the SML or OML could be exceeded in fatty food simulants.
(3)	There is a risk that the migration of the substance deteriorates the organoleptic characteristics of the food in contact and then, that the final product does not comply with Article 3(1) c of the Framework Regulation (EC) No 1935/2004.
[^{F12} (4)	Compliance testing when there is a fat contact [^{F1} shall] be performed using saturated fatty food simulants as simulant D2.]
(5)	Compliance testing when there is a fat contact [^{F1} shall] be performed using isooctane as substitute of simulant D2 (unstable).
(6)	Migration limit might be exceeded at very high temperature.
(7)	If testing in food is performed, Annex V 1.4 shall be taken into account.
(8)	Verification of compliance by residual content per food contact surface area (QMA); QMA = 0,005 mg/6 dm ² .
(9)	Verification of compliance by residual content per food contact surface area (QMA) pending the availability of analytical method for migration testing. The ratio surface to quantity of food shall be lower than 2dm ² /kg.
(10)	Verification of compliance by residual content per food contact surface area (QMA) in case of reaction with food or simulant.
(11)	Only a method of analysis for the determination of the residual monomer in the treated filler is available.
(12)	There is a risk that the SML could be exceeded from polyolefins.
(13)	Only a method for determination of the content in polymer and a method for

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

	determination of the starting substances in food simulants are available.
(14)	There is a risk that the SML could be exceeded from plastics containing more than 0,5 % w/w of the substance.
(15)	There is a risk that the SML could be exceeded in contact with foods with high alcoholic content.
(16)	There is a risk that the SML could be exceeded from low-density polyethylene (LDPE) containing more than 0,3 % w/w of the substance when in contact with fatty foods
(17)	Only a method for determination of the residual content of the substance in the polymer is available
[^{F18} (18)	There is a risk that the SML could be exceeded from low-density polyethylene (LDPE)
(19)	There is a risk that the OML could be exceeded in direct contact with aqueous foods from ethylvinylalcohol (EVOH) and polyvinylalcohol (PVOH) copolymers]
[^{F20} (20)	The substance contains aniline as an impurity; verification of compliance with the restriction set for primary aromatic amines in Annex II (2) is necessary]
[^{F5} (21)	In case of reaction with foods or simulants verification of compliance shall include verification that the migration limits of the hydrolysis products, formaldehyde and 1,4-butanediol, are not exceeded.]
[^{F2} (22)	When used in contact with non-alcoholic foods for which Table 2 of Annex III assigns food simulant D1, food simulant C shall be used for verification of compliance instead of food simulant D1.
(23)	When a final material or article containing this substance is placed on the market, a well described method to determine whether the oligomer migration complies with the restrictions specified in column 10 of Table 1 shall form part of the supporting documentation referred to in Article 16. This method shall be suitable for use by a competent authority to verify compliance. If an adequate method is publicly available,

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

	reference shall be made to that method. If the method requires a calibration sample, a sufficient sample shall be supplied to the competent authority on its request.]
[^{F21} (24)	The substance or its hydrolysis products are authorised food additives and compliance with Article 11(3) shall be verified.]
[^{F23} (25)	When used as reheat agent in polyethylene terephthalate (PET) verification of compliance with the specific migration limit is not required; in all other cases compliance with the specific migration limit shall be verified in accordance with Article 18; the specific migration limit is expressed as mg tungsten/kg food.
(26)	Migration of stearamide, listed in Table 1 under FCM substance No 306 to which no specific migration limit applies, shall be excluded from verification of the compliance of the migration of the mixture with the specific migration limit laid down for the mixture.]
[^{F24} (27)	When a final material or article containing this substance and produced under conditions other than those described in point (a) column 10 of Table 1 is placed on the market, a well described method to determine whether the oligomer migration complies with the restrictions specified in point (b) column 10 of Table 1 shall form part of the supporting documentation referred to in Article 16. This method shall be suitable for use by a competent authority to verify compliance. If an adequate method is publicly available, reference shall be made to that method. If the method requires a calibration sample, a sufficient sample shall be supplied to the competent authority on its request.]
[^{F25} (28)	A detection limit of 0,002 mg/kg food or food simulant applies
(29)	In polar polymers which swell in contact with foods for which simulant B is assigned in Annex III, there is a risk that under severe contact conditions the migration limits for aluminium and fluoride are exceeded. Under contact conditions above 4 hours at 100 °C this exceedance can be high.]

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

4. Detailed specification on substances

Table 4 on detailed specifications on substances contains the following information

Column 1 (FCM substance No): contains the unique identification number of the substances referred to in Column 1 in Table 1 of Annex I to which the specification applies.


Column 2 (Detailed specification on the substance): contains the specification on the substance.

TABLE 4

(1)	(2)	
FCM substance No	Detailed specification on the substance	
744	Definition	The copolymers are produced by the controlled fermentation of <i>Alcaligenes eutrophus</i> using mixtures of glucose and propanoic acid as carbon sources. The organism used has not been genetically engineered and has been derived from a single wildtype organism <i>Alcaligenes eutrophus</i> strain H16 NCIMB 10442. Master stocks of the organism are stored as freeze-dried ampoules. A submaster/working stock is prepared from the master stock and stored in liquid nitrogen and used to prepare inocula for the fermenter. Fermenter samples will be examined daily both microscopically and for any changes in colonial morphology on a variety of agars at different temperatures. The copolymers are isolated from heat treatment bacteria by controlled digestion of the other cellular components, washing and drying. These copolymers are normally offered as formulated, melt formed granules containing additives such as nucleating agents, plasticisers, fillers, stabilisers and pigments which all conform to the

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

		general and individual specifications
	Chemical name	Poly(3-D-hydroxybutanoate-co-3-D-hydroxypentanoate)
	CAS number	0080181-31-3
	Structural formula	 <p>where n/(m + n) greater than 0 and less or equal to 0,25</p>
	Average molecular weight	Not less than 150 000 Daltons (measured by gel permeation chromatography)
	Assay	Not less than 98 % poly(3-D-hydroxybutanoate-co-3-D-hydroxy-pentanoate) analysed after hydrolysis as a mixture of 3-D-hydro-xybutanoic and 3-D-hydroxypentanoic acids
	Description	White to off-white powder after isolation
	Characteristics	
	Identification tests:	
	Solubility	Soluble in chlorinated hydrocarbons such as chloroform or dichloromethane but practically insoluble in ethanol, aliphatic alkanes and water
	[¹⁵ F]Restriction	Specific migration limit for crotonic acid is 0,05 mg/kg food]
	Purity	Prior to granulation the raw material copolymer powder must contain:
	— nitrogen,	Not more than 2 500 mg/kg of plastic
	— zinc,	Not more than 100 mg/kg of plastic
	— copper,	Not more than 5 mg/kg of plastic
	— lead,	Not more than 2 mg/kg of plastic

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

	— arsenic,	Not more than 1 mg/kg of plastic
	— chromium,	Not more than 1 mg/kg of plastic

[^{F3}ANNEX II

Restrictions on plastic materials and articles

The following restrictions on plastic materials and articles apply:

1. Plastic materials and articles shall not release the substances in Table 1 below in quantities exceeding the specific migration limits expressed in mg/kg food or simulant specified in column (3), and subject to the remarks in Column (4).

Substances listed in Table 1 shall only be used in accordance with the compositional requirements set out in Chapter II. If Chapter II does not provide a basis for the authorised use of such a substance, that substance may only be present as an impurity subject to the restrictions specified in Table 1.

Table 1

General list of migration limits for substances migrating from plastic materials and articles

(1)	(2)	(3)	(4)
Name	Salts allowed in accordance with Article 6(3)(a)	SML [mg/kg food or food simulant]	Remark
Aluminium	yes	1	
Ammonium	yes		(1)
Antimony	no	0,04	(2)
Arsenic	no	ND	
Barium	yes	1	
Cadmium	no	ND (LOD 0,002)	
Calcium	yes		(1)
Chromium	no	ND	(3)
Cobalt	yes	0,05	
Copper	yes	5	
Europium	yes	0,05	(4)
Gadolinium	yes	0,05	(4)
Iron	yes	48	
Lanthanum	yes	0,05	(4)

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

Table 1

General list of migration limits for substances migrating from plastic materials and articles

Lead	no	ND	
Lithium	yes	0,6	
Magnesium	yes		(1)
Manganese	yes	0,6	
Mercury	no	ND	
Nickel	no	0,02	
Potassium	yes		(1)
Sodium	yes		(1)
Terbium	yes	0,05	(4)
Zinc	yes	5	

ND: Not Detectable; detection limit assigned in accordance with second subparagraph of Article 11(4); LOD: specified Limit of Detection.

Remarks

(1) The migration is subject to Article 11(3) and Article 12

(2) The note in Annex I, Table 1, FCM No 398 applies: SML might be exceeded at very high temperature

(3) To verify compliance with the Regulation, the detection limit of 0,01 mg/kg shall apply for total chromium. However if the operator that placed the material on the market can prove on the basis of pre-existing documentary evidence that the presence of hexavalent chromium in the material is excluded because it is not used or formed or during the entire production process, a limit for the total chromium of 3,6 mg/kg food shall apply.

(4) The lanthanide substances europium, gadolinium, lanthanum, and/or terbium can be used in accordance with Article 6(3)(a) provided that:

- (a) The sum of all lanthanide substances migrating to the food or food simulant does not exceed the specific migration limit of 0,05 mg/kg; and
- (b) analytical evidence using a well described methodology demonstrating that the lanthanide substance(s) used are present in dissociated ionic form in the food or the food simulant, forms part of the documentation referred to in Article 16.

2. Primary aromatic amines ('PAAs') listed in entry 43 to Appendix 8 of Annex XVII to Regulation (EC) No 1907/2006 of the European Parliament and of the Council⁽¹⁹⁾ and for which no migration limit is specified in Table 1 of Annex I shall not migrate or shall not otherwise be released from plastic materials and articles into food or food simulant. They shall not be detectable using analytical equipment with a limit of detection of 0,002 mg/kg food or food simulant applied to each individual primary aromatic amine ('PAA'), in accordance with Article 11(4).

For PAAs not listed in entry 43 to Appendix 8 of Annex XVII to Regulation (EC) No 1907/2006, but for which no specific migration limit is specified in Annex I, compliance with Article 3 of Regulation (EC) No 1935/2004 shall be verified in accordance with Article 19. The sum of those PAAs shall however not exceed 0,01 mg/kg in food or food simulant.]

ANNEX III

Food simulants

1. Food simulants

For demonstration of compliance for plastic materials and articles not yet in contact with food the food simulants listed in Table 1 below are assigned.

^{F1}TABLE 1**List of food simulants**

Food simulant	Abbreviation
Ethanol 10 % (v/v)	Food simulant A
Acetic acid 3 % (w/v)	Food simulant B
Ethanol 20 % (v/v)	Food simulant C
Ethanol 50 % (v/v)	Food simulant D1
Any vegetable oil containing less than 1 % unsaponifiable matter	Food simulant D2
poly(2,6-diphenyl-p-phenylene oxide), particle size 60-80 mesh, pore size 200 nm	Food simulant E]

2. General assignment of food simulants to foods

Food simulants A, B and C are assigned for foods that have a hydrophilic character and are able to extract hydrophilic substances. Food simulant B shall be used for those foods which have a pH below 4.5. Food simulant C shall be used for alcoholic foods with an alcohol content of up to 20 % and those foods which contain a relevant amount of organic ingredients that render the food more lipophilic.

Food simulants D1 and D2 are assigned for foods that have a lipophilic character and are able to extract lipophilic substances. Food simulant D1 shall be used for alcoholic foods with an alcohol content of above 20 % and for oil in water emulsions. Food simulant D2 shall be used for foods which contain free fats at the surface.

Food simulant E is assigned for testing specific migration into dry foods.

^{F13} **Specific assignment of food simulants to foods for migration testing of materials and articles not yet in contact with food**

For testing migration from materials and articles not yet in contact with food the food simulants that corresponds to a certain food category shall be chosen according to Table 2 below.

For testing migration from materials and articles intended to come into contact with foods not listed in Table 2 below, or a combination of foods, the general food simulant assignments in point 2 shall be used for specific migration testing, and for overall migration testing the food simulant assignments in point 4 shall be applicable.

Table 2 contains the following information:

— Column 1 (Reference number): contains the reference number of the food category

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

- Column 2 (Description of food): contains a description of the foods covered by the food category
- Column 3 (Food simulants): contains sub-columns for each of the food simulants

The food simulant for which a cross is contained in the respective sub-column of column 3 shall be used when testing migration of materials and articles not yet in contact with food.

For food categories where in sub-column D2 or E the cross is followed by an oblique stroke and a figure, the migration test result shall be corrected by dividing the result by this figure. The corrected test result shall then be compared to the migration limit to establish compliance. The test results for substances that shall not migrate in detectable quantities shall not be corrected in this way.

For food category 01.04 food simulant D2 shall be replaced by 95 % ethanol.

For food categories where in sub-column B the cross is followed by (*) the testing in food simulant B can be omitted if the food has a pH of more than 4,5.

For food categories where in sub-column D2 the cross is followed by (**) the testing in food simulant D2 can be omitted if it can be demonstrated that there is no 'fatty contact' with the plastic food contact material.]

TABLE 2

food category specific assignment of food simulants

(1) Reference number	(2) Description of food	(3) Food simulants					
		A	B	C	D1	D2	E
01	Beverages						
01.01	Non-alcoholic beverages or alcoholic beverages of an alcoholic strength lower than or equal to 6 % vol.:						
	A. Water, ciders, clear fruit or vegetable juices of normal strength	Clear drinks:	X(*)	X			

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

	or concentrated, fruit nectars, lemonades, syrups, bitters, infusions, coffee, tea, beers, soft drinks, energy drinks and the like, flavoured water, liquid coffee extract					
	B. cloudy drinks: juices and nectars and soft drinks containing fruit pulp, musts containing fruit pulp, liquid chocolate	X(*)			X	
01.02	Alcoholic beverages of an alcoholic strength of between 6 %vol and 20 %.			X		
01.03	Alcoholic beverages of an alcoholic strength above 20 % and				X	

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

	all cream liquors						
01.04	Miscellaneous: undenaturated ethyl alcohol	X(*)				Substitute 95 % ethanol	
02	Cereals, cereal products, pastry, biscuits, cakes and other bakers' wares						
02.01	Starches						X
02.02	Cereals, unprocessed, puffed, in flakes (including popcorn, corn flakes and the like)						X
02.03	Cereal flour and meal						X
02.04	Dry pasta e.g. macaroni, spaghetti and similar products and fresh pasta						X
02.05	Pastry, biscuits, cakes, bread, and other bakers' wares, dry:						
	A. With fatty					X/3	

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

		substances on the surface					
	B.	Other					X
02.06		Pastry, cakes, bread, dough and other bakers' wares, fresh:					
	A.	With fatty substances on the surface				X/3	
	B.	Other					X
03		Chocolate, sugar and products thereof Confectionery products					
03.01		Chocolate, chocolate- coated products, substitutes and products coated with substitutes				X/3	
03.02		Confectionery products:					
	A.	In solid form:					
	I.	With fatty substances				X/3	

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

		on the surface					
	II.	Other					X
	B.	In paste form:					
	I.	With fatty substances on the surface				X/2	
	II.	Moist		X			
03.03		Sugar and sugar products					
	A.	In solid form: crystal or powder					X
	B.	X Molasses, sugar syrups, honey and the like					
04		Fruit, vegetables and products thereof					
[^{F1} 04.01		Fruit, fresh or chilled:					
	A.	unpeeled and uncut					X/10

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

	B.	X peeled and/ or cut	X (*)				I
04.02	Processed fruit:						
	A.	Dried or dehydrated fruits, whole, sliced, flour or powder					X
	B.	Fruit in the form of purée, preserves, pastes or in its own juice or in sugar syrup (jams, compote, and similar products)	X(*)	X			
	C.	Fruit preserved in a liquid medium:					
	I.	In an				X	

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

		oily medium					
	II.	In an alcoholic medium			X		
04.03		Nuts (peanuts, chestnuts, almonds, hazelnuts, walnuts, pine kernels and others):					
	A.	Shelled, dried, flaked or powdered					X
	B.	Shelled and roasted					X
	C.	X In paste or cream form				X	
[^{F1} 04.04		Vegetables, fresh or chilled:					
	A.	unpeeled and uncut					X/10
	B.	X peeled and/or cut	X (*)				I
[^{F1} 04.05		Processed vegetables:					
	A.	Dried or dehydrated					X

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

	vegetables whole, sliced or in the form of flour or powder.					
B.	(<i>obsolete</i>)					
C.	Vegetables in the form of purée, preserves, pastes or in its own juice (including pickled and in brine).	X (*)	X			
D.	Preserved vegetables:					
I.	X In an oily medium				X	
II.	In an alcoholic medium			X		I
05	Fats and oils					
05.01	Animals and vegetable fats and				X	

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

	oils, whether natural or treated (including cocoa butter, lard, resolidified butter)						
05.02	Margarine, butter and other fats and oils made from water emulsions in oil					X/2	
06	Animal products and eggs						
06.01	Fish:						
	A. X Fresh, chilled, processed, salted or smoked including fish eggs					X/3(**)	
	B. Preserved fish:						
	I. X In an oily medium					X	
	II. In an aqueous medium	X(*)	X				
06.02	Crustaceans and molluscs (including						

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

	oysters, mussels, snails)						
	A.	Fresh within the shell					
	B.	Shell removed, processed, preserved or cooked with the shell					
	I.	X In an oily medium				X	
	II.	In an aqueous medium	X(*)	X			
06.03	Meat of all zoological species (including poultry and game):						
	A.	X Fresh, chilled, salted, smoked				X/4(**)	
	B.	X Processed meat products (such as ham, salami, bacon, sausages,				X/4(**)	

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

		and other) or in the form of paste, creams					
	C.	X Marinated meat products in an oily medium				X	
06.04	Preserved meat:						
	A.	X In an fatty or oily medium				X/3	
	B.	In an aqueous medium	X(*)		X		
06.05	Whole eggs, egg yolk, egg white						
	A.	Powdered or dried or frozen					X
	B.	Liquid and cooked			X		
07	Milk products						
07.01	Milk						

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

	A.	Milk and milk based drinks whole, partly dried and skimmed or partly skimmed			X		
	B.	Milk powder including infant formula (based on whole milk powder)					X
07.02		Fermented milk such as yoghurt, buttermilk and similar products	X(*)		X		
07.03		Cream and sour cream	X(*)		X		
07.04		Cheeses:					
	A.	Whole, with not edible rind					X
	B.	Natural cheese without rind or with edible				X/3(**)	

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

		rind (gouda, camembert, and the like) and melting cheese					
	C.	Processed cheese (soft cheese, cottage cheese and similar)	X(*)		X		
	D.	Preserved cheese:					
	I.	X In an oily medium				X	
	II.	In an aqueous medium (feta, mozzarella, and similar)	X(*)		X		
08	Miscellaneous products						
08.01	Vinegar		X				
08.02	Fried or roasted foods:						
	A.	X Fried potatoes, fritters and the like				X/5	

*Status: Point in time view as at 23/09/2020.**Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)*

	B.	X Of animal origin				X/4	
08.03		Preparations for soups, broths, sauces, in liquid, solid or powder form (extracts, concentrates); homogenised composite food preparations, prepared dishes including yeast and raising agents					
	A.	Powdered or dried:					
	I.	With fatty character				X/5	
	II.	Other					X
	B.	any other form than powdered or dried:					
	I.	X With fatty character	X(*)			X/3	
	II.	Other	X(*)	X			
08.04		Sauces:					

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

	A.	With aqueous character	X(*)	X			
	B.	X With fatty character e.g. mayonnaise, sauces derived from mayonnaise, salad creams and other oil/water mixtures e.g. coconut based sauces	X(*)			X	
08.05	Mustard (except powdered mustard under heading 08.14)	X	X(*)			X/3(**)	
08.06	Sandwiches, toasted bread pizza and the like containing any kind of foodstuff						
	A.	X With fatty substances on the surface				X/5	
	B.	Other					X

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

08.07	Ice-creams			X			
08.08	Dried foods:						
	A. With fatty substances on the surface					X/5	
	B. Other						X
08.09	Frozen or deep-frozen foods						X
08.10	Concentrated extracts of an alcoholic strength equal to or exceeding 6 % vol.		X(*)		X		
08.11	Cocoa:						
	A. Cocoa powder, including fat-reduced and highly fat reduced						X
	B. Cocoa paste					X/3	
08.12	Coffee, whether or not roasted, decaffeinated or soluble, coffee substitutes,						X

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

	granulated or powdered						
08.13	Aromatic herbs and other herbs such as camomile, mallow, mint, tea, lime blossom and others						X
08.14	Spices and seasonings in the natural state such as cinnamon, cloves, powdered mustard, pepper, vanilla, saffron, salt and other						X
08.15	Spices and seasoning in oily medium such as pesto, curry paste					X	

[^{F26}4. Food simulant assignment for testing overall migration

For tests to demonstrate compliance with the overall migration limit food simulants shall be chosen as set out in Table 3:

TABLE 3

Food simulant assignment for demonstrating compliance with the overall migration limit

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

Foods covered	Food simulants in which testing shall be performed
all types of food	<ol style="list-style-type: none"> 1. distilled water or water of equivalent quality or food simulant A; 2. food simulant B; and 3. food simulant D2.
all types of food except for acidic foods	<ol style="list-style-type: none"> 1. distilled water or water of equivalent quality or food simulant A; and 2. food simulant D2.
[^{F15} all aqueous and alcoholic foods and milk products with a pH ≥ 4,5	food simulant D1
all aqueous and alcoholic foods and milk products with a pH < 4,5	food simulant D1 and food simulant B]
all aqueous foods and alcoholic foods up to an alcohol content of 20 %	food simulant C
all aqueous and acidic foods and alcoholic foods up to an alcohol content of 20 %	<ol style="list-style-type: none"> 1. food simulant C; and 2. food simulant B.]

Textual Amendments

F26 Substituted by [Commission Regulation \(EU\) 2017/752 of 28 April 2017 amending and correcting Regulation \(EU\) No 10/2011 on plastic materials and articles intended to come into contact with food \(Text with EEA relevance\).](#)

[^{F25} General derogation to the assignment of food simulants

By derogation from the assignments of food simulants in points 2 to 4 of this Annex, where testing with several food simulants is required, a single food simulant shall be sufficient if on the basis of evidence acquired using generally recognised scientific methods this food simulant is shown to be the most severe food simulant for the particular material or article being tested under the applicable time and temperature conditions selected in accordance with Chapters 2 and 3 of Annex V.

The scientific basis on which this derogation is used shall in such cases form part of the documentation required under Article 16 of this Regulation.]

ANNEX IV

Declaration of compliance

The written declaration referred to in Article 15 shall contain the following information:

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

- (1) the identity and address of the business operator issuing the declaration of compliance;
- (2) the identity and address of the business operator which manufactures or imports the plastic materials or articles or products from intermediate stages of their manufacturing or the substances intended for the manufacturing of those materials and articles;
- (3) the identity of the materials, the articles, products from intermediate stages of manufacture or the substances intended for the manufacturing of those materials and articles;
- (4) the date of the declaration;
- (5) [^{F1}confirmation that the plastic materials or articles, products from intermediate stages of manufacture or the substances meet the relevant requirements laid down in this Regulation and in Article 3, 11(5), 15 and 17 of Regulation (EC) No 1935/2004;]
- (6) [^{F3}adequate information relative to the substances used or products of degradation thereof for which restrictions and/or specifications are set out in Annex I and II to the Regulation to allow the downstream business operators to ensure compliance with the Regulation.

At intermediate stages, this information shall include the identification and amount of substances in the intermediate material,

- that are subject to restrictions in Annex II, or
 - for which genotoxicity has not been ruled out, and which originate from an intentional use during a manufacturing stage of that intermediate material and which could be present in an amount that foreseeably gives rise to a migration from the final material exceeding 0,00015 mg/kg food or food simulant;]
- (7) adequate information relative to the substances which are subject to a restriction in food, obtained by experimental data or theoretical calculation about the level of their specific migration and, where appropriate, purity criteria in accordance with Directives 2008/60/EC, 95/45/EC and 2008/84/EC to enable the user of these materials or articles to comply with the relevant EU provisions or, in their absence, with national provisions applicable to food;
 - (8) specifications on the use of the material or article, such as:
 - (i) type or types of food with which it is intended to be put in contact;
 - (ii) time and temperature of treatment and storage in contact with the food;
 - (iii) [^{F26}the highest food contact surface area to volume ratio for which compliance has been verified in accordance with Article 17 and 18 or equivalent information;]
 - (9) when a functional barrier is used in a multi-layer material or article, the confirmation that the material or article complies with the requirements of Article 13(2), (3) and (4) or Article 14(2) and (3) of this Regulation.

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

ANNEX V

COMPLIANCE TESTING

For testing compliance of migration from plastic food contact materials and articles the following general rules apply.

CHAPTER 1

Testing for specific migration of materials and articles already in contact with food

1.1. Sample preparation

The material or article shall be stored as indicated on the packaging label or under conditions adequate for the packaged food if no instructions are given. The food shall be removed from contact with the material or article before its expiration date or any date by which the manufacturer has indicated the product should be used for reasons of quality or safety.

1.2. Conditions of testing

The food shall be treated in accordance with the cooking instructions on the package if the food is to be cooked in the package. Parts of the food which are not intended to be eaten shall be removed and discarded. The remainder shall be homogenised and analysed for migration. The analytical results shall always be expressed on the basis of the food mass that is intended to be eaten, in contact with the food contact material.

1.3. Analysis of migrated substances

The specific migration is analysed in the food using an analytical method in accordance with the requirements of Article 11 of Regulation (EC) No 882/2004.

[^F1.4. **Account of substances originating from other sources**

In case there is evidence linked to the food sample that a substance partially or wholly originates from a source or sources other than the material or article for which the test is being carried out, the test results shall be corrected for the amount of that substance originating from the other source or sources before comparing the test results to the applicable specific migration limit.]

CHAPTER 2

Testing for specific migration of materials and articles not yet in contact with food

2.1. Verification method

Verification of compliance of migration into foods with the migration limits shall be carried out under the most extreme conditions of time and temperature foreseeable in actual use taking into account paragraphs 1.4, 2.1.1, 2.1.6 and 2.1.7.

Verification of compliance of migration into food simulants with the migration limits shall be carried out using conventional migration tests according to the rules set out in paragraphs 2.1.1 to 2.1.7.

2.1.1. Sample preparation

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

The material or article shall be treated as described by accompanying instructions or by provisions given in the declaration of compliance.

Migration is determined on the material or article or, if this is impractical, on a specimen taken from the material or article, or a specimen representative of this material or article. For each food simulant or food type, a new test specimen is used. Only those parts of the sample which are intended to come into contact with foods in actual use shall be placed in contact with the food simulant or the food.

2.1.2. Choice of food simulant

Materials and articles intended for contact with all types of food shall be tested with food simulant A, B and D2. However, if substances that may react with acidic food simulant or foods are not present testing in food simulant B can be omitted.

Materials and articles intended only for specific types of foods shall be tested with the food simulants indicated for the food types in Annex III.

2.1.3. Conditions of contact when using food simulants

[^{F1}The sample shall be placed in contact with the food simulant in a manner representing the worst of the foreseeable conditions of use as regard contact time in Table 1 and as regard contact temperature in Table 2.

By way of derogation to the conditions set out in Tables 1 and 2, the following rules apply:

- (i) If it is found that carrying out the tests under the combination of contact conditions specified in Tables 1 and 2 causes physical or other changes in the test specimen which do not occur under worst foreseeable conditions of use of the material or article under examination, the migration tests shall be carried out under the worst foreseeable conditions of use in which these physical or other changes do not take place;
- (ii) if the material or article during its intended use is subjected only to precisely controlled time and temperature conditions in food processing equipment, either as part of food packaging or as part of the processing equipment itself, testing may be done using the worst foreseeable contact conditions that can occur during the processing of the food in that equipment;
- (iii) if the material or article is intended to be employed only for hot-fill conditions, only a 2-hour test at 70 °C shall be carried out. However, if the material or article is intended to be used also for storage at room temperature or below, the test conditions set out in Tables 1 and 2 of this Section or in Section 2.1.4 of this Chapter apply depending on the duration of storage.
- (iv) [^{F25}if the plastic material or article intended to come into contact with food of which the compliance must be verified becomes in its final application part of a food processing equipment or an appliance, or a part thereof, the migration tests may be carried out by determining the specific migration into the food or food simulant produced or processed by the whole equipment or appliance, or the part thereof, as appropriate, subject to the following conditions:
 - the food or food simulant is processed during testing by the equipment or part thereof in accordance with the worst foreseeable conditions that can be achieved if the equipment or its part is operated in accordance with its operating instructions, and
 - the migration from parts used for storage such as from reservoirs, containers, or capsules or pads which are part of the equipment during the processing of

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

the food, is determined using conditions representative for their use, unless the applied testing conditions for the whole tested equipment or appliance are representative also of their use.

When migration testing is done under the above conditions, and the transfer of constituents from the equipment or appliance as a whole does not exceed the migration limits, the plastic parts or materials present in the equipment or appliance shall be considered to comply with Article 11(1).

The testing of the parts used for storage or supply such as reservoirs, containers, capsules or pads shall be under conditions representative of their use, and shall include the foreseeable storage conditions of the food in these parts.

The supporting documentation referred to in Article 16 shall clearly document the testing on the whole food processing and/or food producing equipment or appliance, or on parts thereof. It shall demonstrate that the testing was representative of its foreseeable use, and shall indicate for which substances migration testing was carried out and provide all testing results. The manufacturer of individual plastic parts shall ensure the absence of migration for substances for which the Regulation specifies that their migration shall not be detectable at a specified level of detection in accordance with Article 11(4).

Compliance documentation supplied in accordance with the Regulation to the producer of the final equipment or appliance, or part thereof, shall list all substances subject to migration limits that might be exceeded under the foreseeable use of the supplied part or material.

When the result is not in compliance with the Regulation it shall be determined whether the source of the non-compliance is a plastic part subject to the Regulation or a part made from another material not subject to the Regulation on the basis of documentary evidence or analytical testing. Without prejudice to Article 3 of Regulation (EU) No 1935/2004, non-compliance to the Regulation shall only be established if the migration originates from a plastic part.]

If the testing conditions representative for the worst foreseeable conditions of intended use of the material or article, are not technically feasible in food simulant D2, migration tests shall be done using ethanol 95 % and isooctane. In addition a migration test shall be done using food simulant E if the temperature under the worst foreseeable conditions of intended use exceeds 100 °C. The test that results in the highest specific migration shall be used to establish compliance with this Regulation.]

TABLE 1

[^{F1}Selection of test time]

Contact time in worst foreseeable use	[^{F1}Time to be selected for testing]
$t \leq 5 \text{ min}$	5 min
$5 \text{ min} < t \leq 0,5 \text{ hour}$	0,5 hour
$0,5 \text{ hours} < t \leq 1 \text{ hour}$	1 hour
$1 \text{ hour} < t \leq 2 \text{ hours}$	2 hours
$2 \text{ hours} < t \leq 6 \text{ hours}$	6 hours
$6 \text{ hours} < t \leq 24 \text{ hours}$	24 hours

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

1 day < t ≤ 3 days	3 days
3 days < t ≤ 30 days	10 days
Above 30 days	See specific conditions

^[F1]TABLE 2

Selection of test temperature

Worst foreseeable contact temperature	Contact temperature to be selected for testing
T ≤ 5 °C	5 °C
5 °C < T ≤ 20 °C	20 °C
20 °C < T ≤ 40 °C	40 °C
40 °C < T ≤ 70 °C	70 °C
70 °C < T ≤ 100 °C	100 °C or reflux temperature
100 °C < T ≤ 121 °C	121 °C ^a
121 °C < T ≤ 130 °C	130 °C ^a
130 °C < T ≤ 150 °C	150 °C ^a
150 °C < T < 175 °C	175 °C ^a
175 °C < T ≤ 200 °C	200 °C ^a
T > 200 °C	225 °C ^a

- ^a This temperature shall be used only for food simulants D2 and E. For applications heated under pressure, migration testing under pressure at the relevant temperature may be performed. For food simulants A, B, C or D1 the test may be replaced by a test at 100 °C or at reflux temperature for duration of four times the time selected according to the conditions in Table 1.]

^[F12.1.4] Specific conditions for contact times above 30 days at room temperature and below

For contact times above 30 days (long term) at room temperature and below, the specimen shall be tested in accelerated test conditions at elevated temperature for a maximum of 10 days at 60 °C⁽²⁰⁾.

- Testing for 10 days at 20 °C shall cover all storage times at frozen condition. This test can include the freezing and defrosting processes if labelling or other instructions ensure that 20 °C is not exceeded and the total time above – 15 °C does not exceed 1 day in total during the foreseeable intended use of the material or article.
- Testing for 10 days at 40 °C shall cover all storage times at refrigerated and frozen conditions including hot-fill conditions and/or heating up to 70 °C ≤ T ≤ 100 °C for maximum $t = 120/2^{((T-70)/10)}$ minutes.
- Testing for 10 days at 50 °C shall cover all storage times of up to 6 months at room temperature, including hot-fill conditions and/or heating up to 70 °C ≤ T ≤ 100 °C for maximum $t = 120/2^{((T-70)/10)}$ minutes.

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

- (d) Testing for 10 days at 60 °C shall cover storage above 6 months at room temperature and below, including hot-fill conditions and/or heating up to 70 °C $\leq T \leq 100$ °C for maximum $t = 120/2^{((T-70)/10)}$ minutes.
- (e) For storage at room temperature the testing conditions can be reduced to 10 days at 40 °C if it is shown by scientific evidence that migration of the respective substance in the polymer has reached equilibration under this test condition.
- (f) For worst foreseeable conditions of intended use not covered by the test conditions set out in points (a) to (e), the testing time and temperature conditions shall be based on the following formula:

$$t_2 = t_1 * \text{Exp}(9627 * (1/T_2 - 1/T_1))$$

t1 is the contact time

t2 is the testing time

T1 is the contact temperature in Kelvin. For room temperature storage this is set at 298K (25 °C). For refrigerated conditions it is set at 278K (5 °C). For frozen storage it is set at 258 K (-15 °C).

T2 is the testing temperature in Kelvin.]

2.1.5. Specific conditions for combinations of contact times and temperature

[^{F1}If a material or article is intended for different applications covering different combinations of contact time and temperature the testing shall be restricted to the test conditions which are recognised to be the most severe on the basis of scientific evidence.]

If the material or article is intended for a food contact application where it is successively subject to a combination of two or more times and temperatures, the migration test shall be carried out subjecting the test specimen successively to all the applicable worst foreseeable conditions appropriate to the sample, using the same portion of food simulant.

[^{F3}2.1.6. *Repeated use materials and articles*

If the material or article is intended to come into repeated contact with foods, the migration test(s) shall be carried out three times on a single sample using another portion of food simulant on each occasion. The specific migration in the second test shall not exceed the level observed in the first test, and the specific migration in the third test shall not exceed the level observed in the second test.

Compliance of the material or article shall then be verified on the basis of the level of the migration found in the third test and on the basis of the stability of the material or article from the first to the third migration test. The stability of the material shall be considered insufficient if migration is observed above the level of detection in any of the three migration tests, and increases from the first migration test to the third migration test. In case of insufficient stability, compliance of the material shall not be established even in case the specific migration limit is not exceeded in any of the three tests.

However, if there is conclusive scientific proof that the level of the migration decreases in the second and third tests and if the migration limits are not exceeded on the first test, no further test is necessary.

Irrespective of the above rules, a material or article shall never be considered to comply with this Regulation if in the first test a substance that is prohibited from migrating or from being released in detectable quantities under Article 11(4) is detected.]

2.1.7. Analysis of migrating substances

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

At the end of the prescribed contact time, the specific migration is analysed in the food or food simulant using an analytical method in accordance with the requirements of Article 11 of Regulation (EC) No 882/2004.

2.1.8. Verification of compliance by residual content per food contact surface area (QMA)

For substances which are unstable in food simulant or food or for which no adequate analytical method is available it is indicated in Annex I that verification of compliance shall be undertaken by verification of residual content per 6 dm² of contact surface. For materials and articles between 500 ml and 10 l the real contact surface is applied. For materials and articles below 500 ml and above 10 l as well as for articles for which it is impractical to calculate the real contact surface the contact surface is assumed to be 6 dm² per kg food.

2.2. Screening approaches

[^{F1}To screen if a material or article complies with the migration limits any of the following approaches can be applied which are considered at least as severe as the verification method described in section 2.1.]

2.2.1. Replacing specific migration by overall migration

To screen for specific migration of non-volatile substances, determination of overall migration under test conditions at least as severe as for specific migration can be applied.

2.2.2. Residual content

To screen for specific migration the migration potential can be calculated based on the residual content of the substance in the material or article assuming complete migration.

[^{F1}2.2.3. *Migration modelling*

To screen for specific migration, the migration potential can be calculated based on the residual content of the substance in the material or article applying generally recognised diffusion models based on scientific evidence that are constructed in a way that must never underestimate real levels of migration.]

[^{F1}2.2.4. *Food simulant substitutes*

To screen for specific migration, food simulants can be replaced by substitute food simulants if it is based on scientific evidence that the substitute food simulants result in migration that is at least as severe as migration that would be obtained using the food simulants specified in Section 2.1.2.]

[^{F2}2.2.5. *Single test for successive combinations of time and temperature*

If the material or article is intended for a food contact application where it is successively subject to two or more time and temperature combinations, a single migration contact test time can be defined based on the highest contact test temperature from Section 2.1.3 and/or 2.1.4 by using the equation as described in point (f) of Section 2.1.4. The reasoning justifying that the resulting single test is at least as severe as the combined time and temperature combinations shall be documented in the supporting documentation provided for in Article 16.]

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

CHAPTER 3

Testing for overall migration

Overall migration testing shall be performed under the standardised testing conditions set out in this chapter.

3.1. Standardised testing conditions

The overall migration test for materials and articles intended for the food contact conditions described in column 3 of Table 3 shall be performed for the time specified and at the temperature specified in column 2. For test OM5 the test can be performed either for 2 hours at 100 °C (food simulant D2) or at reflux (food simulant A, B, C, D1) or for 1 hour at 121 °C. The food simulant shall be chosen in accordance with Annex III.

If it is found that carrying out the tests under the contact conditions specified in Table 3 causes physical or other changes in the test specimen which do not occur under worst foreseeable conditions of use of the material or article under examination, the migration tests shall be carried out under the worst foreseeable conditions of use in which these physical or other changes do not take place.

TABLE 3

Standardised conditions for testing the overall migration

Column 1	Column 2	Column 3
Test number	Contact time in days [d] or hours [h] at Contact temperature in [°C] for testing	Intended food contact conditions
OM0	30 min at 40 °C	Any food contact at cold or ambient temperatures and for a short duration (≤ 30 minutes).
OM1	10 d at 20 °C	Any food contact at frozen and refrigerated conditions
OM2	10 d at 40 °C	Any long-term storage at room temperature or below, including when packaged under hot-fill conditions, and/or heating up to a temperature T where $70\text{ °C} \leq T \leq 100\text{ °C}$ for a maximum of $t = 120/2^{(T-70)/10}$ minutes.
OM3	2 h at 70 °C	Any food contact conditions that include hot-fill and/or heating up to a temperature T where $70\text{ °C} \leq T \leq 100\text{ °C}$ for maximum of $t = 120/2^{(T-70)/10}$ minutes, which are not followed by

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

		long-term room temperature or refrigerated storage.
OM4	1 h at 100 °C or at reflux	High temperature applications for all types of food at temperature up to 100 °C.
OM5	2 h at 100 °C or at reflux or alternatively 1 h at 121 °C	High temperature applications up to 121 °C.
OM6	4 h at 100 °C or at reflux	Any food contact conditions at a temperature exceeding 40 °C, and with foods for which point 4 of Annex III assigns simulants A, B, C or D1.
OM7	2 h at 175 °C	High temperature applications with fatty foods exceeding the conditions of OM5.

Test OM 7 covers also food contact conditions described for OM0, OM1, OM2, OM3, OM4, OM5. It represents the worst case conditions for fatty food simulants in contact with non-polyolefins. In case it is technically not feasible to perform OM 7 with food simulant D2 the test can be replaced as set out in paragraph 3.2.

Test OM 6 covers also food contact conditions described for OM0, OM1, OM2, OM3, OM4 and OM5. It represents worst case conditions for food simulants A, B and C in contact with non-polyolefins.

Test OM 5 covers also food contact conditions described for OM0, OM1, OM2, OM3, OM4. It represents the worst case conditions for all food simulants in contact with polyolefins.

Test OM 2 covers also food contact conditions described for OM0, OM1 and OM3.]

[^{F1}3.2. Substitute overall migration tests for tests with food simulant D2

[^{F3}If it is not technically feasible to perform one or more of the tests OM0 to OM6 in food simulant D2, migration tests shall be done using ethanol 95 % and isooctane. In addition a test shall be done using food simulant E in case the worst foreseeable conditions of use exceed 100 °C. The test that results in the highest overall migration shall be used to establish compliance with the Regulation.

In case it is technically not feasible to perform OM7 with food simulant D2, either test OM8 or test OM9 shall be selected as a replacement test by selecting the most appropriate of these two tests on the basis of the intended and the foreseeable use of the material or article that is being tested. Subsequently, a migration test shall be done at each of the two test conditions specified for the selected test, using a new test sample for each test condition. The test condition that results in the higher overall migration shall be used to establish compliance with the Regulation.]

Test number	Test conditions	Intended food contact conditions	Covers the intended food contact conditions described in

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

OM8	Food simulant E for 2 hours at 175 °C and food simulant D2 for 2 hours at 100 °C	High temperature applications only	OM1, OM3, OM4, OM5 and OM6
OM9	Food simulant E for 2 hours at 175 °C and food simulant D2 for 10 days at 40 °C	High temperature applications including long term storage at room temperature	OM1, OM2, OM3, OM4, OM5 and OM6]

[^{F1}3.3. Verification of compliance

3.3.1. Single use articles and materials

At the end of the prescribed contact time, to verify compliance the overall migration is analysed in the food simulant using an analytical method in accordance with the requirements of Article 11 of Regulation (EC) No 882/2004.

[^{F3}3.3.2. Repeated use articles and materials

The applicable overall migration test shall be carried out three times on a single sample using another portion of food simulant on each occasion. The migration shall be determined using an analytical method in accordance with the requirements of Article 34 of Regulation (EU) 2017/625 of the European Parliament and of the Council⁽²¹⁾. The overall migration in the second test shall be lower than in the first test, and the overall migration in the third test shall be lower than in the second test. Compliance with the overall migration limit shall be verified on the basis of the level of the overall migration found in the third test.

If it is not technically feasible to test the same sample three times, such as when testing in vegetable oil, the overall migration test can be carried out by testing different samples for three different periods of time lasting one, two and three times the applicable contact test time. The difference between the third and the second test results shall be considered to represent the overall migration. Compliance shall be verified on the basis of this difference, which shall not exceed the overall migration limit. In addition, the difference between the second and the first test results shall be lower than the first test results and the difference between the third and the second test results shall be lower than the difference between the second and the first test results.

By derogation from the first paragraph, if, on the basis of scientific evidence, it is established that for the material or article being tested the overall migration decreases in the second and third tests and if the overall migration limit is not exceeded in the first test, the first test alone shall be sufficient.]]

3.4. Screening approaches

[^{F1}To screen if a material or article complies with the migration limits, any of the following approaches can be applied which are considered at least as severe as the verification method described in Sections 3.1 and 3.2.]

3.4.1. Residual content

To screen for overall migration the migration potential can be calculated based on the residual content of migratable substances determined in a complete extraction of the material or article.

[^{F1}3.4.2. Food simulant substitutes

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

To screen for overall migration, food simulants can be replaced if based on scientific evidence the substitute food simulants result in migration that is at least as severe as migration that would be obtained using the food simulants specified in Annex III.]

CHAPTER 4

Correction factors applied when comparing migration test results with migration limits

4.1. Correction of specific migration in foods containing more than 20 % fat by the Fat Reduction Factor (FRF)

For lipophilic substances for which in Annex I it is indicated in column 7 that the FRF is applicable the specific migration can be corrected by the FRF. The FRF is determined according to the formula $FRF = (g \text{ fat in food/kg of food})/200 = (\% \text{ fat} \times 5)/100$.

The FRF shall be applied according to the following rules.

The migration test results shall be divided by the FRF before comparing with the migration limits.

The correction by the FRF is not applicable in the following cases:

- (a) when the material or article is or is intended to be brought in contact with food intended for infants and young children as defined by Directives 2006/141/EC and 2006/125/EC;
- (b) for materials and articles for which it is impracticable to estimate the relationship between the surface area and the quantity of food in contact therewith, for example due to their shape or use, and the migration is calculated using the conventional surface area/volume conversion factor of 6 dm²/kg.

[^{F1}The specific migration in food or food simulant shall not exceed 60 mg/kg food before application of the FRF.]

[^{F2}When testing is performed in food simulant D2 or E and when the test results are corrected in application of the correction factor laid down in Table 2 of Annex III this correction may be applied in combination with the FRF by multiplying both factors. The combined correction factor shall not exceed 5, unless the correction factor laid down in Table 2 of Annex III exceeds 5.]

^{F4}4.2. Correction of migration into food simulant D2

.....

^{F4}4.3. Combination of correction factors 4.1 and 4.2.

.....

ANNEX VI

Correlation tables

Directive 2002/72/EC	This Regulation
----------------------	-----------------

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

Article 1(1)	Article 1
Article 1(2), (3) and (4)	Article 2
Article 1a	Article 3
Article 3(1), Article 4(1) and Article 5	Article 5
Article 4(2), Article 4a(1) and (4), Article 4d, Annex II (2) and (3) and Annex III (2) and (3)	Article 6
Article 4a(3) and (6)	Article 7
Annex II (4) and Annex III (4)	Article 8
Article 3(1) and Article 4(1)	Article 9
Article 6	Article 10
Article 5a(1) and Annex I (8)	Article 11
Article 2	Article 12
Article 7a	Article 13
Article 9(1) and (2)	Article 15
Article 9(3)	Article 16
Article 7 and Annex I (5a)	Article 17
Article 8	Article 18
Annex II (3) and Annex III (3)	Article 19
Annex I, Annex II, Annex IV, Annex IVa, Annex V Part B, and Annex VI	Annex I
Annex II (2), Annex III (2) and Annex V, Part A	Annex II
Article 8(5) and Annex VIa	Annex IV
Annex I	Annex V
Directive 93/8/EEC	This Regulation
Article 1	Article 11
Article 1	Article 12
Article 1	Article 18
Annex	Annex III
Annex	Annex V
Directive 97/48/EC	This Regulation
Annex	Annex III
Annex	Annex V

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

- (1) OJ L 338, 13.11.2004, p. 4.
- (2) OJ L 220, 15.8.2002, p. 18.
- (3) OJ L 44, 15.2.1978, p. 15.
- (4) OJ L 135, 30.5.2009, p. 3.
- (5) OJ L 354, 31.12.2008, p. 16.
- (6) OJ L 354, 31.12.2008, p. 34.
- (7) OJ L 31, 1.2.2002, p. 1.
- (8) SCF opinion of 4 December 2002 on the introduction of a Fat (Consumption) Reduction Factor (FRF) in the estimation of the exposure to a migrant from food contact materials.
http://ec.europa.eu/food/fs/sc/scf/out149_en.pdf
- (9) Opinion of the Scientific Panel on Food Additives, Flavourings, Processing Aids and Materials in Contact with Food (AFC) on a request from the Commission related to the introduction of a Fat (consumption) Reduction Factor for infants and children, The EFSA Journal (2004) 103, 1-8.
- (10) OJ L 297, 23.10.1982, p. 26.
- (11) OJ L 213, 16.8.1980, p. 42.
- (12) OJ L 167, 24.6.1981, p. 6.
- (13) OJ L 165, 30.4.2004, p. 1.
- (14) OJ L 384, 29.12.2006, p. 75.
- (15) OJ L 401, 30.12.2006, p. 1.
- (16) OJ L 339, 6.12.2006, p. 16.
- (17) OJ L 353, 31.12.2008, p. 1.
- (18) OJ L 372, 31.12.1985, p. 14.
- (19) [F³Regulation (EC) No 1907/2006 of the European Parliament and of the Council of 18 December 2006 concerning the Registration, Evaluation, Authorisation and Restriction of Chemicals (REACH), establishing a European Chemicals Agency, amending Directive 1999/45/EC and repealing Council Regulation (EEC) No 793/93 and Commission Regulation (EC) No 1488/94 as well as Council Directive 76/769/EEC and Commission Directives 91/155/EEC, 93/67/EEC, 93/105/EC and 2000/21/EC (OJ L 396, 30.12.2006, p. 1).:]
- (20) [F¹When testing at these accelerated test conditions the test specimen shall not undergo any physical or other changes compared to the real conditions of use, including a phase transition of the material.]
- (21) [F¹[F³Regulation (EU) 2017/625 of the European Parliament and of the Council of 15 March 2017 on official controls and other official activities performed to ensure the application of food and feed law, rules on animal health and welfare, plant health and plant protection products, amending Regulations (EC) No 999/2001, (EC) No 396/2005, (EC) No 1069/2009, (EC) No 1107/2009, (EU) No 1151/2012, (EU) No 652/2014, (EU) 2016/429 and (EU) 2016/2031 of the European Parliament and of the Council, Council Regulations (EC) No 1/2005 and (EC) No 1099/2009 and Council Directives 98/58/EC, 1999/74/EC, 2007/43/EC, 2008/119/EC and 2008/120/EC, and repealing Regulations (EC) No 854/2004 and (EC) No 882/2004 of the European Parliament and of the Council, Council Directives 89/608/EEC, 89/662/EEC, 90/425/EEC, 91/496/EEC, 96/23/EC, 96/93/EC and 97/78/EC and Council Decision 92/438/EEC (Official Controls Regulation) (OJ L 95, 7.4.2017, p. 1).]]

Textual Amendments

- F1** Substituted by Commission Regulation (EU) 2016/1416 of 24 August 2016 amending and correcting Regulation (EU) No 10/2011 on plastic materials and articles intended to come into contact with food (Text with EEA relevance).

Status: Point in time view as at 23/09/2020.

Changes to legislation: There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011. (See end of Document for details)

- F3** Substituted by Commission Regulation (EU) 2020/1245 of 2 September 2020 amending and correcting Regulation (EU) No 10/2011 on plastic materials and articles intended to come into contact with food (Text with EEA relevance).

Status:

Point in time view as at 23/09/2020.

Changes to legislation:

There are currently no known outstanding effects for the Commission Regulation (EU) No 10/2011.