Changes to legislation: There are outstanding changes not yet made to Commission Decision of 9 August 2005 establishing the classes of reaction-to-fire performance for certain construction products (notified under document number C(2005) 2925) (Text with EEA relevance) (2005/610/EC). Any changes that have already been made to the legislation appear in the content and are referenced with annotations. (See end of Document for details)

Commission Decision of 9 August 2005 establishing the classes of reaction-to-fire performance for certain construction products (notified under document number C(2005) 2925) (Text with EEA relevance) (2005/610/EC)

COMMISSION DECISION

of 9 August 2005

establishing the classes of reaction-to-fire performance for certain construction products

(notified under document number C(2005) 2925)

(Text with EEA relevance)

(2005/610/EC)

THE COMMISSION OF THE EUROPEAN COMMUNITIES,

Having regard to the Treaty establishing the European Community,

Having regard to Council Directive 89/106/EEC of 21 December 1988, on the approximation of laws, regulations and administrative provisions of the Member States relating to construction products⁽¹⁾, and in particular Article 20(2) a thereof,

Whereas:

- (1) Directive 89/106/EEC envisages that in order to take account of different levels of protection for the construction works at national, regional or local levels, it may be necessary to establish in the interpretative documents classes corresponding to the performance of products in respect of each essential requirement. Those documents have been published as the 'Communication of the Commission with regard to the interpretative documents of Directive 89/106/EEC⁽²⁾.
- (2) With respect of the essential requirement of safety in the event of fire, interpretative document No 2 lists a number of interrelated measures which together define the fire safety strategy to be developed in different ways in the Member States.
- (3) Interpretative document No 2 identifies one of those measures as the limitation of the generation and spread of fire and smoke within a given area by limiting the potential of construction products to contribute to the full development of a fire.
- (4) The level of that limitation may be expressed only in terms of the different levels of reaction-to-fire performance of the products in their end-use application.
- (5) By way of harmonised solution, a system of classes was adopted in Commission Decision 2000/147/EC of 8 February 2000 implementing Council Directive 89/106/ EEC as regard the classification of the reaction-to-fire performance of construction products⁽³⁾.

Changes to legislation: There are outstanding changes not yet made to Commission Decision of 9 August 2005 establishing the classes of reaction-to-fire performance for certain construction products (notified under document number C(2005) 2925) (Text with EEA relevance) (2005/610/EC). Any changes that have already been made to the legislation appear in the content and are referenced with annotations. (See end of Document for details)

- (6) In the case of certain construction products it is necessary to use the classification established in Decision 2000/147/EC.
- (7) The reaction-to-fire performance of many construction products and/or materials, within the classification provided for in Decision 2000/147/EC, is well established and sufficiently well known to fire regulators in Member States with the consequence that they do not require testing for this particular performance characteristic.
- (8) Products have been considered in relation to their end-use application, where relevant.
- (9) The measures provided for in this Decision are in accordance with the opinion of the Standing Committee on Construction,

HAS ADOPTED THIS DECISION:

Article 1

The construction products and/or materials which satisfy all the requirements of the performance characteristic 'reaction to fire' without need for further testing are set out in the Annex.

Article 2

The specific classes to be applied to different construction products and/or materials, within the reaction-to-fire classification adopted in Decision 2000/147/EC, are set out in the Annex to this Decision.

Article 3

This Decision is addressed to the Member States.

Done at Brussels, 9 August 2005.

For the Commission

Günter VERHEUGEN

Vice-President

Changes to legislation: There are outstanding changes not yet made to Commission Decision of 9 August 2005 establishing the classes of reaction-to-fire performance for certain construction products (notified under document number C(2005) 2925) (Text with EEA relevance) (2005/610/EC). Any changes that have already been made to the legislation appear in the content and are referenced with annotations. (See end of Document for details)

ANNEX

The tables set out in this Annex, list construction products and/or materials which satisfy all of the requirements for the performance characteristic reaction to fire without need for testing.

TABLE 1

CLASSES OF REACTION TO FIRE PERFORMANCE FOR GLULAM⁰

Material	Product detail	Minimum mean density ^b (kg/ m ³)	Minimum overall thickness(mm)	Class ^c
Glulam	Glued laminated timber products in accordance with EN 14080.	380	40	D-s2, d0

- a Applies to all species and glues covered by the product standard.
- b Conditioned according to EN 13238.
- c Class as provided for in Table 1 of the Annex to Decision 2000/147/EC.

TABLE 2

CLASSES OF REACTION TO FIRE PERFORMANCE OF LAMINATE FLOOR COVERINGS

Floor covering type ^a	Product detail	Minimum density(kg/m³)	Minimum overall thickness(mm)	Class ^b Floorings
Laminate floor coverings	Laminate floor coverings manufactured in accordance with EN 13329:2000.	800	6,5	$E_{ m FL}$

- $\textbf{a} \qquad \text{Floor covering loose laid over any wood based substrate} \geq \text{D-s2}, \, d0, \, \text{or any substrate of class A2-s1}, \, d0.$
- **b** Class as provided for in table 2 to the Annex to Decision 2000/147/EC.

TABLE 3

CLASSES OF REACTION TO FIRE PERFORMANCE OF RESILIENT FLOOR COVERINGS

Floor covering type ^a	EN product standard	Minimum mass(g/m²)	Maximum mass(g/m²)	Minimum overall thickness(mn	Class ^b Floorings
Plain and decorative Linoleum	EN 548	2 300	4 900	2	E_{FL}

- a Floor covering loose laid over any wood based substrate ≥ D-s2, d0, or any substrate of class A2-s1, d0.
- **b** Class as provided for in table 2 to the Annex to Decision 2000/147/EC.

Changes to legislation: There are outstanding changes not yet made to Commission Decision of 9 August 2005 establishing the classes of reaction-to-fire performance for certain construction products (notified under document number C(2005) 2925) (Text with EEA relevance) (2005/610/EC). Any changes that have already been made to the legislation appear in the content and are referenced with annotations. (See end of Document for details)

Homogeneous and heterogeneous polyvinyl chloride floor coverings		2 300	3 900	1,5	${ m E_{FL}}$
Polyvinyl chloride floor coverings with foam layer	EN 651	1 700	5 400	2	E_{FL}
Polyvinyl chloride floor covering with cork-based backing	EN 652	3 400	3 700	3,2	$\mathrm{E_{FL}}$
Expanded (cushioned) polyvinyl chloride floor coverings	EN 653	1 000	2 800	1,1	E_{FL}
Semi-flexible polyvinyl chloride tiles	EN 654	4 200	5 000	2	E_{FL}
Linoleum on corkment backing	EN 687	2 900	5 300	2,5	E _{FL}
Homogeneous and heterogeneous smooth rubber floor coverings with foam backing		3 400	4 300	4	$\mathrm{E_{FL}}$
Homogeneous and heterogeneous smooth rubber floor coverings		3 000	6 000	1,8	$\mathrm{E_{FL}}$
Homogeneous and heterogeneous relief		4 600	6 700	2,5	E_{FL}

a Floor covering loose laid over any wood based substrate ≥ D-s2, d0, or any substrate of class A2-s1, d0.

b Class as provided for in table 2 to the Annex to Decision 2000/147/EC.

Changes to legislation: There are outstanding changes not yet made to Commission Decision of 9 August 2005 establishing the classes of reaction-to-fire performance for certain construction products (notified under document number C(2005) 2925) (Text with EEA relevance) (2005/610/EC). Any changes that have already been made to the legislation appear in the content and are referenced with annotations. (See end of Document for details)

	bber floor verings					
a	a Floor covering loose laid over any wood based substrate ≥ D-s2, d0, or any substrate of class A2-s1, d0.					
b	b Class as provided for in table 2 to the Annex to Decision 2000/147/EC.					

TABLE 4

CLASSES OF REACTION TO FIRE PERFORMANCE OF TEXTILE FLOOR COVERINGS

Floor covering type ^a	EN product standard	Class ^b Floorings
Non-FR machine-made wall- to-wall pile carpets and pile carpet tiles ^c	EN 1307	$\mathrm{E_{FL}}$
Non-FR needled textile floor coverings without pile ^c	EN 1470	E_{FL}
Non-FR needled textile floor coverings with pile ^c	EN 13297	E_{FL}

- Floor covering glued or loose laid over a class A2-s1, d0 substrate
- b Class as provided for in table 2 to the Annex to Decision 2000/147/EC.
- Textile floor coverings having a total mass of max 4 800 g/m², a minimum pile thickness of 1,8 mm (ISO 1766) and:
 - a surface of 100 % wool,

 - a surface of 80 % wool or more 20 % polyamide or less, a surface of 80 % wool or more 20 % polyamide/polyester or less,
 - a surface of 100 % polyamide,
 - a surface of 100 % polypropylene and if with SBR-foam backing, a total mass of > 780 g/m². All polypropylene carpets with other foam backings are excluded.

Changes to legislation: There are outstanding changes not yet made to Commission Decision of 9 August 2005 establishing the classes of reaction-to-fire performance for certain construction products (notified under document number C(2005) 2925) (Text with EEA relevance) (2005/610/EC). Any changes that have already been made to the legislation appear in the content and are referenced with annotations. (See end of Document for details)

- (1) OJ L 40, 11.2.1989, p. 12. Directive as last amended by Regulation (EC) No 1882/2003 of the European Parliament and of the Council (OJ L 284, 31.10.2003, p. 1).
- (2) OJ C 62, 28.2.1994, p. 1.
- (3) OJ L 50, 23.2.2000, p. 14. Decision as last amended by Decision 2003/632/EC (OJ L 220, 3.9.2003, p. 5).

Status:

Point in time view as at 09/08/2005.

Changes to legislation:

There are outstanding changes not yet made to Commission Decision of 9 August 2005 establishing the classes of reaction-to-fire performance for certain construction products (notified under document number C(2005) 2925) (Text with EEA relevance) (2005/610/EC). Any changes that have already been made to the legislation appear in the content and are referenced with annotations.