

## ANNEX

13. In Annex IV, Part A, Section I, point 7, is replaced by the following:

<p>7.1. Whether or not listed among the CN codes in Annex V, Part B, wood in the form of chips, particles, sawdust, shavings, wood waste and scrap and obtained in whole or in part from:</p> <p>— <i>Acer saccharum</i> Marsh., originating in the USA and Canada,</p> <p>— <i>Platanus</i> L., originating in the USA or Armenia,</p> <p>— <i>Populus</i> L., originating in the American continent.</p>	<p>Official statement that the wood:</p> <p>(a) has been produced from debarked round wood,</p> <p>or</p> <p>(b) has undergone kiln-drying to below 20 % moisture content, expressed as a percentage of dry matter achieved through an appropriate time/temperature schedule,</p> <p>or</p> <p>(c) has undergone an appropriate fumigation to a specification approved in accordance with the procedure laid down in Article 18.2. There shall be evidence of the fumigation by indicating on the certificates referred to in Article 13.1.(ii), the active ingredient, the minimum wood temperature, the rate (<math>\text{g/m}^3</math>) and the exposure time (h),</p> <p>or</p> <p>(d) has undergone an appropriate heat treatment to achieve a minimum core temperature of 56 °C for at least 30 minutes, the latter to be indicated on the certificates referred to in Article 13.1.(ii).</p>
<p>7.2. Whether or not listed among the CN codes in Annex V, Part B, wood in the form of chips, particles, sawdust, shavings, wood waste and scrap and obtained in whole or part from <i>Quercus</i> L. originating in the USA.</p>	<p>Official statement that the wood:</p> <p>(a) has undergone kiln-drying to below 20 % moisture content, expressed as a percentage of dry matter achieved through an appropriate time/temperature schedule,</p> <p>or</p> <p>(b) has undergone an appropriate fumigation to a specification approved in accordance with the procedure laid down in Article 18.2. There shall be evidence of the fumigation by indicating on the certificates referred to in Article 13.1.(ii), the active ingredient, the minimum wood temperature, the rate (<math>\text{g/m}^3</math>) and the exposure time (h),</p> <p>or</p>

---

**Status:** EU Directives are being published on this site to aid cross referencing from UK legislation. After IP completion day (31 December 2020 11pm) no further amendments will be applied to this version.

---

- 
- |     |  |
|-----|--|
| (c) | has undergone an appropriate heat treatment to achieve a minimum core temperature of 56 °C for at least 30 minutes, the latter to be indicated on the certificates referred to in 13.1.(ii). |
|-----|--|
-