

Commission Regulation (EU) No 10/2011 of 14 January 2011 on plastic materials and articles intended to come into contact with food (Text with EEA relevance)

ANNEX I

Substances

1. Union list of authorised monomers, other starting substances, macromolecules obtained from microbial fermentation, additives and polymer production aids

Table 1 contains the following information:

Column 1 (FCM substance No): the unique identification number of the substance

Column 2 (Ref. No): the EEC packaging material reference number

Column 3 (CAS No): the Chemical Abstracts Service (CAS) registry number

Column 4 (Substance Name): the chemical name

Column 5 (Use as additive or polymer production aid (PPA) (yes/no)): an indication if the substance is authorised to be used as additive or polymer production aid (yes) or if the substance is not authorised to be used as additive or polymer production aid (no). If the substance is only authorised as PPA it is indicated (yes) and in the specifications the use is restricted to PPA.

Column 6 (Use as monomer or other starting substance or macromolecule obtained from microbial fermentation (yes/no)): an indication if the substance is authorised to be used as monomer or other starting substance or macromolecule obtained from microbial fermentation (yes) or if the substance is not authorised to be used as monomer or other starting substance or macromolecule obtained from microbial fermentation (no). If the substance is authorised as macromolecule obtained from microbial fermentation it is indicated (yes) and in the specifications it is indicated that the substance is a macromolecule obtained from microbial fermentation.

Column 7 (FRF applicable (yes/no)): an indication if for the substance the migration results can be corrected by the Fat Consumption Reduction Factor (FRF) (yes) or if they cannot be corrected by the FRF (no).

Column 8 (SML [mg/kg]): the specific migration limit applicable for the substance. It is expressed in mg substance per kg food. It is indicated ND if the substance shall not migrate in detectable quantities.

Column 9 (SML(T) [mg/kg] (group restriction No)): contains the identification number of the group of substances for which the group restriction in Column 1 in Table 2 of this Annex applies.

Column 10 (Restrictions and specifications): contains other restrictions than the specific migration limit specifically mentioned and it contains specifications related to the substance. In case detailed specifications are set out a reference to Table 4 is included.

Column 11 (Notes on verification of compliance): contains the Notes number which refers to the detailed rules applicable for verification of compliance for this substance included in Column 1 in Table 3 of this Annex.

If a substance appearing on the list as an individual compound is also covered by a generic term, the restrictions applying to this substance shall be those indicated for the individual compound.

If in Column 8 the specific migration limit is non-detectable (ND) a detection limit of 0,01 mg substance per kg food is applicable unless specified differently for an individual substance.

TABLE 1

| (1) | (2) | (3) | (4) | (5) | (6) | (7) | (8) | (9) | (10) | (11) |
|------------------|---------|---------|--|---|---|---------------------|----------------------|--|--|-------------------------------------|
| FCM substance No | Ref. No | CAS No | Substance name | Use as additive or polymer product aid (yes/no) | Use as monomer or other starting substance or macromolecule obtained from microbial fermentation (yes/no) | FRF applicable (no) | SML [mg/kg] (yes/no) | SML (T) [mg/kg] (Group restriction No) | Restrictions and specifications | Notes on verification of compliance |
| 1 | 12310 | 0266309 | albumin | no | yes | no | | | | |
| 2 | 12340 | — | albumin coagulated by formaldehyde | no | yes | no | | | | |
| 3 | 12375 | — | alcohols, aliphatic, monohydric, saturated, linear, primary (C ₄ -C ₂₂) | no | yes | no | | | | |
| 4 | 22332 | — | mixture of (40 % w/w) 2,2,4-trimethylhexane-1,6-diisocyanate and (60 % w/w) 2,4,4-trimethylhexane-1,6-diisocyanate | no | yes | no | | (17) | 1 mg/kg in final product expressed as isocyanate moiety. | (10) |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | | |
|---|-------|---|---|-----|-----|----|------|------|--|-----|
| 5 | 25360 | — | trialkyl(C ₆ -C ₁₅)acetic acid, 2,3-epoxypropyl ester | no | yes | no | ND | | 1 mg/kg in final product expressed as epoxygroup. Molecular weight is 43 Da. | |
| 6 | 25380 | — | trialkyl acetic acid (C ₇ -C ₁₇), vinyl esters | no | yes | no | 0,05 | | | (1) |
| 7 | 30370 | — | acetylates acid, salts | yes | no | no | | | | |
| 8 | 30401 | — | acetylates mono- and diglycerides of fatty acids | yes | no | no | | (32) | | |
| 9 | 30610 | — | acids, C ₂ -C ₂₄ , aliphatic, linear, monocarboxylic from natural oils and fats, and their mono-, di- and triglycerol | yes | no | no | | | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | | |
|----|-------|---|--|----|----|--|--|--|--|--|
| | | | esters (branched fatty acids at naturally occurring levels are included) | | | | | | | |
| 10 | 30612 | — | acids, yes C ₂ - C ₂₄ , aliphatic, linear, monocarboxylic, synthetic and their mono-, di- and triglycerol esters | no | no | | | | | |
| 11 | 30960 | — | acids, yes aliphatic, monocarboxylic (C ₆ - C ₂₂), esters with polyglycerol | no | no | | | | | |
| 12 | 31328 | — | acids, yes fatty, from animal or vegetable food fats and oils | no | no | | | | | |
| 13 | 33120 | — | alcohols, yes aliphatic, monohydric, | no | no | | | | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | | |
|----|-------|---|---|-----|----|-----|----|-----|--|--|
| | | | saturated, linear, primary (C ₄ - C ₂₄) | | | | | | | |
| 14 | 33801 | — | n- alkyl(C ₁₀ - C ₁₃)benzenesulphonic acid | yes | no | no | 30 | | | |
| 15 | 34130 | — | alkyl, linear with even number of carbon atoms (C ₁₂ - C ₂₀) dimethylamines | yes | no | yes | 30 | | | |
| 16 | 34230 | — | alkyl(C ₈ - C ₂₂)sulphonic acids | yes | no | no | 6 | | | |
| 17 | 34281 | — | alkyl(C ₈ - C ₂₂)sulphuric acids, linear, primary with an even number of carbon atoms | yes | no | no | | | | |
| 18 | 34475 | — | aluminium, calcium hydroxide phosphite, hydrate | yes | no | no | | | | |
| 19 | 39090 | — | N,N- bis(2- | yes | no | no | | (7) | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | |
|----|-------|---|--|-----|----|----|-----|-----|--------------------------------|
| | | | hydroxyethyl)alkyl(C ₈ -C ₁₈)amine | | | | | | |
| 20 | 39120 | — | N,N-bis(2-hydroxyethyl)alkyl(C ₈ -C ₁₈)amine hydrochlorides | yes | no | no | | (7) | SML(T) expressed excluding HCl |
| 21 | 42500 | — | carbonic acid, salts | yes | no | no | | | |
| 22 | 43200 | — | castor oil, mono- and diglycerides | yes | no | no | | | |
| 23 | 43515 | — | chlorides of choline esters of coconut oil fatty acids | yes | no | no | 0,9 | | (1) |
| 24 | 45280 | — | cotton fibers | yes | no | no | | | |
| 25 | 45440 | — | cresols, butylated, styrenated | yes | no | no | 12 | | |
| 26 | 46700 | — | 5,7-di-tert-butyl-3-(3,4- and 2,3-dimethylphenyl)-3H-benzofuran-2-one containing: a) 5,7-di-tert-butyl-3- | yes | no | no | 5 | | |

a [OJ L 302, 19.11.2005, p. 28.](#)

b [OJ L 330, 5.12.1998, p. 32.](#)

c [OJ L 253, 20.9.2008, p. 1.](#)

d [OJ L 226, 22.9.1995, p. 1.](#)

e [OJ L 158, 18.6.2008, p. 17.](#)

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | | |
|----|-------|---|--|-----|----|----|---|------|--|--|
| | | | (3,4-dimethylphenyl)-3H-benzofuran-2-one (80 to 100 % w/w) and b) 5,7-di-tert-butyl-3-(2,3-dimethylphenyl)-3H-benzofuran-2-one (0 to 20 % w/w) | | | | | | | |
| 27 | 48960 | — | 9,10-dihydroxy stearic acid and its oligomers | yes | no | no | 5 | | | |
| 28 | 50160 | — | di-n-octyltin bis(n-alkyl(C ₁₀ -C ₁₆) mercaptoacetate) | yes | no | no | | (10) | | |
| 29 | 50360 | — | di-n-octyltin bis(ethyl maleate) | yes | no | no | | (10) | | |
| 30 | 50560 | — | di-n-octyltin 1,4-butanediol bis(mercaptoacetate) | yes | no | no | | (10) | | |
| 31 | 50800 | — | di-n-octyltin dimaleate, esterified | yes | no | no | | (10) | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | | |
|----|-------|---|--|-----|----|----|--|------|--|--|
| 32 | 50880 | — | di-n-octyltin dimaleate, polymers (n = 2-4) | yes | no | no | | (10) | | |
| 33 | 51120 | — | di-n-octyltin thiobenzoate 2-ethylhexyl mercaptoacetate | yes | no | no | | (10) | | |
| 34 | 54270 | — | ethylhydroxyethylcellulose | yes | no | no | | | | |
| 35 | 54280 | — | ethylhydroxypropylcellulose | yes | no | no | | | | |
| 36 | 54450 | — | fats and oils, from animal or vegetable food sources | yes | no | no | | | | |
| 37 | 54480 | — | fats and oils, hydrogenated, from animal or vegetable food sources | yes | no | no | | | | |
| 38 | 55520 | — | glass fibers | yes | no | no | | | | |
| 39 | 55600 | — | glass microballs | yes | no | no | | | | |
| 40 | 56360 | — | glycerol esters with | yes | no | no | | | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | |
|----|-------|---|--|-----|----|----|--|--|--|
| | | | acetic acid | | | | | | |
| 41 | 56486 | — | glycerol, esters with acids, aliphatic, saturated, linear, with an even number of carbon atoms (C ₁₄ -C ₁₈) and with acids, aliphatic, unsaturated, linear, with an even number of carbon atoms (C ₁₆ -C ₁₈) | yes | no | no | | | |
| 42 | 56487 | — | glycerol, esters with butyric acid | yes | no | no | | | |
| 43 | 56490 | — | glycerol, esters with erucic acid | yes | no | no | | | |

a [OJ L 302, 19.11.2005, p. 28.](#)

b [OJ L 330, 5.12.1998, p. 32.](#)

c [OJ L 253, 20.9.2008, p. 1.](#)

d [OJ L 226, 22.9.1995, p. 1.](#)

e [OJ L 158, 18.6.2008, p. 17.](#)

| | | | | | | | | | | |
|----|-------|---|---|-----|----|----|--|--|--|--|
| 44 | 56495 | — | glycerol esters with 12-hydroxystearic acid | yes | no | no | | | | |
| 45 | 56500 | — | glycerol esters with lauric acid | yes | no | no | | | | |
| 46 | 56510 | — | glycerol esters with linoleic acid | yes | no | no | | | | |
| 47 | 56520 | — | glycerol esters with myristic acid | yes | no | no | | | | |
| 48 | 56535 | — | glycerol esters with nonanoic acid | yes | no | no | | | | |
| 49 | 56540 | — | glycerol esters with oleic acid | yes | no | no | | | | |
| 50 | 56550 | — | glycerol esters with palmitic acid | yes | no | no | | | | |
| 51 | 56570 | — | glycerol esters with propionic acid | yes | no | no | | | | |

a [OJ L 302, 19.11.2005, p. 28.](#)

b [OJ L 330, 5.12.1998, p. 32.](#)

c [OJ L 253, 20.9.2008, p. 1.](#)

d [OJ L 226, 22.9.1995, p. 1.](#)

e [OJ L 158, 18.6.2008, p. 17.](#)

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | | |
|----|-------|---|---|-----|----|----|--|--|--|--|
| 52 | 56580 | — | glycerol esters with ricinoleic acid | yes | no | no | | | | |
| 53 | 56585 | — | glycerol esters with stearic acid | yes | no | no | | | | |
| 54 | 57040 | — | glycerol monooleate, ester with ascorbic acid | yes | no | no | | | | |
| 55 | 57120 | — | glycerol monooleate, ester with citric acid | yes | no | no | | | | |
| 56 | 57200 | — | glycerol monopalmitate, ester with ascorbic acid | yes | no | no | | | | |
| 57 | 57280 | — | glycerol monopalmitate, ester with citric acid | yes | no | no | | | | |
| 58 | 57600 | — | glycerol monostearate, ester with ascorbic acid | yes | no | no | | | | |
| 59 | 57680 | — | glycerol monostearate, | yes | no | no | | | | |

a [OJ L 302, 19.11.2005, p. 28.](#)

b [OJ L 330, 5.12.1998, p. 32.](#)

c [OJ L 253, 20.9.2008, p. 1.](#)

d [OJ L 226, 22.9.1995, p. 1.](#)

e [OJ L 158, 18.6.2008, p. 17.](#)

| | | | | | | | | | |
|----|-------|---|--|-----|----|----|--|------|--|
| | | | ester with citric acid | | | | | | |
| 60 | 58300 | — | glycine, salts | yes | no | no | | | |
| 62 | 64500 | — | lysine, salts | yes | no | no | | | |
| 63 | 65440 | — | manganese pyrophosphate | yes | no | no | | | |
| 64 | 66695 | — | methylhydroxymethylcellulose | yes | no | no | | | |
| 65 | 67155 | — | mixture of 4-(2-benzoxazolyl)-4'-(5-methyl-2-benzoxazolyl)stilbene, 4,4'-bis(2-benzoxazolyl)stilbene and 4,4'-bis(5-methyl-2-benzoxazolyl)stilbene | yes | no | no | | | Not more than 0,05 % (w/w) (quantity of substance used/ quantity of the formulation). Mixture obtained from the manufacturing process in the typical ratio of (58-62 %): (23-27 %): (13-17 %). |
| 66 | 67600 | — | mono-n-octyltin tris(alkyl(C ₁₀ -C ₁₆) mercaptoacetate) | yes | no | no | | (11) | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | | |
|----|-------|---|--|-----|----|-----|------|------|--|--|
| 67 | 67840 | — | montanic acids and/or their esters with ethyleneglycol and/or with 1,3- butanediol and/or with glycerol | yes | no | no | | | | |
| 68 | 73160 | — | phosphoric acid, mono- and di- n-alkyl (C ₁₆ and C ₁₈) esters | yes | no | yes | 0,05 | | | |
| 69 | 74400 | — | phosphoric acid, tris(nonyl- and/or dinonylphenyl) ester | yes | no | yes | 30 | | | |
| 70 | 76463 | — | polyacrylic acid, salts | yes | no | no | | (22) | | |
| 71 | 76730 | — | polydimethylsiloxane, γ- hydroxypropylated | yes | no | no | 6 | | | |
| 72 | 76815 | — | polyester of adipic acid with glycerol or pentaerythritol, | yes | no | no | | (32) | The fraction with molecular weight below 1 000 Da | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | esters with even numbered, unbranched C ₁₂ -C ₂₂ fatty acids | | | | | should not exceed 5 % (w/w) |
|----|-------|---|---|-----|----|-----|--------------|-----------------------------|
| 73 | 76866 | — | polyesters of 1,2-propanediol and/or 1,3- and/or 1,4-butanediol and/or polypropyleneglycol with adipic acid, which may be end-capped with acetic acid or fatty acids C ₁₂ -C ₁₈ or n-octanol and/or n-decanol | yes | no | yes | (31) (32) | |
| 74 | 77440 | — | polyethyleneglycol diricinoleate | yes | no | yes | 42 | |
| 75 | 77702 | — | polyethyleneglycol esters of | yes | no | no | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | |
|----|-------|---|--|-----|----|----|------|--|---------------------|
| | | | aliph. monocarb. acids (C ₆ -C ₂₂) and their ammonium and sodium sulphates | | | | | | |
| 76 | 77732 | — | polyethylene glycol (EO = 1-30, typically 5) ether of butyl 2-cyano-3-(4-hydroxy-3-methoxyphenyl) acrylate | yes | no | no | 0,05 | | Only for use in PET |
| 77 | 77733 | — | polyethylene glycol (EO = 1-30, typically 5) ether of butyl-2-cyano-3-(4-hydroxyphenyl) acrylate | yes | no | no | 0,05 | | Only for use in PET |
| 78 | 77897 | — | polyethylene glycol monoalkylether (linear and branched, | yes | no | no | 5 | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | |
|----|-------|---|--|-----|----|----|--|--|--|
| | | | C ₈ - C ₂₀) sulphate, salts | | | | | | |
| 79 | 80640 | — | polyoxyalkyl (C ₂ - C ₄) dimethylpolysiloxane | no | no | | | | |
| 80 | 81760 | — | powders flakes and fibres of brass, bronze, copper, stainless steel, tin, iron and alloys of copper, tin and iron | yes | no | no | | | |
| 81 | 83320 | — | propylhydroxyethylcellulose | yes | no | no | | | |
| 82 | 83325 | — | propylhydroxymethylcellulose | yes | no | no | | | |
| 83 | 83330 | — | propylhydroxypropylcellulose | yes | no | no | | | |
| 84 | 85601 | — | silicates, natural (with the exception of asbestos) | yes | no | no | | | |
| 85 | 85610 | — | silicates, natural, silanated (with the exception | yes | no | no | | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | | |
|----|-------|---|---|-----|----|-----|------|-----|--|---|
| | | | of asbestos) | | | | | | | |
| 86 | 86000 | — | silicic acid, silylated | yes | no | no | | | | |
| 87 | 86285 | — | silicon dioxide, silanated | yes | no | no | | | | |
| 88 | 86880 | — | sodium monoalkyl dialkylphenoxybenzenedisulphonate | yes | no | no | 9 | | | |
| 89 | 89440 | — | stearic acid, esters with ethyleneglycol | yes | no | no | | (2) | | |
| 90 | 92195 | — | taurine, salts | yes | no | no | | | | |
| 91 | 92320 | — | tetradecyl polyethyleneglycol (EO = 3-8) ether of glycolic acid | yes | no | yes | 15 | | | |
| 92 | 93970 | — | tricyclic bis(hexahydrophthalate) | yes | no | no | 0,05 | | | |
| 93 | 95858 | — | waxes, paraffinic, refined, derived from petroleum based or synthetic hydrocarbon feedstocks, low viscosity | yes | no | no | 0,05 | | | Not to be used for articles in contact with fatty foods for which simulant D is |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | |
|----------|------------------------------|---|--|-----|----|----|--|--|--|
| | | | | | | | | | laid down. Average molecular weight not less than 350 Da. Viscosity at 100 °C not less than 2,5 cSt (2,5 × 10 ⁻⁶ m ² /s). Content of hydrocarbons with Carbon number less than 25, not more than 40 % (w/w). |
| 94 | 95859 | — | waxes, refined, derived from petroleum based or synthetic hydrocarbon feedstocks, high viscosity | yes | no | no | | | Average molecular weight not less than 500 Da. Viscosity at 100 °C not |
| a | OJ L 302, 19.11.2005, p. 28. | | | | | | | | |
| b | OJ L 330, 5.12.1998, p. 32. | | | | | | | | |
| c | OJ L 253, 20.9.2008, p. 1. | | | | | | | | |
| d | OJ L 226, 22.9.1995, p. 1. | | | | | | | | |
| e | OJ L 158, 18.6.2008, p. 17. | | | | | | | | |

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | |
|----|-------|---|---|-----|----|----|--|--|--|
| | | | | | | | | | less than 11 cSt ($11 \times 10^{-6} \text{ m}^2/\text{s}$). Content of mineral hydrocarbons with Carbon number less than 25, not more than 5 % (w/w). |
| 95 | 95883 | — | white mineral oils, paraffinic, derived from petroleum based hydrocarbon feedstocks | yes | no | no | | | Average molecular weight not less than 480 Da. Viscosity at 100 °C not less than 8,5 cSt ($8,5 \times 10^{-6} \text{ m}^2/\text{s}$). Content of mineral hydrocarbons with Carbon number |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | |
|----|----------|---|---|-----|----|----|--|--|--|
| | | | | | | | | | less than 25, not more than 5 % (w/w). |
| 96 | 95920 | — | wood flour and fibers, untreated | yes | no | no | | | |
| 97 | 72081/10 | — | petroleum hydrocarbon resins (hydrogenated) | yes | no | no | | | Petroleum hydrocarbon resins, hydrogenated are produced by the catalytic or thermal polymerisation of dienes and olefins of the aliphatic, alicyclic and/or monobenzenoidarylalkene types from distillates of cracked petroleum stocks with a boiling range not greater than 220 °C, |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | |
|----------|------------------------------|--|--|--|--|--|--|---|
| | | | | | | | | as well as the pure monomers found in these distillation streams, subsequently followed by distillation, hydrogenation and additional processing. Properties: — Viscosity at 120 °C: > 3 Pa.s, — Softening point: > 95 °C as determined by ASTM Method E 28-67, — Bromine number: < 40 (ASTM D1159), — The colour of a 50 % solution in toluene < 11 |
| a | OJ L 302, 19.11.2005, p. 28. | | | | | | | |
| b | OJ L 330, 5.12.1998, p. 32. | | | | | | | |
| c | OJ L 253, 20.9.2008, p. 1. | | | | | | | |
| d | OJ L 226, 22.9.1995, p. 1. | | | | | | | |
| e | OJ L 158, 18.6.2008, p. 17. | | | | | | | |

| | | | | | | | | | | on the Gardner scale, Residual aromatic monomer ≤ 50 ppm, |
|-----|-------|--------------------------|----------------------------------|-----|-----|----|------|--|--|---|
| 98 | 17260 | 0000050600 | Formaldehyde | yes | no | | (15) | | | |
| | 54880 | | | | | | | | | |
| 99 | 19460 | 0000050621 | Lactic acid | yes | yes | no | | | | |
| | 62960 | | | | | | | | | |
| 100 | 24490 | 0000050507 | Sorbitol | yes | yes | no | | | | |
| | 88320 | | | | | | | | | |
| 101 | 36000 | 0000050807 | Ascorbic acid | yes | no | no | | | | |
| 102 | 17530 | 0000050907 | Glucose | no | yes | no | | | | |
| 103 | 18100 | 0000050816 | Glycerol | yes | yes | no | | | | |
| | 55920 | | | | | | | | | |
| 104 | 58960 | 0000057020 | Dodecyltrimethylammonium bromide | yes | yes | no | 6 | | | |
| 105 | 22780 | 0000057101 | Phthalic acid | yes | yes | no | | | | |
| | 70400 | | | | | | | | | |
| 106 | 24550 | 0000057101 | Stearic acid | yes | yes | no | | | | |
| | 89040 | | | | | | | | | |
| 107 | 25960 | 0000057136 | Urea | no | yes | no | | | | |
| 108 | 24880 | 0000057501 | Sorbitose | no | yes | no | | | | |
| 109 | 23740 | 0000057136 | 1,2-propanediol | yes | yes | no | | | | |
| | 81840 | | | | | | | | | |
| 110 | 93520 | 0000059029 0010191400 | 1-Deoxy-D-xylitol | yes | no | no | | | | |
| 111 | 53600 | 0000060014 | Benzoic acid | yes | no | no | | | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | |
|-----|-------|--------------|--------------------|-----|-----|----|----|-----|--------------------------|
| 112 | 64015 | 0000060133-3 | lactic acid | yes | no | no | | | |
| 113 | 16780 | 0000064177-5 | ethanol | yes | yes | no | | | |
| | 52800 | | | | | | | | |
| 114 | 55040 | 0000064181-6 | formic acid | yes | no | no | | | |
| 115 | 10090 | 0000064191-7 | acetic acid | yes | yes | no | | | |
| | 30000 | | | | | | | | |
| 116 | 13090 | 0000065851-0 | benzoic acid | yes | yes | no | | | |
| | 37600 | | | | | | | | |
| 117 | 21550 | 0000067561-1 | methanol | no | yes | no | | | |
| 118 | 23830 | 0000067263-0 | propanol | yes | yes | no | | | |
| | 81882 | | | | | | | | |
| 119 | 30295 | 0000067661-0 | acetone | yes | no | no | | | |
| 120 | 49540 | 0000067668-1 | diethyl sulphoxide | no | no | no | | | |
| 121 | 24270 | 0000069571-7 | salicylic acid | yes | yes | no | | | |
| | 84640 | | | | | | | | |
| 122 | 23800 | 0000071123-8 | propanol | no | yes | no | | | |
| 123 | 13840 | 0000071136-3 | butanol | no | yes | no | | | |
| 124 | 22870 | 0000071141-0 | pentanol | no | yes | no | | | |
| 125 | 16950 | 0000074815-1 | ethylene | no | yes | no | | | |
| 126 | 10210 | 0000074861-2 | ethylene | no | yes | no | | | |
| 127 | 26050 | 0000075011-4 | vinyl chloride | no | yes | no | ND | | 1 mg/kg in final product |
| 128 | 10060 | 0000075071-0 | acetaldehyde | yes | no | no | | (1) | |
| 129 | 17020 | 0000075071-0 | ethylene oxide | no | yes | no | ND | | 1 mg/kg in (10) |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | final product | |
|-----|----------------|--------------|--|-----|-----|-----|------|---|------|
| 130 | 26110 | 0000075354 | vinylidene chloride | yes | no | ND | | | (1) |
| 131 | 48460 | 0000075437-6 | 1,1-difluoroethane | yes | no | no | | | |
| 132 | 26140 | 0000075387 | vinylidene fluoride | yes | no | 5 | | | |
| 133 | 14380 23155 | 0000075416 | vinylidene chloride | yes | no | ND | | 1 mg/kg in final product | (10) |
| 134 | 43680 | 0000075456 | 1,1-dichloro-1,1-difluoroethane | yes | no | 6 | | Content of chlorofluoromethane less than 1 mg/kg of the substance | |
| 135 | 24010 | 0000075569 | ethylene oxide | yes | no | ND | | 1 mg/kg in final product | |
| 136 | 41680 | 0000076212 | phosphoric acid | yes | no | no | | | (3) |
| 137 | 66580 | 0000077262-3 | methylenbis(4-methyl-6-(1-methylcyclohexyl)phenol) | yes | no | yes | (5) | | |
| 138 | 93760 | 0000077407 | butyl acetyl citrate | yes | no | no | (32) | | |
| 139 | 14680 44160 | 0000077929 | citric acid | yes | yes | no | | | |
| 140 | 44640 | 0000077930 | citric acid, triethyl ester | yes | no | no | (32) | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | |
|-----|-------|--------------|-------------------------------------|-----|-----|----|------|--|--------------------------|
| 141 | 13380 | 0000077199-6 | 199-6-trimethylolpropane | yes | yes | no | 6 | | |
| | 25600 | | | | | | | | |
| | 94960 | | | | | | | | |
| 142 | 26305 | 0000078084-0 | 8084-0-trimethoxysilanes | no | no | no | 0,05 | Only to be used as a surface treatment agent | (1) |
| 143 | 62450 | 0000078178-4 | 8178-4-pentanes | yes | no | no | | | |
| 144 | 19243 | 0000078279-5 | 8279-5-methyl-1,3-butadiene | no | yes | no | ND | | 1 mg/kg in final product |
| | 21640 | | | | | | | | |
| 145 | 10630 | 0000079006-1 | 9006-1-amide | no | yes | no | ND | | |
| 146 | 23890 | 0000079009-1 | 9009-1-acid | yes | yes | no | | | |
| | 82000 | | | | | | | | |
| 147 | 10690 | 0000079011-1 | 9011-1-acrylic acid | no | yes | no | | (22) | |
| 148 | 14650 | 0000079118-9 | 9118-9-trifluoroethylene | no | no | no | ND | | (1) |
| 149 | 19990 | 0000079130-0 | 9130-0-acrylamide | no | yes | no | ND | | |
| 150 | 20020 | 0000079141-1 | 9141-1-methacrylic acid | no | yes | no | | (23) | |
| 151 | 13480 | 0000080205-7 | 80205-7-bis(4-hydroxyphenyl)propane | no | yes | no | 0,6 | | |
| | 13607 | | | | | | | | |
| 152 | 15610 | 0000080407-9 | 80407-9-dichlorodiphenyl sulphone | no | yes | no | 0,05 | | |
| 153 | 15267 | 0000080408-0 | 80408-0-diaminodiphenyl sulphone | no | yes | no | 5 | | |
| 154 | 13617 | 0000080409-1 | 80409-1-dihydroxydiphenyl sulphone | no | yes | no | 0,05 | | |
| | 16090 | | | | | | | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | | |
|-----|-------|--------------|-----------------------------------|-----|-----|----|-----|------|---------------------------------------|---|
| 155 | 23470 | 0000080e56-8 | pinene | no | yes | no | | | | |
| 156 | 21130 | 0000080e62-6 | acrylic acid, methyl ester | no | yes | no | | (23) | | |
| 157 | 74880 | 00000847-4 | phthalic acid, dibutyl ester | yes | no | no | 0,3 | (32) | Only to be used as: (a) (b) | (7) plasticiser in repeated use materials and articles contacting non-fatty foods; technical support agent in polyolefins in concentrations up to 0,05 % in the final product. |
| 158 | 23380 | 00000851-4 | phthalic anhydride | yes | yes | no | | | | |
| | 76320 | | | | | | | | | |
| 159 | 74560 | 00000851-7 | phthalic acid, benzyl butyl ester | yes | no | no | 30 | (32) | Only to be used as: (a) | (7) plasticiser in |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | (c) | Directive 2006/125/EC; technical support agent in concentrations up to 0,1 % in the final product. |
|-----|----------------|---------|--|-----|-----|-----|------|------|---|--|
| 160 | 84800 | 0000087 | salicylic acid, 4-tert-butylphenyl ester | yes | no | yes | 12 | | | |
| 161 | 92160 | 0000087 | phthalic acid | yes | no | no | | | | |
| 162 | 65520 | 0000087 | nitro- | yes | no | no | | | | |
| 163 | 66400 | 0000088 | 2,2'-4-methylene bis(4-ethyl-6-tert-butylphenol) | yes | no | yes | | (13) | | |
| 164 | 34895 | 0000088 | 2,6-aminobenzamide | yes | no | no | 0,05 | | Only for use in PET for water and beverages | |
| 165 | 23200 74480 | 0000088 | 99-3 phthalic acid | yes | yes | no | | | | |
| 166 | 24057 | 0000089 | 3,2,7-mellitic anhydride | yes | yes | no | 0,05 | | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | | |
|-----|-------|--------|--|-----|-----|----|------|------|---|------|
| 167 | 25240 | 000009 | 1208-7 toluene diisocyanate | no | yes | no | | (17) | 1 mg/ kg in final product expressed as isocyanate moiety | (10) |
| 168 | 13075 | 000009 | 1274-9 diamino-6- phenyl-1,3,5- triazine | no | yes | no | 5 | | | (1) |
| | 15310 | | | | | | | | | |
| 169 | 16240 | 000009 | 1397-4 dimethyl-4,4'- diisocyanatobiphenyl | no | yes | no | | (17) | 1 mg/ kg in final product expressed as isocyanate moiety | (10) |
| 170 | 16000 | 000009 | 2488-6 dihydroxybiphenyl | no | yes | no | 6 | | | |
| 171 | 38080 | 000009 | 3582-3 benzoic acid, methyl ester | yes | no | no | | | | |
| 172 | 37840 | 000009 | 3582-3 benzoic acid, ethyl ester | yes | no | no | | | | |
| 173 | 60240 | 000009 | 4413-3 hydroxybenzoic acid, propyl ester | yes | no | no | | | | |
| 174 | 14740 | 000009 | 5048-7 cresol | no | yes | no | | | | |
| 175 | 20050 | 000009 | 60516-6 methacrylic acid, allyl ester | no | yes | no | 0,05 | | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | | |
|-----|-------|-----------|---|-----|-----|-----|------|------|---|--|
| 176 | 11710 | 000009633 | acrylic acid, methyl ester | no | yes | no | | (22) | | |
| 177 | 16955 | 000009645 | ethylene carbonate | no | yes | no | 30 | | SML expressed as ethyleneglycol. Residual content of 5 mg ethylene carbonate per kg of hydrogel with max 10 g of hydrogel in contact with 1 kg of food. | |
| 178 | 92800 | 000009649 | 5,5'-thiobis(6-tert-butyl-3-methylphenol) | yes | no | yes | 0,48 | | | |
| 179 | 48800 | 000009722 | 4,4'-dihydroxy-5,5'-dichlorodiphenylmethane | yes | no | yes | 12 | | | |
| 180 | 17160 | 000009753 | phenol | no | yes | no | ND | | | |
| 181 | 20890 | 000009762 | methacrylic acid, ethyl ester | no | yes | no | | (23) | | |
| 182 | 19270 | 000009765 | acetic acid | no | yes | no | | | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | |
|-----|-------|---------|---|-----|-----|------|------|--|-----|
| 183 | 21010 | 0000097 | 8619 acrylic acid, isobutyl ester | yes | no | | (23) | | |
| 184 | 20110 | 0000097 | 8814 acrylic acid, butyl ester | yes | no | | (23) | | |
| 185 | 20440 | 0000097 | 9016 acrylic acid, diester with ethyleneglycol | yes | no | 0,05 | | | |
| 186 | 14020 | 0000098 | 4514 4- butylphenol | no | yes | no | 0,05 | | |
| 187 | 22210 | 0000098 | 83-9 methylstyrene | no | yes | no | 0,05 | | |
| 188 | 19180 | 0000099 | 63 phthalic acid dichloride | yes | no | | (27) | | |
| 189 | 60200 | 0000099 | 476-3 hydroxybenzoic acid, methyl ester | yes | no | no | | | |
| 190 | 18880 | 0000099 | 96-7 hydroxybenzoic acid | no | yes | no | | | |
| 191 | 24940 | 0000100 | 20-9 phthalic acid dichloride | yes | no | | (28) | | |
| 192 | 23187 | — | phthalic acid | no | yes | no | (28) | | |
| 193 | 24610 | 0000100 | 42-5 styrene | no | yes | no | | | |
| 194 | 13150 | 0000100 | 51-6 benzyl alcohol | no | yes | no | | | |
| 195 | 37360 | 0000100 | 52-7 benzaldehyde | no | no | no | | | (3) |
| 196 | 18670 | 0000100 | 07-0 N-methyl- tetraethylamine | no | yes | no | (15) | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | |
|-----|-------|-------------|------------------------------------|-----|----|------|------|--|------|
| | 59280 | | | | | | | | |
| 197 | 20260 | 00001014319 | methacrylic acid, cyclohexyl ester | yes | no | 0,05 | | | |
| 198 | 16630 | 00001016818 | 4,4'-diphenylmethane diisocyanate | no | no | | (17) | 1 mg/kg in final product expressed as isocyanate moiety | (10) |
| 199 | 24073 | 00001019016 | epichlorohydrin diglycidyl ether | yes | no | ND | | Not to be used for articles in contact with fatty foods for which simulant D is laid down. For indirect food contact only, behind a PET layer. | (8) |
| 200 | 51680 | 00001020819 | diphenylthiourea | yes | no | yes | 3 | | |
| 201 | 16540 | 00001024010 | diphenyl carbonate | yes | no | 0,05 | | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | | |
|-----|-------|-------------|---|-----|-----|-----|------|------|---|-----|
| 202 | 23070 | 00001024336 | 2,2'-oxybis(4,4'-oxydiphenyl)acetic acid | no | yes | no | 0,05 | | | (1) |
| 203 | 13323 | 00001024409 | bis(2-hydroxyethoxy)benzene | no | yes | no | 0,05 | | | |
| 204 | 25180 | 00001025603 | N,N'-tetrakis(2-hydroxypropyl)ethylenediamine | yes | yes | no | | | | |
| | 92640 | | | | | | | | | |
| 205 | 25385 | 00001027015 | Hydramine | no | yes | no | | | 40 mg/kg hydrogel at a ratio of 1 kg food to a maximum of 1,5 grams of hydrogel. Only to be used in hydrogels intended for non-direct food contact use. | |
| 206 | 11500 | 00001032111 | acrylic acid, 2-ethylhexyl ester | no | yes | no | 0,05 | | | |
| 207 | 31920 | 00001032211 | adipic acid, bis(2- | yes | no | yes | 18 | (32) | | (2) |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | |
|-----|-------|--------------|---------------------------------|-----|----|------|------|------------------------------------|------|
| | | | ethylhexyl ester | | | | | | |
| 208 | 18898 | 000010319042 | no hydroxyphenyl) acetamide | yes | no | 0,05 | | | |
| 209 | 17050 | 0000104276-7 | ethyl-1-hexanol | yes | no | 30 | | | |
| 210 | 13390 | 0000105404-8 | bis(hydroxymethyl)cyclohexane | yes | no | | | | |
| | 14880 | | | | | | | | |
| 211 | 23920 | 0000105384 | no acid, vinyl ester | yes | no | | (1) | | |
| 212 | 14200 | 0000105602 | lactam | yes | no | | (4) | | |
| | 41840 | | | | | | | | |
| 213 | 82400 | 0000105162-4 | yes propyleneglycol dioleate | no | no | | | | |
| 214 | 61840 | 0000106124-9 | yes hydroxystearic acid | no | no | | | | |
| 215 | 14170 | 0000106346 | no butyric anhydride | yes | no | | | | |
| 216 | 14770 | 0000106344-5 | no cresol | yes | no | | | | |
| 217 | 15565 | 0000106446-7 | no dichlorobenzene | yes | no | 12 | | | |
| 218 | 11590 | 0000106603 | no acid, isobutyl ester | yes | no | | (22) | | |
| 219 | 14570 | 0000106898 | no chlorohydrin | yes | no | ND | | 1 mg/ kg in final product | (10) |
| | 16750 | | | | | | | | |
| 220 | 20590 | 0000106942 | no methacrylic acid, | yes | no | 0,02 | | | (10) |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | |
|-----|-------|--------------|-----------------------------|-----|-----|----|-----|--|--------------------------|
| | | | 2,3-epoxypropyl ester | | | | | | |
| 221 | 40570 | 000010697-8 | butane | yes | no | no | | | |
| 222 | 13870 | 0000106498-9 | butene | no | yes | no | | | |
| 223 | 13630 | 000010699-0 | butadiene | no | yes | no | ND | | 1 mg/kg in final product |
| 224 | 13900 | 0000107291-7 | butene | no | yes | no | | | |
| 225 | 12100 | 000010711-0 | butyl acrylate | yes | no | no | ND | | |
| 226 | 15272 | 000010715-1 | butyl diamine | yes | no | no | 12 | | |
| | 16960 | | | | | | | | |
| 227 | 16990 | 000010717-2 | ethylene glycol | yes | no | no | (2) | | |
| | 53650 | | | | | | | | |
| 228 | 13690 | 000010718-0 | butanediol | no | yes | no | | | |
| 229 | 14140 | 000010719-1 | butyric acid | no | yes | no | | | |
| 230 | 16150 | 000010810-1 | butyl aminoethanol | yes | no | no | 18 | | |
| 231 | 10120 | 000010805-4 | butyl acrylate, vinyl ester | no | yes | no | 12 | | |
| 232 | 10150 | 000010824-7 | butyl acrylate anhydride | yes | yes | no | | | |
| | 30280 | | | | | | | | |
| 233 | 24850 | 000010810-1 | butyl acrylate anhydride | no | yes | no | | | |
| 234 | 19960 | 000010811-2 | butyl acrylate anhydride | no | yes | no | (3) | | |
| 235 | 14710 | 000010879-4 | cresol | no | yes | no | | | |
| 236 | 23050 | 000010845-2 | phenylenediamine | no | yes | no | ND | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | | |
|-----|-------|--------------|-------------------------------|-----|-----|----|------|------|--|------|
| 237 | 15910 | 0000108146-3 | 2,4-dihydroxybenzene | no | yes | no | 2,4 | | | |
| | 24072 | | | | | | | | | |
| 238 | 18070 | 0000108554-1 | sebacic anhydride | no | yes | no | | | | |
| 239 | 19975 | 0000108274-1 | 1,3,5-triamino-1,3,5-triazine | yes | yes | no | 30 | | | |
| | 25420 | | | | | | | | | |
| | 93720 | | | | | | | | | |
| 240 | 45760 | 0000108911-8 | hexylamine | no | no | no | | | | |
| 241 | 22960 | 0000108952-1 | pentene | no | yes | no | | | | |
| 242 | 85360 | 0000109548-3 | sebacic acid, dibutyl ester | yes | no | no | | (32) | | |
| 243 | 19060 | 0000109556-1 | isobutyl vinyl ether | no | yes | no | 0,05 | | | (10) |
| 244 | 71720 | 0000109661-0 | pentene | yes | no | no | | | | |
| 245 | 22900 | 0000109167-1 | pentene | no | yes | no | 5 | | | |
| 246 | 25150 | 0000109409-9 | 2,5-dimethylfuran | yes | no | no | 0,6 | | | |
| 247 | 24820 | 0000110156-1 | succinic acid | yes | yes | no | | | | |
| | 90960 | | | | | | | | | |
| 248 | 19540 | 0000110167-1 | maleic acid | yes | yes | no | | (3) | | |
| | 64800 | | | | | | | | | |
| 249 | 17290 | 0000110178-1 | fumaric acid | yes | yes | no | | | | |
| | 55120 | | | | | | | | | |
| 250 | 53520 | 0000110305-5 | N,N'-ethylenebisstearamide | yes | no | no | | | | |
| 251 | 53360 | 0000110306-6 | N,N'-ethylenebisoleamide | yes | no | no | | | | |
| 252 | 87200 | 0000110341-1 | sebacic acid | yes | no | no | | | | |
| 253 | 15250 | 0000110460-1 | 1,4-diaminobutane | no | yes | no | | | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | | |
|-----|-------|--------------|------------------------------|-----|-----|----|------|------|--|---|
| 254 | 13720 | 0000110164-4 | butanediol | yes | yes | no | | (30) | | |
| | 40580 | | | | | | | | | |
| 255 | 25900 | 0000110188-3 | hexane | no | yes | no | 5 | | | |
| 256 | 18010 | 0000110244-3 | tartaric acid | yes | yes | no | | | | |
| | 55680 | | | | | | | | | |
| 257 | 13550 | 0000110277-5 | propylene glycol | yes | yes | no | | | | |
| | 16660 | | | | | | | | | |
| | 51760 | | | | | | | | | |
| 258 | 70480 | 0000111008-3 | phthalic acid, butyl ester | yes | no | no | | | | |
| 259 | 58720 | 0000111048-3 | heptanoic acid | yes | no | no | | | | |
| 260 | 24280 | 0000111206-3 | sebacic acid | no | yes | no | | | | |
| 261 | 15790 | 0000111400-0 | dodecyltrimethylamine | yes | yes | no | 5 | | | |
| 262 | 35284 | 0000111412-1 | N-(2-aminoethyl)ethanolamine | yes | no | no | 0,05 | | | Not to be used for articles in contact with fatty foods for which simulant D is laid down. For indirect food contact only, behind |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | |
|-----|-------|--------------|------------------|-----|-----|----|------|---|--------------|
| | | | | | | | | | a PET layer. |
| 263 | 13326 | 0000111466-1 | ethylene glycol | yes | no | | (2) | | |
| | 15760 | | | | | | | | |
| | 47680 | | | | | | | | |
| 264 | 22660 | 0000111466-0 | octene | no | yes | no | 15 | | |
| 265 | 22600 | 0000111487-5 | octanol | no | yes | no | | | |
| 266 | 25510 | 0000112477-6 | ethylene glycol | yes | no | | | | |
| | 94320 | | | | | | | | |
| 267 | 15100 | 0000112430-1 | decanol | no | yes | no | | | |
| 268 | 16704 | 0000112441-4 | dodecene | no | yes | no | 0,05 | | |
| 269 | 25090 | 0000112407-7 | ethylene glycol | yes | no | | | | |
| | 92350 | | | | | | | | |
| 270 | 22763 | 0000112811-8 | acid | yes | yes | no | | | |
| | 69040 | | | | | | | | |
| 271 | 52720 | 0000112845-5 | amide | yes | no | no | | | |
| 272 | 37040 | 0000112856-6 | benzoic acid | yes | no | no | | | |
| 273 | 52730 | 0000112867-7 | acid | yes | no | no | | | |
| 274 | 22570 | 0000112969-9 | decyl isocyanate | no | yes | no | (17) | 1 mg/kg in final product expressed as isocyanate moiety | (10) |
| 275 | 23980 | 0000115007-7 | polyene | no | yes | no | | | |
| 276 | 19000 | 0000115107-7 | isobutene | no | yes | no | | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | |
|-----|----------------|------------|--|-----|----|------|------|---------------------------------------|---|
| 277 | 18280 | 0000115276 | 2,7-dichloroendomethylene tetrahydrophthalic anhydride | yes | no | ND | | | |
| 278 | 18250 | 0000115286 | 2,8-dichloroendomethylene tetrahydrophthalic acid | yes | no | ND | | | |
| 279 | 22840 71600 | 0000115375 | penterythritol | yes | no | | | | |
| 280 | 73720 | 0000115908 | Phosphoric acid, trichloroethyl ester | yes | no | ND | | | |
| 281 | 25120 | 0000116443 | Hexafluoroethylene | yes | no | 0,05 | | | |
| 282 | 18430 | 0000116454 | Hexafluoropropylene | yes | no | ND | | | |
| 283 | 74640 | 0000117817 | Phthalic acid, bis(2-ethylhexyl) ester | yes | no | 1,5 | (32) | Only to be used as: (a) (b) | (7) plasticiser in repeated use materials and articles contacting non-fatty foods; technical support agent in concentrations up to 0,1 % in the final product. |
| 284 | 84880 | 0000119368 | Salicylic acid, | yes | no | 30 | | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | | |
|-----|-------|--------------|---|-----|-----|-----|------|--------------------------|-----|--|
| | | | methyl ester | | | | | | | |
| 285 | 66480 | 0000119247-1 | yes methylene bis(4-methyl-6-tert-butylphenol) | no | yes | | (13) | | | |
| 286 | 38240 | 0000119612-9 | benzophenone | no | yes | 0,6 | | | | |
| 287 | 60160 | 0000120447-8 | yes hydroxybenzoic acid, ethyl ester | no | no | | | | | |
| 288 | 24970 | 0000120612-1 | terephthalic acid, dimethyl ester | yes | no | | | | | |
| 289 | 15880 | 0000120482-9 | no 1,2-dihydroxybenzene | yes | no | 6 | | | | |
| | 24051 | | | | | | | | | |
| 290 | 55360 | 0000121711-0 | yes lactic acid, propyl ester | no | no | | (20) | | | |
| 291 | 19150 | 0000121915-5 | isophthalic acid | yes | no | | (27) | | | |
| 292 | 94560 | 0000122410-3 | propylamine | yes | no | 5 | | | | |
| 293 | 23175 | 0000122512-5 | phosphoric acid, triethyl ester | yes | no | ND | | 1 mg/kg in final product | (1) | |
| 294 | 93120 | 0000123428-1 | yes propionic acid, didodecyl ester | no | yes | | (14) | | | |
| 295 | 15940 | 0000123134-9 | yes 1,4-dihydroxybenzene | yes | no | 0,6 | | | | |
| | 18867 | | | | | | | | | |
| | 48620 | | | | | | | | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | |
|-----|-------|-------------|--|-----|-----|----|------|--|
| 296 | 23860 | 00001233860 | 3860 hexanaldehyde | yes | no | | | |
| 297 | 23950 | 00001233950 | 3950 phthalic anhydride | no | yes | no | | |
| 298 | 14110 | 00001234110 | 4110 7-oxoheptanaldehyde | yes | no | | | |
| 299 | 63840 | 00001236384 | 6384 7-oxoheptanoic acid | yes | no | no | | |
| 300 | 30045 | 00001238045 | 8045 3-oxobutanoic acid, butyl ester | yes | no | no | | |
| 301 | 89120 | 00001239120 | 9120 3-oxobutanoic acid, butyl ester | yes | no | no | | |
| 302 | 12820 | 00001232820 | 2820 3-oxobutanoic acid | no | yes | no | | |
| 303 | 12130 | 00001241130 | 4113 4-oxobutanoic acid | yes | yes | no | | |
| | 31730 | | | | | | | |
| 304 | 14320 | 00001240320 | 4032 4-oxobutanoic acid | yes | yes | no | | |
| | 41960 | | | | | | | |
| 305 | 15274 | 00001240274 | 4027 4-oxo-2-methylpentanediamine | no | no | no | 2,4 | |
| | 18460 | | | | | | | |
| 306 | 88960 | 00001240960 | 4096 4-oxobutanoic acid | no | yes | no | | |
| 307 | 42160 | 00001242160 | 4216 4-oxobutanoic acid | yes | no | no | | |
| 308 | 91200 | 00001261200 | 6120 6-oxoheptanoic acid, isobutyrate | yes | no | no | | |
| 309 | 91360 | 00001261360 | 6136 6-oxoheptanoic acid, octaacetate | yes | no | no | | |
| 310 | 16390 | 00001262390 | 6239 2,2,4,4-tetrahydro-1,3-dioxane | no | yes | no | 0,05 | |
| | 22437 | | | | | | | |
| 311 | 16480 | 00001264800 | 6480 5-oxopentanoic acid, erythritol | yes | no | | | |
| | 51200 | | | | | | | |

a [OJ L 302, 19.11.2005, p. 28.](#)

b [OJ L 330, 5.12.1998, p. 32.](#)

c [OJ L 253, 20.9.2008, p. 1.](#)

d [OJ L 226, 22.9.1995, p. 1.](#)

e [OJ L 158, 18.6.2008, p. 17.](#)

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | |
|-----|-------|--------------|------------------------------|-----|-----|-----|------|--|--|
| 312 | 21490 | 00001260817 | acrylonitrile | yes | no | ND | | | |
| 313 | 16650 | 00001274630 | phenylsulphone | yes | yes | no | 3 | | |
| | 51570 | | | | | | | | |
| 314 | 23500 | 0000127991-3 | pinene | no | yes | no | | | |
| 315 | 46640 | 0000128236-0 | tert-butyl-p-cresol | yes | no | no | 3 | | |
| 316 | 23230 | 0000131171 | phthalic acid, diallyl ester | no | yes | no | ND | | |
| 317 | 48880 | 0000131253-3 | 4-methoxybenzophenone | yes | no | yes | (8) | | |
| 318 | 48640 | 0000131256-6 | 4-dihydroxybenzophenone | yes | no | no | (8) | | |
| 319 | 61360 | 0000131257-7 | 4-hydroxybenzophenone | yes | no | yes | (8) | | |
| 320 | 37680 | 0000136607 | benzoic acid, butyl ester | yes | no | no | | | |
| 321 | 36080 | 0000137466 | hexyl palmitate | yes | no | no | | | |
| 322 | 63040 | 0000138121 | lactic acid, butyl ester | yes | no | no | | | |
| 323 | 11470 | 0000140488 | stearic acid, ethyl ester | no | yes | no | (22) | | |
| 324 | 83700 | 0000141220 | oleic acid | yes | no | yes | 42 | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | | |
|-----|----------------|--------|---|-----|-----|----|------|------|---|--|
| 325 | 10780 | 000014 | 132-1- lactic acid, n- butyl ester | no | yes | no | | (22) | | |
| 326 | 12763 35170 | 000014 | 1243-5 aminoethanol | yes | yes | no | 0,05 | | Not to be used for articles in contact with fatty foods for which simulant D is laid down. For indirect food contact only, behind a PET layer. | |
| 327 | 30140 | 000014 | 178-1- lactic acid, ethyl ester | yes | no | no | | | | |
| 328 | 65040 | 000014 | 182-1- lactic acid | yes | no | no | | | | |
| 329 | 59360 | 000014 | 262-1- lactic acid | yes | no | no | | | | |
| 330 | 19470 63280 | 000014 | 3107-7 lactic acid | yes | yes | no | | | | |
| 331 | 22480 | 000014 | 3108-8 nonanol | no | yes | no | | | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | |
|-----|-------|--------------|---------------------------------|-----|-----|----|------|------|------|
| 332 | 69760 | 0000143618-2 | 2,2,4-trimethyl-1-butanol | yes | no | no | | | |
| 333 | 22775 | 0000144621-7 | 4-oxo-2-pentenoic acid | yes | yes | no | 6 | | |
| | 69920 | | | | | | | | |
| 334 | 17005 | 0000151664-4 | 1,2-cyclohexanediamine | yes | no | no | ND | | |
| 335 | 68960 | 0000301022-0 | 1,2-ethanediamine | yes | no | no | | | |
| 336 | 15095 | 0000334448-5 | decanoic acid | yes | yes | no | | | |
| | 45940 | | | | | | | | |
| 337 | 15820 | 0000345492-6 | 2,2,4,4-tetrafluorobenzophenone | no | yes | no | 0,05 | | |
| 338 | 71020 | 0000373449-5 | 3-aminobenzoic acid | yes | no | no | | | |
| 339 | 86160 | 0000409511-2 | silicon carbide | yes | no | no | | | |
| 340 | 47440 | 0000461458-5 | 1,3-dioxane | no | no | no | | | |
| 341 | 13180 | 0000498566-8 | [2,2,1]hept-2-ene | no | no | no | 0,05 | | |
| | 22550 | | | | | | | | |
| 342 | 14260 | 0000502441-3 | ε-caprolactone | yes | no | no | | (29) | |
| 343 | 23770 | 0000504163-2 | propanediol | no | yes | no | 0,05 | | |
| 344 | 13810 | 0000505165-7 | butanediol formal | no | yes | no | ND | | (10) |
| | 21821 | | | | | | | | |
| 345 | 35840 | 0000506309-9 | 6-aminocaproic acid | yes | no | no | | | |
| 346 | 10030 | 0000514101-1 | 4-oxoheptanoic acid | no | yes | no | | | |
| 347 | 13050 | 0000528449-9 | 4-oxoheptanoic acid | no | yes | no | | (21) | |
| | 25540 | | | | | | | | |
| 348 | 22350 | 0000544463-8 | 4-oxoheptanoic acid | yes | yes | no | | | |
| | 67891 | | | | | | | | |
| 349 | 25550 | 0000552410-7 | 4-oxoheptanoic anhydride | yes | no | no | | (21) | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | | |
|-----|-------|--------------|--------------------------------|-----|-----|----|------|---|---|------|
| 350 | 63920 | 0000557159-5 | hexanoic acid | no | no | | | | | |
| 351 | 21730 | 0000563345-1 | methyl-1-butene | no | yes | no | ND | Only to be used in polypropylene | (1) | |
| 352 | 16360 | 0000576226-1 | dimethylphenol | no | yes | no | 0,05 | | | |
| 353 | 42480 | 0000584008-8 | nicotinic acid, rubidium salt | yes | no | no | 12 | | | |
| 354 | 25210 | 0000584284-9 | toluene diisocyanate | no | yes | no | | (17) | 1 mg/kg in final product expressed as isocyanate moiety | (10) |
| 355 | 20170 | 0000585071-0 | acrylic acid, tert-butyl ester | yes | no | no | | (23) | | |
| 356 | 18820 | 0000592441-6 | hexene | no | yes | no | 3 | | | |
| 357 | 13932 | 0000598332-3 | buten-2-ol | no | yes | no | ND | Only to be used as a co-monomer for the preparation of polymeric additive | (1) | |
| 358 | 14841 | 0000599464-4 | cumylphenol | no | yes | no | 0,05 | | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | | |
|-----|----------------|---------------|---|-----|-----|----|------|------|--|---|
| 359 | 15970 48720 | 000061149-4 | 49-4 dihydroxybenzophenone | yes | yes | no | | (8) | | |
| 360 | 57920 | 000062067-7 | 67-7 glycerol triheptanoate | yes | no | no | | | | |
| 361 | 18700 | 000062916-8 | 16-8 hexanediol | no | yes | no | 0,05 | | | |
| 362 | 14350 | 000063048-0 | 48-0 carbon monoxide | no | yes | no | | | | |
| 363 | 16450 | 000064610-0 | 10-0 dioxolane | no | yes | no | 5 | | | |
| 364 | 15404 | 000065217-3,6 | 17-3,6 dianhydrosorbitol | no | yes | no | 5 | | | Only to be used as a co-monomer in poly(ethylene-co-isosorbide terephthalate) |
| 365 | 11680 | 000068942-1c | 42-1c acetic acid, isopropyl ester | no | yes | no | | (22) | | |
| 366 | 22150 | 000069143-2 | 143-2 methyl-1-pentene | no | yes | no | 0,05 | | | |
| 367 | 16697 | 000069323-2 | 323-2 dodecanedioic acid | no | yes | no | | | | |
| 368 | 93280 | 000069316-7 | 16-7 dipropionic acid, dioctadecyl ester | no | yes | no | | (14) | | |
| 369 | 12761 | 000069312-2 | 12-2 aminododecanoic acid | no | yes | no | 0,05 | | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | |
|-----|-------|-------------|--|-----|-----|----|------|---|------|
| 370 | 21460 | 00007609310 | methacrylic anhydride | yes | no | | (23) | | |
| 371 | 11510 | 00008186110 | acrylic acid, monoester with ethyleneglycol | no | yes | no | (22) | | |
| 372 | 18640 | 00008221060 | hexamethylene diisocyanate | yes | no | | (17) | 1 mg/kg in final product expressed as isocyanate moiety | (10) |
| 373 | 22390 | 0000840265 | 2,6-naphthalenedicarboxylic acid, dimethyl ester | no | yes | no | 0,05 | | |
| 374 | 21190 | 00008687110 | methacrylic acid, monoester with ethyleneglycol | yes | no | | (23) | | |
| 375 | 15130 | 0000872105 | 9-decene | no | yes | no | 0,05 | | |
| 376 | 66905 | 0000872150 | 4-methylpyrrolidone | yes | no | no | | | |
| 377 | 12786 | 0000919330 | 2-aminopropyltriethoxysilane | no | yes | no | 0,05 | Residual extractable content of 3-aminopropyltriethoxysilane to be less than 3 mg/kg filler when used for the | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | |
|-----|-------|---------|------------------------------------|-----|-----|-----|------|------|--|
| | | | | | | | | | reactive surface treatment of inorganic fillers. SML = 0,05 mg/kg when used for the surface treatment of materials and articles. |
| 378 | 21970 | 0000923 | 302-4 methylmethacrylamide | no | yes | no | 0,05 | | |
| 379 | 21940 | 0000924 | 442-5 methylolacrylamide | no | yes | no | ND | | |
| 380 | 11980 | 0000925 | 66-1 acrylic acid, propyl ester | no | yes | no | | (22) | |
| 381 | 15030 | 0000931 | 884-0 lethyl octanoate | yes | no | no | 0,05 | | Only to be used in polymers contacting foods for which simulant A is laid down |
| 382 | 19490 | 0000947 | 104-6 lactam | yes | no | no | 5 | | |
| 383 | 72160 | 0000948 | 265-2 phenylindole | yes | no | yes | 15 | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | | |
|-----|-------|--------------|--|-----|-----|-----|------|------|--|-----|
| 384 | 40000 | 0000991284-4 | bis(octylmercapto)-6-(4-hydroxy-3,5-di-tert-butylanilino)-1,3,5-triazine | yes | no | yes | 30 | | | |
| 385 | 11530 | 0000999611 | acrylic acid, 2-hydroxypropyl ester | no | yes | no | 0,05 | | SML (1) expressed as the sum of acrylic acid, 2-hydroxypropyl ester and acrylic acid, 2-hydroxyisopropyl ester. It may contain up to 25 % (m/m) of acrylic acid, 2-hydroxyisopropyl ester (CAS No 0002918-23-2). | (1) |
| 386 | 55280 | 0001034611 | gallic acid, octyl ester | yes | no | no | | (20) | | |
| 387 | 26155 | 0001072163-5 | vinylimidazole | no | yes | no | 0,05 | | | (1) |
| 388 | 25080 | 0001120136-1 | tetradecene | no | yes | no | 0,05 | | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | |
|-----|-------|--------------|--|-----|-----|-----|------|------|--|
| 389 | 22360 | 0001141236-4 | naphthalenedicarboxylic acid | no | yes | no | 5 | | |
| 390 | 55200 | 0001166511-6 | acid, dodecyl ester | yes | no | no | | (20) | |
| 391 | 22932 | 0001187923-5 | perfluoromethyl perfluorovinyl ether | yes | no | no | 0,05 | | Only to be used in anti-stick coatings |
| 392 | 72800 | 0001241945-7 | phosphonic acid, diphenyl 2-ethylhexyl ester | yes | no | yes | 2,4 | | |
| 393 | 37280 | 0001302578-9 | nitrite | yes | no | no | | | |
| 394 | 41280 | 0001305621-0 | hydroxide | yes | no | no | | | |
| 395 | 41520 | 000130578-8 | oxide | yes | no | no | | | |
| 396 | 64640 | 0001309142-8 | hydroxide | yes | no | no | | | |
| 397 | 64720 | 0001309148-4 | oxide | yes | no | no | | | |
| 398 | 35760 | 0001309641-1 | antimony trioxide | yes | no | no | 0,04 | | SML (6) expressed as antimony |
| 399 | 81600 | 0001310583-3 | potassium hydroxide | yes | no | no | | | |
| 400 | 86720 | 0001310571-2 | hydroxide | yes | no | no | | | |
| 401 | 24475 | 0001313821-2 | sulphide | no | yes | no | | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | |
|-----|-------|---------|--|-----|----|----|------|---|--|
| 402 | 96240 | 0001314 | 413-2 zinc oxide | yes | no | no | | | |
| 403 | 96320 | 0001314 | 498-3 zinc sulphide | yes | no | no | | | |
| 404 | 67200 | 0001317 | 331-5 zinc disulphide | yes | no | no | | | |
| 405 | 16690 | 0001321 | 174-0 divinylbenzene | yes | no | ND | | SML (1) expressed as the sum of divinylbenzene and ethylvinylbenzene. It may contain up to 45 % (m/ m) of ethylvinylbenzene. | |
| 406 | 83300 | 0001323 | 312-3 propyleneglycol monostearate | yes | no | no | | | |
| 407 | 87040 | 0001330 | 414-4 sodium tetraborate | yes | no | no | (16) | | |
| 408 | 82960 | 0001330 | 180-9 propyleneglycol monooleate | yes | no | no | | | |
| 409 | 62240 | 0001332 | 137-2 zinc oxide | yes | no | no | | | |
| 410 | 62720 | 0001332 | 181-7 zinc oxide | yes | no | no | | | |
| 411 | 42080 | 0001333 | 864-4 carbon black | yes | no | no | | Primary particles of 10 – 300 nm which are aggregated to a size of 100 | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | |
|-----|-------|---------|------------------------------------|-----|-----|----|------|--|--|
| | | | | | | | | | of analysis. Benzo(a)pyrene content: max 0,25 mg/kg carbon black. Maximum use level of carbon black in the polymer: 2,5 % w/w. |
| 412 | 45200 | 0001335 | 5205 copper iodide | yes | no | no | (6) | | |
| 413 | 35600 | 0001336 | 2116 ammonium hydroxide | yes | no | no | | | |
| 414 | 87600 | 0001338 | 5012 sodium monolaurate | yes | no | no | | | |
| 415 | 87840 | 0001338 | 4111 sodium monostearate | yes | no | no | | | |
| 416 | 87680 | 0001338 | 4111 sodium monooleate | yes | no | no | | | |
| 417 | 85680 | 0001343 | 1812 ascorbic acid | yes | no | no | | | |
| 418 | 34720 | 0001344 | 2811 aluminium oxide | yes | no | no | | | |
| 419 | 92150 | 0001401 | 1511 tartaric acids | yes | no | no | | | According to the JECFA specifications |
| 420 | 19210 | 0001459 | 9311 phthalic acid, dimethyl ester | no | yes | no | 0,05 | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | | |
|-----|-------|--------------|--|-----|-----|-----|------|------|--|---|
| 421 | 13000 | 0001477153-0 | benzenedimethanamine | no | yes | no | 0,05 | | | |
| 422 | 38515 | 0001533445-5 | bis(2-benzoxazolyl)stilbene | yes | no | yes | 0,05 | | | (2) |
| 423 | 22937 | 0001623058-0 | perfluoropropyl ether | no | yes | no | 0,05 | | | |
| 424 | 15070 | 0001647116-1 | decadiene | no | yes | no | 0,05 | | | |
| 425 | 10840 | 0001663304-4 | acetic acid, tert-butyl ester | no | yes | no | | (22) | | |
| 426 | 13510 | 0001675252-3 | bis(4-hydroxyphenyl)propane bis(2,3-epoxypropyl) ether | no | yes | no | | | | In compliance with Commission Regulation (EC) No 1895/2005 ^a |
| | 13610 | | | | | | | | | |
| 427 | 18896 | 0001679451-2 | (hydroxymethyl)-1-cyclohexene | no | yes | no | 0,05 | | | |
| 428 | 95200 | 0001709170-5 | trimethyl-2,4,6-tris(3,5-di-tert-butyl-4-hydroxybenzyl)benzene | yes | no | no | | | | |
| 429 | 13210 | 0001761574-4 | (4-aminocyclohexyl)methane | no | yes | no | 0,05 | | | |
| 430 | 95600 | 0001843108-3 | tris(2-methyl-4-hydroxy-5-tert-butylphenyl)butane | yes | no | yes | 5 | | | |
| 431 | 61600 | 0001843205-6 | hydroxy-4- | yes | no | yes | | (8) | | |

^a OJ L 302, 19.11.2005, p. 28.

^b OJ L 330, 5.12.1998, p. 32.

^c OJ L 253, 20.9.2008, p. 1.

^d OJ L 226, 22.9.1995, p. 1.

^e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | |
|-----|-------|---------|--|-----|-----|-----|------|------|--|
| | | | n-octyloxybenzophenone | | | | | | |
| 432 | 12280 | 0002035 | 758 anhydride | no | yes | no | | | |
| 433 | 68320 | 0002082 | 761 3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate | yes | no | yes | 6 | | |
| 434 | 20410 | 0002082 | 817 acrylic acid, diester with 1,4-butanediol | yes | no | no | 0,05 | | |
| 435 | 14230 | 0002123 | 212 sodium salt | yes | no | no | | (4) | |
| 436 | 19480 | 0002146 | 716 acid, vinyl ester | no | yes | no | | | |
| 437 | 11245 | 0002156 | 071 acid, dodecyl ester | no | yes | no | 0,05 | | (2) |
| 438 | 38875 | 0002162 | 574 diisopropylphenyl carbodiimide | yes | no | no | 0,05 | | For indirect food contact only, behind a PET layer |
| 439 | 21280 | 0002177 | 760 acrylic acid, phenyl ester | yes | no | no | | (23) | |
| 440 | 21340 | 0002210 | 288 acrylic acid, | yes | no | no | | (23) | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | |
|-----|-------|--------------|---------------------------------------|-----|-----|----|----|------|---|
| | | | propyl ester | | | | | | |
| 441 | 38160 | 00023156826 | benzoic acid, propyl ester | yes | no | no | | | |
| 442 | 13780 | 0002425179-8 | butanediol bis(2,3-epoxypropyl)ether | no | yes | no | ND | | Residual(10) content = 1 mg/kg in final product expressed as epoxygroup. Molecular weight is 43 Da. |
| 443 | 12788 | 0002432199-7 | aminoundecanoic acid | no | yes | no | 5 | | |
| 444 | 61440 | 00024402224 | hydroxy-5'-methylphenyl)benzotriazole | yes | no | no | | (12) | |
| 445 | 83440 | 0002466992 | phosphoric acid | no | yes | no | | | |
| 446 | 10750 | 00024953544 | acrylic acid, benzyl ester | no | yes | no | | (22) | |
| 447 | 20080 | 00024953544 | acrylic acid, benzyl ester | no | yes | no | | (23) | |
| 448 | 11890 | 00024995044 | acrylic acid, n-octyl ester | no | yes | no | | (22) | |
| 449 | 49840 | 00025008826 | dodecyl disulphide | no | yes | no | 3 | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | | |
|-----|-------|---------|---------|---|-----|-----|----|------|------|--|
| 450 | 24430 | 0002561 | 888-4-1 | Basic anhydride | no | yes | no | | | |
| 451 | 66755 | 0002682 | 220-4 | methyl-4-isothiazolin-3-one | yes | no | no | 0,5 | | Only to be used in aqueous polymer dispersions and emulsions |
| 452 | 38885 | 0002725 | 224-6 | bis(2,4-dimethylphenyl)-6-(2-hydroxy-4-n-octyloxyphenyl)-1,3,5-triazine | yes | no | no | 0,05 | | Only to be used in aqueous foods |
| 453 | 26320 | 0002768 | 007 | Trimethoxysilane | no | yes | no | 0,05 | | (10) |
| 454 | 12670 | 0002855 | 113-2 | amino-3-aminomethyl-3,5,5-trimethylcyclohexane | no | yes | no | 6 | | |
| 455 | 20530 | 0002867 | 4712 | methacrylic acid, 2-(dimethylamino)-ethyl ester | yes | yes | no | ND | | |
| 456 | 10810 | 0002998 | 008 | Fic acid, sec-butyl ester | no | yes | no | | (22) | |
| 457 | 20140 | 0002998 | 1817 | methacrylic acid, sec-butyl ester | yes | yes | no | | (23) | |
| 458 | 36960 | 0003061 | 754 | Benamids | no | yes | no | | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | |
|-----|-------|---------------|--|-----|-----|-----|------|---|------|
| 459 | 46870 | 0003135318-01 | tert-butyl-4-hydroxybenzylphosphonic acid, dioctadecyl ester | yes | no | no | | | |
| 460 | 14950 | 0003173513-01 | hexyl isocyanate | yes | no | | (17) | 1 mg/kg in final product expressed as isocyanate moiety | (10) |
| 461 | 22420 | 0003173172-6 | naphthalene diisocyanate | no | yes | no | | 1 mg/kg in final product expressed as isocyanate moiety | (10) |
| 462 | 26170 | 0003195178-6 | vinyl-N-methylacetamide | no | yes | no | 0,02 | | (1) |
| 463 | 25840 | 0003290192-4 | trimethylolpropane trimethacrylate | no | yes | no | 0,05 | | |
| 464 | 61280 | 0003293297-8 | hydroxy-4-n-hexyloxybenzophenone | yes | no | yes | | (8) | |
| 465 | 68040 | 0003333762-8 | naphtho-(1,2-D)triazol-2-yl]-3-phenylcoumarin | yes | no | no | | | |

a [OJ L 302, 19.11.2005, p. 28.](#)

b [OJ L 330, 5.12.1998, p. 32.](#)

c [OJ L 253, 20.9.2008, p. 1.](#)

d [OJ L 226, 22.9.1995, p. 1.](#)

e [OJ L 158, 18.6.2008, p. 17.](#)

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | | |
|-----|-------|---------|--|-----|-----|-----|------|------|--|-----|
| 466 | 50640 | 0003648 | 18-8 dioctyltin dilaurate | yes | no | no | | (10) | | |
| 467 | 14800 | 0003724 | 65-0 ferric acid | yes | yes | no | 0,05 | | | (1) |
| | 45600 | | | | | | | | | |
| 468 | 71960 | 0003825 | 26-0 fluorocyclohexane acid, ammonium salt | no | no | no | | | Only to be used in repeated use articles, sintered at high temperatures | |
| 469 | 60480 | 0003864 | 29-2 hydroxy-3,5'- di-tert- butylphenyl)-5- chlorobenzotriazole | yes | no | yes | | (12) | | |
| 470 | 60400 | 0003896 | 21-2 hydroxy-3'- tert- butyl-5'- methylphenyl)-5- chlorobenzotriazole | yes | no | yes | | (12) | | |
| 471 | 24888 | 0003965 | 55-7 sulphoisophthalic acid, monosodium salt, dimethyl ester | no | yes | no | 0,05 | | | |
| 472 | 66560 | 0004066 | 27-8 methylenebis(4- methyl-6- cyclohexylphenol) | yes | no | yes | | (5) | | |
| 473 | 12265 | 0004074 | 10-2 adipic acid, divinyl ester | no | yes | no | ND | | 5 mg/ kg in final product | (1) |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | Only to be used as co-monomer. | |
|-----|-------|-----------|--|-----|-----|-----|-----|------|---|------|
| 474 | 43600 | 000408013 | 33-chloroallyl)-3,5,7-triaza-1-azoniaadamantane chloride | yes | no | no | 0,3 | | | |
| 475 | 19110 | 000409817 | 1-9-isocyanato-3-isocyanatomethyl-3,5,5-trimethylcyclohexane | no | yes | no | | (17) | 1 mg/kg in final product expressed as isocyanate moiety | (10) |
| 476 | 16570 | 000412817 | 1,4-bis(isocyanato)benzene | yes | yes | no | | (17) | 1 mg/kg in final product expressed as isocyanate moiety | (10) |
| 477 | 46720 | 000413024 | 2,4-di-tert-butyl-4-ethylphenol | yes | no | yes | 4,8 | | | (1) |
| 478 | 60180 | 000419147 | 3-5-hydroxybenzoic acid, isopropyl ester | yes | no | no | | | | |
| 479 | 12970 | 000419625 | 1,4-bis(isocyanato)benzene | no | yes | no | | | | |
| 480 | 46790 | 000422138 | 2,4-di-tert-butyl-4-hydroxybenzoic acid | yes | no | no | | | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | | | |
|-----|----------------|--------------|---|-----|-----|----|------|------|---|------|--|
| | | | tert-butylphenyl ester | | | | | | | | |
| 481 | 13060 | 0004422195-5 | 1,3,5-benzenetricarboxylic acid trichloride | no | yes | no | 0,05 | | SML (1) expressed as 1,3,5-benzenetricarboxylic acid | | |
| 482 | 21100 | 00046552416 | methacrylic acid, isopropyl ester | yes | no | | | (23) | | | |
| 483 | 68860 | 000472448-5 | 4-octylphosphonic acid | yes | no | no | 0,05 | | | | |
| 484 | 13395 | 000476720-7 | bis(hydroxymethyl)propionic acid | no | yes | no | 0,05 | | | (1) | |
| 485 | 13560 15700 | 000512430-1 | 4,4'-diphenylmethane diisocyanate | yes | no | no | | (17) | 1 mg/kg in final product expressed as isocyanate moiety | (10) | |
| 486 | 54005 | 000513644-7 | N,N'-dipalmitamido-N'-stearamide | yes | no | no | | | | | |
| 487 | 45640 | 0005232299-5 | 3,3'-dicyanodiphenylacrylic acid, ethyl ester | yes | no | no | 0,05 | | | | |
| 488 | 53440 | 000551818-3 | N,N'-ethylenebispalmitamide | yes | no | no | | | | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | |
|-----|-------|---------|---|-----|----|----|------|---|------|
| 489 | 41040 | 0005743 | 36-2m butyrate | yes | no | no | | | |
| 490 | 16600 | 0005873 | 55-phenylmethane-2,4'- diisocyanate | no | no | no | (17) | 1 mg/ kg in final product expressed as isocyanate moiety | (10) |
| 491 | 82720 | 0006182 | 11-2 propyleneglycol distearate | yes | no | no | | | |
| 492 | 45650 | 0006197 | 230-4 cyano-3,3- diphenylacrylic acid, 2- ethylhexyl ester | yes | no | no | 0,05 | | |
| 493 | 39200 | 0006200 | 14-2 hydroxyethyl)-2- hydroxypropyl-3- (dodecyloxy)methylammonium chloride | yes | no | no | 1,8 | | |
| 494 | 62140 | 0006303 | 31-5 hypophosphorous acid | no | no | no | | | |
| 495 | 35160 | 0006642 | 2631-5 amino-1,3- dimethyluracil | yes | no | no | 5 | | |
| 496 | 71680 | 0006683 | 19-18 erythritol tetrakis[3- (3,5- di-tert- butyl-4- hydroxyphenyl)- propionate] | no | no | no | | | |
| 497 | 95020 | 0006846 | 25-24 trimethyl-1,3- pentanediol diisobutyrate | yes | no | no | 5 | Only to be used in single- | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | | |
|-----|----------------|--------------|---|-----|-----|------|------|--|---|-----|
| | | | | | | | | | use gloves | |
| 498 | 16210 | 0006864337-5 | no dimethyl-4,4'-diaminodicyclohexylmethane | yes | no | 0,05 | | | Only to be used in polyamides | (5) |
| 499 | 19965 65020 | 00069151117 | maleic acid | yes | yes | no | | | In case of use as a monomer only to be used as a co-monomer in aliphatic polyesters up to maximum level of 1 % on a molar basis | |
| 500 | 38560 | 0007128264-5 | bis(5-tert-butyl-2-benzoxazolyl)thiophene | yes | no | yes | 0,6 | | | |
| 501 | 34480 | — | aluminium fibers, flakes and powders | yes | no | no | | | | |
| 502 | 22778 | 0007456468-0 | oxybis(benzenesulphonylazide) | no | yes | no | 0,05 | | | (1) |
| 503 | 46080 | 0007585839-9 | dextrin | yes | no | no | | | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | |
|-----|-------|---------|-------------------|-----|-----|----|-----|------|--|
| 504 | 86240 | 0007631 | silicon dioxide | yes | no | no | | | For synthetic amorphous silicon dioxide: primary particles of 1 – 100 nm which are aggregated to a size of 0,1 – 1 µm which may form agglomerates within the size distribution of 0,3 µm to the mm size. |
| 505 | 86480 | 0007632 | sulfur dioxide | yes | no | no | | (19) | |
| 506 | 86920 | 0007632 | sulfur dioxide | yes | no | no | 0,6 | | |
| 507 | 59990 | 0007647 | hydrochloric acid | yes | no | no | | | |
| 508 | 86560 | 0007647 | sodium bromide | yes | no | no | | | |
| 509 | 23170 | 0007664 | phosphoric acid | yes | yes | no | | | |
| | 72640 | | | | | | | | |
| 510 | 12789 | 0007664 | ammonia | yes | yes | no | | | |
| | 35320 | | | | | | | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | | |
|-----|-------|---------|-------|--------------------|-----|-----|----|--|------|--|
| 511 | 91920 | 0007664 | 45019 | puric acid | yes | no | no | | | |
| 512 | 81680 | 0007681 | 10108 | potassium iodide | yes | no | no | | (6) | |
| 513 | 86800 | 0007681 | 18215 | iodide | yes | no | no | | (6) | |
| 514 | 91840 | 0007704 | 45019 | puric acid | yes | no | no | | | |
| 515 | 26360 | 0007732 | 21005 | water | yes | yes | no | | | In compliance with Directive 98/83/EC ^b |
| | 95855 | | | | | | | | | |
| 516 | 86960 | 0007757 | 8017 | sulphite | yes | no | no | | (19) | |
| 517 | 81520 | 0007758 | 9023 | potassium bromide | yes | no | no | | | |
| 518 | 35845 | 0007771 | 44010 | iodic acid | yes | no | no | | | |
| 519 | 87120 | 0007772 | 9081 | thiosulphate | yes | no | no | | (19) | |
| 520 | 65120 | 0007773 | 30015 | manganese chloride | yes | no | no | | | |
| 521 | 58320 | 0007782 | 4201 | zinc white | yes | no | no | | | |
| 522 | 14530 | 0007782 | 5101 | zinc white | no | yes | no | | | |
| 523 | 45195 | 0007787 | 7004 | potassium bromide | yes | no | no | | | |
| 524 | 24520 | 0008001 | 13017 | lanolin oil | no | yes | no | | | |
| 525 | 62640 | 0008001 | 13016 | lanolin wax | yes | no | no | | | |
| 526 | 43440 | 0008001 | 13016 | lanolin wax | yes | no | no | | | |
| 527 | 14411 | 0008001 | 13017 | lanolin oil | yes | yes | no | | | |
| | 42880 | | | | | | | | | |
| 528 | 63760 | 0008002 | 13015 | lanolin wax | yes | no | no | | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | | |
|-----|-------|------------|-------------------------|-----|----|----|-------------|------|-----|---|
| 529 | 67850 | 0008002537 | non-an wax | yes | no | no | | | | |
| 530 | 41760 | 0008006448 | cellulose wax | yes | no | no | | | | |
| 531 | 36880 | 0008012893 | beeswax | yes | no | no | | | | |
| 532 | 88640 | 0008013078 | soybean oil, epoxidised | yes | no | no | 60 30(*) | (32) | (*) | In the case of PVC gaskets used to seal glass jars containing infant formulae and follow-on formulae as defined by Directive 2006/141/EC or processed cereal-based foods and baby foods for infants and young children as defined |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | |
|-----|-------|----------|---------|-----------------|-----|----|------|--|---|
| 540 | 63940 | 00080621 | 21505 | phosphoric acid | no | no | 0,24 | | Only to be used as dispersant for plastics dispersions |
| 541 | 58480 | 00090000 | 0115 | arabic gum | yes | no | | | |
| 542 | 42640 | 00090000 | 0117 | cellulose | yes | no | | | |
| 543 | 45920 | 00090000 | 0112 | damar | yes | no | | | |
| 544 | 58400 | 00090000 | 0110 | gum | yes | no | | | |
| 545 | 93680 | 00090000 | 0155 | gum | yes | no | | | |
| 546 | 71440 | 00090000 | 0160 | gum | yes | no | | | |
| 547 | 55440 | 00090000 | 0118 | gum | yes | no | | | |
| 548 | 42800 | 00090000 | 0111 | gum | yes | no | | | |
| 549 | 80000 | 00090002 | 0184 | wax | yes | no | | | |
| 550 | 81060 | 00090003 | 0170 | wax | yes | no | | | |
| 551 | 79920 | 00090003 | 0106392 | glycol | yes | no | | | |
| 552 | 81500 | 00090003 | 0108 | pyrrolidone | yes | no | | | The substance shall meet the purity criteria as laid down in Commission Directive |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | 2008/84/ EC ^c |
|-----|-------|--------------|--|-----|-----|----|----|--|-----------------------------|
| 553 | 14500 | 0009004e3116 | cellulose | yes | yes | no | | | |
| | 43280 | | | | | | | | |
| 554 | 43300 | 0009004e3118 | cellulose acetate butyrate | yes | no | no | | | |
| 555 | 53280 | 0009004e571c | cellulose | yes | no | no | | | |
| 556 | 54260 | 0009004e581h | hydroxyethyl cellulose | yes | no | no | | | |
| 557 | 66640 | 0009004e591f | ethyl cellulose | yes | no | no | | | |
| 558 | 60560 | 0009004e6210 | hydroxyethyl cellulose | yes | no | no | | | |
| 559 | 61680 | 0009004e6412 | propyl cellulose | yes | no | no | | | |
| 560 | 66700 | 0009004e6513 | hydroxypropyl cellulose | yes | no | no | | | |
| 561 | 66240 | 0009004e6715 | cellulose | yes | no | no | | | |
| 562 | 22450 | 0009004e7010 | cellulose | yes | yes | no | | | |
| 563 | 78320 | 0009004e071e | polyethylene glycol monoricinoleate | yes | yes | no | 42 | | |
| 564 | 24540 | 0009005e2f18 | starch, edible | yes | yes | no | | | |
| | 88800 | | | | | | | | |
| 565 | 61120 | 0009005e3710 | hydroxyethyl starch | yes | no | no | | | |
| 566 | 33350 | 0009005e421c | lactic acid | yes | no | no | | | |
| 567 | 82080 | 0009005137-2 | propyleneglycol alginate | yes | no | no | | | |
| 568 | 79040 | 0009005e6415 | polyethylene glycol sorbitan monolaurate | yes | no | no | | | |
| 569 | 79120 | 0009005e6516 | polyethylene glycol sorbitan monooleate | yes | no | no | | | |
| 570 | 79200 | 0009005e6617 | polyethylene glycol sorbitan monopalmitate | yes | no | no | | | |

^a OJ L 302, 19.11.2005, p. 28.

^b OJ L 330, 5.12.1998, p. 32.

^c OJ L 253, 20.9.2008, p. 1.

^d OJ L 226, 22.9.1995, p. 1.

^e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | |
|-----|-------|-------------|---|-----|-----|----|--|--|
| 571 | 79280 | 00090056078 | poly(8-hydroxyoctyl) glycol sorbitan monostearate | yes | no | | | |
| 572 | 79360 | 00090057033 | poly(3-hydroxypropyl) glycol sorbitan trioleate | yes | no | | | |
| 573 | 79440 | 00090057144 | poly(4-hydroxybutyl) glycol sorbitan tristearate | yes | no | | | |
| 574 | 24250 | 00090060466 | 60466, natural | yes | yes | no | | |
| | 84560 | | | | | | | |
| 575 | 76721 | 00631486299 | polydimethylsiloxane (Mw > 6 800 Da) | yes | no | | Viscosity at 25 °C not less than 100 cSt (100 × 10 ⁻⁶ m ² /s) | |
| 576 | 60880 | 00090324242 | hydroxyethylmethylcellulose | yes | no | | | |
| 577 | 62280 | 00090441576 | isobutylene-butene copolymer | yes | no | no | | |
| 578 | 79600 | 00090460190 | poly(9-tridecyl ether phosphate) | yes | no | 5 | For materials and articles intended for contact with aqueous foods only. Polyethyleneglycol (EO ≤ 11) tridecyl | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | |
|-----|----------------|-------------|--------------------------------------|-----|-----|-----|------|--|--|
| | | | | | | | | | ether phosphate (mono- and dialkyl ester) with a maximum 10 % content of polyethyleneglycol (EO ≤ 11) tridecylether. |
| 579 | 61800 | 00090491747 | hydroxypropyl starch | yes | no | no | | | |
| 580 | 46070 | 001001620-3 | dextrin | yes | no | no | | | |
| 581 | 36800 | 001002211-8 | barium nitrate | yes | no | no | | | |
| 582 | 50240 | 001003913-5 | dioctyltin bis(2-ethylhexyl maleate) | yes | no | no | (10) | | |
| 583 | 40400 | 001004311-5 | boron nitride | yes | no | no | (16) | | |
| 584 | 13620 40320 | 001004311-3 | boric acid | yes | yes | no | (16) | | |
| 585 | 41120 | 001004311-4 | beryllium chloride | yes | no | no | | | |
| 586 | 65280 | 001004311-2 | barium hypophosphite | yes | no | no | | | |
| 587 | 68400 | 001009445-8 | decylsuccinimide | yes | no | yes | 5 | | |
| 588 | 64320 | 001037711-2 | lithium iodide | yes | no | no | (6) | | |
| 589 | 52645 | 001043608-1 | eicosenamide | yes | no | no | | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | |
|-----|-------|--------------------|--|-----|-----|----|------|--|---------------|
| 590 | 21370 | 0010595 | 8019 acrylic acid, 2- sulphoethyl ester | yes | no | ND | | | (1) |
| 591 | 36160 | 0010605 | 0019 ethyl stearate | no | no | | | | |
| 592 | 34690 | 0011097 | 5019 magnesium carbonate hydroxide | no | no | | | | |
| 593 | 44960 | 0011104 | 4011 cobalt oxide | yes | no | no | | | |
| 594 | 65360 | 0011129 | 6019 manganese oxide | no | no | | | | |
| 595 | 19510 | 0011132 | 1713 high cell ulose | yes | no | | | | |
| 596 | 95935 | 0011138 | 6611 gum | yes | no | | | | |
| 597 | 67120 | 0012001 | 1216 zinc | yes | no | no | | | |
| 598 | 41600 | 0012004 0037293 | 4117 sulfate aluminum | yes | no | no | | | |
| 599 | 36840 | 0012007 | 5115 tetraborate | yes | no | no | (16) | | |
| 600 | 60030 | 0012072 | 9011 hydroxide | no | no | | | | |
| 601 | 35440 | 0012124 | 0719 bromide | yes | no | no | | | |
| 602 | 70240 | 0012198 | 9215 oxide | yes | no | no | | | |
| 603 | 83460 | 0012269 | 7812 phthalate | yes | no | no | | | |
| 604 | 60080 | 0012304 | 6513 talcite | yes | no | no | | | |
| 605 | 11005 | 0012542 | 3011 acid, dicyclopentenyl ester | no | yes | no | 0,05 | | (1) |
| 606 | 65200 | 0012626 | 8819 hydroxide | no | no | | | | |
| 607 | 62245 | 0012751 | 2213 phosphide | yes | no | no | | | Only to be |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | used in PET polymers and copolymers |
|-----|-------|--------------|--|-----|-----|-----|------|------|---|
| 608 | 40800 | 001300341-8 | butylidene-bis(6-tert-butyl-3-methylphenyl-ditridecyl phosphite) | yes | no | yes | 6 | | |
| 609 | 83455 | 001344556-2 | pyrophosphoric acid | no | no | no | | | |
| 610 | 93440 | 001346367-7 | dioxide | yes | no | no | | | |
| 611 | 35120 | 0013560349-1 | aminocrotonic acid, diester with thiobis (2-hydroxyethyl) ether | yes | no | no | | | |
| 612 | 16694 | 001381150-2 | divinyl-2-imidazolidinone | no | yes | no | 0,05 | | (10) |
| 613 | 95905 | 001398370-10 | styrene | yes | no | no | | | |
| 614 | 45560 | 001446461-6 | stibates | yes | no | no | | | |
| 615 | 92080 | 001480716-6 | | yes | no | no | | | |
| 616 | 83470 | 001480860-7 | | yes | no | no | | | |
| 617 | 10660 | 0015214289-8 | acrylamido-2-methylpropanesulphonic acid | no | yes | no | 0,05 | | |
| 618 | 51040 | 0015535179-2 | octyltin mercaptoacetate | yes | no | no | | (10) | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | | |
|-----|-------|---------|---|-----|-----|-----|------|------|--|-----|
| 619 | 50320 | 0015571 | 158-1 dioctyltin bis(2-ethylhexyl mercaptoacetate) | yes | no | no | | (10) | | |
| 620 | 50720 | 0015571 | 160-5 dioctyltin dimaleate | yes | no | no | | (10) | | |
| 621 | 17110 | 0016219 | 575-3 ethylidenebicyclo[2,2,1]hept-2-ene | no | yes | no | 0,05 | | | (9) |
| 622 | 69840 | 0016260 | 009-6 N-ethylpiperidone | no | yes | no | 5 | | | |
| 623 | 52640 | 0016389 | 488-1 zinc nitrate | yes | no | no | | | | |
| 624 | 18897 | 0016712 | 264-4 2-hydroxy-2-naphthalenecarboxylic acid | no | yes | no | 0,05 | | | |
| 625 | 36720 | 0017194 | 400-2 zinc hydroxide | yes | no | no | | | | |
| 626 | 57800 | 0018641 | 177-1 glycerol tribehenate | yes | no | no | | | | |
| 627 | 59760 | 0019569 | 211-2 zinc nitrate | yes | no | no | | | | |
| 628 | 96190 | 0020427 | 278-1 zinc hydroxide | yes | no | no | | | | |
| 629 | 34560 | 0021645 | 511-1 zinc hydroxide | yes | no | no | | | | |
| 630 | 82240 | 0022788 | 112-8 propyleneglycol dilaurate | yes | no | no | | | | |
| 631 | 59120 | 0023128 | 176-7 hexamethylene-bis(3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionamide) | yes | no | yes | 45 | | | |
| 632 | 52880 | 0023676 | 409-7 ethoxybenzoic acid, | yes | no | no | 3,6 | | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | | |
|-----|-------|--------------|---|-----|----|-----|------|------|---|---|
| | | | ethyl ester | | | | | | | |
| 633 | 53200 | 0023949266-8 | ethoxy-2'-ethyloxanilide | yes | no | yes | 30 | | | |
| 634 | 25910 | 002480044-0 | propylene glycol | | | no | | | | |
| 635 | 40720 | 002501346-5 | butyl-4-hydroxyanisole | yes | no | no | 30 | | | |
| 636 | 31500 | 002513451-4 | acrylic acid, acrylic acid, 2-ethylhexyl ester, copolymer | yes | no | no | 0,05 | (22) | SML expressed as acrylic acid, 2-ethylhexyl ester | |
| 637 | 71635 | 002515196-6 | terephthalate diolate | | | no | no | 0,05 | | Not to be used for articles in contact with fatty foods for which simulant D is laid down |
| 638 | 23590 | 002532268-2 | diethylene glycol | | | no | | | | |
| | 76960 | | | | | | | | | |
| 639 | 23651 | 002532269-4 | propylene glycol | | | no | | | | |
| | 80800 | | | | | | | | | |
| 640 | 54930 | 002535991-5 | formaldehyde-naphthol, copolymer | | no | no | 0,05 | | | |

a [OJ L 302, 19.11.2005, p. 28.](#)

b [OJ L 330, 5.12.1998, p. 32.](#)

c [OJ L 253, 20.9.2008, p. 1.](#)

d [OJ L 226, 22.9.1995, p. 1.](#)

e [OJ L 158, 18.6.2008, p. 17.](#)

| | | | | | | | | | |
|-----|-------|---------|---|-----|-----|----|------|--|------|
| 641 | 22331 | 0025513 | 6448 of (35-45 % w/w) 1,6- diamino-2,2,4- trimethylhexane and (55-65 % w/ w)1,6- diamino-2,4,4- trimethylhexane | no | yes | no | 0,05 | | (10) |
| 642 | 64990 | 0025736 | 6442 anhydride- styrene, copolymer, sodium salt | yes | no | no | | The fraction with molecular weight below 1 000 Da should not exceed 0,05 % (w/w) | |
| 643 | 87760 | 0026266 | 6579 monopalmitate | yes | no | no | | | |
| 644 | 88080 | 0026266 | 6580 trioleate | yes | no | no | | | |
| 645 | 67760 | 0026401 | 865 n- octyltin tris(isooctyl mercaptoacetate) | yes | no | no | | (11) | |
| 646 | 50480 | 0026401 | 865 n- octyltin bis(isooctyl mercaptoacetate) | yes | no | no | | (10) | |
| 647 | 56720 | 0026402 | 863 glycerol monoheptanoate | yes | no | no | | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | | |
|-----|-------|---------|-------|---|-----|-----|-----|------|------|--|
| 648 | 56880 | 0026402 | 2166 | glycerol mono-octanoate | yes | no | no | | | |
| 649 | 47210 | 0026427 | 4056 | di-tert-butyltin octanoic acid polymer | yes | no | no | | | Molecular unit = $(C_8H_{18}S_3Sn_2)_n$ (n = 1,5-2) |
| 650 | 49600 | 0026636 | 601 | dimethylbis(isooctyl mercaptoacetate) | yes | no | no | (9) | | |
| 651 | 88240 | 0026658 | 1017 | stearic acid tristearate | yes | no | no | | | |
| 652 | 38820 | 0026741 | 153 | (2,4-di-tert-butylphenyl) pentaerythritol diphosphite | yes | no | yes | 0,6 | | |
| 653 | 25270 | 0026747 | 290-0 | toluene diisocyanate dimer | no | yes | no | | (17) | 1 mg/kg in final product expressed as isocyanate moiety (10) |
| 654 | 88600 | 0026836 | 647 | stearic acid monostearate | yes | no | no | | | |
| 655 | 25450 | 0026896 | 148 | 1,4-bis(2-chlorophenyl)propane | no | yes | no | 0,05 | | |
| 656 | 24760 | 0026914 | 432 | 2-sulphonic acid | yes | yes | no | 0,05 | | |
| 657 | 67680 | 0027107 | 807 | n-octyltin tris(2-ethylhexyl mercaptoacetate) | yes | no | no | | (11) | |
| 658 | 52000 | 0027176 | 874 | tert-butylbenzenesulphonic acid | yes | no | no | 30 | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | | |
|-----|-------|--------------|---|-----|-----|-----|-------|------|-----------------------------------|-----|
| 659 | 82800 | 0027194172-7 | propyleneglycol monolaurate | yes | no | no | | | | |
| 660 | 47540 | 0027458400-8 | dodecyl disulphide | yes | no | yes | 0,05 | | | |
| 661 | 95360 | 0027676162-5 | tris(3,5-di-tert-butyl-4-hydroxybenzyl)-1,3,5-triazine-2,4,6(1H,3H,5H)-trione | yes | no | yes | 5 | | | |
| 662 | 25927 | 0027955194-8 | tris(4-hydroxyphenyl)ethane | no | yes | no | 0,005 | | Only to be used in polycarbonates | (1) |
| 663 | 64150 | 0028290170-1 | oleic acid | yes | no | no | | | | |
| 664 | 95000 | 0028931674-1 | trimethylpropylmethacrylate-methyl methacrylate copolymer | no | no | no | | | | |
| 665 | 83120 | 0029013428-3 | propyleneglycol monopalmitate | yes | no | no | | | | |
| 666 | 87280 | 0029116508-1 | oleic diolate | yes | no | no | | | | |
| 667 | 55190 | 0029204621-1 | oleic acid | yes | no | no | | | | |
| 668 | 80240 | 0029894357-7 | polyglycerol ricinoleate | no | no | no | | | | |
| 669 | 56610 | 0030233648-8 | monobehenate | yes | no | no | | | | |
| 670 | 56800 | 0030899672-8 | monolaurate diacetate | yes | no | no | | (32) | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | |
|-----|-------|---------|---|-----|----|-----|--------------|---|--|
| 671 | 74240 | 0031570 | 04-4 phosphoric acid, tris(2,4-di-tert-butylphenyl)ester | yes | no | no | | | |
| 672 | 76845 | 0031831 | 51-5 polyester of 1,4-butanediol with caprolactone | yes | no | no | (29) (30) | The fraction with molecular weight below 1 000 Da should not exceed 0,5 % (w/w) | |
| 673 | 53670 | 0032509 | 66-6 polyethylene glycol bis[3,3-bis(3-tert-butyl-4-hydroxyphenyl)butyrate] | yes | no | yes | 6 | | |
| 674 | 46480 | 0032647 | 67-0 azylidene sorbitol | yes | no | no | | | |
| 675 | 38800 | 0032687 | 71-8 bis(3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionyl)hydrazide | yes | no | yes | 15 | | |
| 676 | 50400 | 0033568 | 99-9 octyltin bis(isooctyl maleate) | yes | no | no | (10) | | |
| 677 | 82560 | 0033587 | 20-1 propyleneglycol dipalmitate | yes | no | no | | | |
| 678 | 59200 | 0035074 | 76-2 hexamethylene- | yes | no | yes | 6 | | |

a [OJ L 302, 19.11.2005, p. 28.](#)

b [OJ L 330, 5.12.1998, p. 32.](#)

c [OJ L 253, 20.9.2008, p. 1.](#)

d [OJ L 226, 22.9.1995, p. 1.](#)

e [OJ L 158, 18.6.2008, p. 17.](#)

| | | | | | | | | | | |
|-----|-------|--------------|--|-----|-----|-----|------|--|--|--|
| | | | bis(3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate) | | | | | | | |
| 679 | 39060 | 0035958430-6 | bis(2-hydroxy-3,5-di-tert-butylphenyl)ethane | yes | no | yes | 5 | | | |
| 680 | 94400 | 003644366812 | bis[3-(3-tert-butyl-4-hydroxy-5-methylphenyl)propionate] | yes | no | no | 9 | | | |
| 681 | 18310 | 0036653482-4 | hexadecanol | no | yes | no | | | | |
| 682 | 53270 | 00372056012 | ethylcarboxymethylcellulose | yes | yes | no | | | | |
| 683 | 66200 | 00372066012 | butylcarboxymethylcellulose | yes | yes | no | | | | |
| 684 | 68125 | 00372444016 | epihyalin | yes | no | no | | | | |
| 685 | 85950 | 00372965172 | sulfuric acid, magnesium-sodium-fluoride salt | yes | no | no | 0,15 | | | SML expressed as fluoride. Only to be used in layers of multi-layer materials not coming into direct contact |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | | with food. |
|-----|-------|---------|-------|---|-----|-----|-----|------|--|------------|
| 686 | 61390 | 0037353 | 5906 | hydroxy-methylcellulose | no | | | | | |
| 687 | 13530 | 0038103 | 206-9 | bis(4-hydroxyphenyl)propane bis(phthalic anhydride) | no | yes | no | 0,05 | | |
| | 13614 | | | | | | | | | |
| 688 | 92560 | 0038613 | 6774 | bis(3,4-di-tert-butyl-phenyl)-4,4'-biphenylene diphosphonite | yes | no | yes | 18 | | |
| 689 | 95280 | 0040601 | 176-5 | tris(4-tert-butyl-3-hydroxy-2,6-dimethylbenzyl)-1,3,5-triazine-2,4,6(1H,3H,5H)-trione | yes | no | yes | 6 | | |
| 690 | 92880 | 0041484 | 435-0 | bis(3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate) | no | yes | no | 2,4 | | |
| 691 | 13600 | 0047465 | 397-4 | bis(3-methyl-4-hydroxyphenyl)-2-indolinone | no | yes | no | 1,8 | | |
| 692 | 52320 | 0052047 | 2504 | dodecylphenylindole | yes | no | yes | 0,06 | | |
| 693 | 88160 | 0054140 | 3064 | sorbitan tripalmitate | yes | yes | no | | | |
| 694 | 21400 | 0054276 | 3516 | methacrylic acid, | yes | no | no | 0,05 | | (1) |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | |
|-----|-------|---------|--|-----|----|-----|-----|--|--|
| | | | sulphopropyl ester | | | | | | |
| 695 | 67520 | 0054849 | 2,2,6,6-tetramethyl-1,3-bis(isooctyl mercaptoacetate) | no | no | | (9) | | |
| 696 | 92205 | 0057569 | terephthalic acid, diester with 2,2'-methylenebis(4-methyl-6-tert-butylphenol) | no | no | | | | |
| 697 | 67515 | 0057583 | 2,2,6,6-tetramethyl-1,3-bis(ethylhexyl mercaptoacetate) | no | no | | (9) | | |
| 698 | 49595 | 0057583 | 2,2,6,6-tetramethyl-1,3-bis(ethylhexyl mercaptoacetate) | no | no | | (9) | | |
| 699 | 90720 | 0058446 | 2,2,4,4-tetrahydro-1H-benzopyran | no | no | | | | |
| 700 | 31520 | 0061167 | 58% acetic acid, 2-tert-butyl-6-(3-tert-butyl-2-hydroxy-5-methylbenzyl)-4-methylphenyl ester | yes | no | yes | 6 | | |
| 701 | 40160 | 0061269 | N,N-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine-1,2-dibromoethane, copolymer | yes | no | no | 2,4 | | |
| 702 | 87920 | 0061752 | 68% stearic acid tetrastearate | yes | no | no | | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | |
|-----|----------------------|----------|--|-----|-----|-----|----|------|-----|
| 703 | 17170 | 00617884 | fatty acids, coco | no | yes | no | | | |
| 704 | 77600 | 00617885 | polyethylene glycol ester of hydrogenated castor oil | yes | no | no | | | |
| 705 | 10599/90 10599/91 | 00617888 | fatty, unsaturated (C ₁₈), dimers, non hydrogenated, distilled and non-distilled | no | yes | no | | (18) | (1) |
| 706 | 17230 | 00617901 | fatty acids, tall oil | no | yes | no | | | |
| 707 | 46375 | 00617905 | diatomaceous earth | no | no | no | | | |
| 708 | 77520 | 00617911 | polyethylene glycol ester of castor oil | yes | no | no | 42 | | |
| 709 | 87520 | 00625685 | soften monobehenate | yes | no | no | | | |
| 710 | 38700 | 00633976 | carbutoxyethyltin-bis(isooctyl mercaptoacetate) | yes | no | yes | 18 | | |
| 711 | 42000 | 00634384 | carbutoxyethyltin-tris(isooctyl mercaptoacetate) | yes | no | yes | 30 | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | | |
|-----|-------|---------|--|-----|----|----|---|--|---|--|
| 712 | 42960 | 0064147 | 406 oil, dehydrated | yes | no | no | | | | |
| 713 | 43480 | 0064365 | charcoal activated | yes | no | no | | | Only for use in PET at maximum 10 mg/kg of polymer. Same purity requirements as for Vegetable Carbon (E 153) set out by Commission Directive 95/45/EC ^d with exception of ash content which can be up to 10 % (w/w). | |
| 714 | 84400 | 0064365 | 170 hydrogenated, ester with pentaerythritol | yes | no | no | | | | |
| 715 | 46880 | 0065140 | 391-2 tert- butyl-4- hydroxybenzyl acid, | yes | no | no | 6 | | | |

^a OJ L 302, 19.11.2005, p. 28.

^b OJ L 330, 5.12.1998, p. 32.

^c OJ L 253, 20.9.2008, p. 1.

^d OJ L 226, 22.9.1995, p. 1.

^e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | |
|-----|-------|---------------|---|-----|----|----|----|------|--|
| | | | monoethyl ester, calcium salt | | | | | | |
| 716 | 60800 | 006544717(20) | 4-hydroxyethyl)-4-hydroxy-2,2,6,6-tetramethyl piperidine-succinic acid, dimethyl ester, copolymer | yes | no | no | 30 | | |
| 717 | 84210 | 00659970610 | hydrogenated | yes | no | no | | | |
| 718 | 84240 | 00659970310 | hydrogenated, ester with glycerol | yes | no | no | | | |
| 719 | 65920 | 0066822160-4 | methacryloyloxyethyl-N,N-dimethyl-N-carboxymethylammonium chloride, sodium salt - octadecyl methacrylate-ethyl methacrylate-cyclohexyl methacrylate-N-vinyl-2-pyrrolidone, copolymers | yes | no | no | | | |
| 720 | 67360 | 00676491654- | n-dodecyltin | yes | no | no | | (25) | |

a [OJ L 302, 19.11.2005, p. 28.](#)

b [OJ L 330, 5.12.1998, p. 32.](#)

c [OJ L 253, 20.9.2008, p. 1.](#)

d [OJ L 226, 22.9.1995, p. 1.](#)

e [OJ L 158, 18.6.2008, p. 17.](#)

| | | | | | | | | | |
|-----|-------|--------------|---|-----|-----|----|------|--|--|
| | | | tris(isooctyl mercaptoacetate) | | | | | | |
| 721 | 46800 | 0067845395-6 | tert-butyl-4-hydroxybenzoic acid, hexadecyl ester | yes | no | no | | | |
| 722 | 17200 | 0068308651-2 | fatty acids, soya | no | yes | no | | | |
| 723 | 88880 | 0068412529-3 | starch, hydrolysed | yes | no | no | | | |
| 724 | 24903 | 0068425577-5 | syrups, hydrolysed starch, hydrogenated | no | yes | no | | | In compliance with the purity criteria for maltitol syrup E 965(ii) as laid down in Commission Directive 2008/60/EC ^e |
| 725 | 77895 | 0068439649-6 | polyethyleneglycol (EO = 2-6) monoalkyl (C ₁₆ -C ₁₈) ether | yes | no | no | 0,05 | | The composition of this mixture is as follows: — polyethyleneglycol (EO = 2-6) monoalkyl (C ₁₆ -C ₁₈) |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | | |
|-----|-------|--------------------|--|-----|----|-----|--|--------------|----------------------------|---|
| | | | | | | | | | — | ether (approximately 28 %), fatty alcohols (C ₁₆ -C ₁₈) (approximately 48 %), ethyleneglycol monoalkyl (C ₁₆ -C ₁₈) ether (approximately 24 %), |
| 726 | 83599 | 0068442 | 2nd 26 products of oleic acid, 2-mercaptoethyl ester, with dichlorodimethyltin, sodium sulphide and trichloromethyltin | yes | no | yes | | (9) | | |
| 727 | 43360 | 0068442 | 28th 10 regenerated | yes | no | no | | | | |
| 728 | 75100 | 0068515 0028553 | 18th 10 diesters with primary, saturated C ₈ -C ₁₀ branched alcohols, more than | yes | no | no | | (26) (32) | Only to be used as: (a) | (7) plasticiser in repeated use materials and articles; |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | |
|----------|------------------------------|------------------------|--|--|--|--|-----|--|
| | | 60 % C ₉ | | | | | (b) | plasticiser in single-use materials and articles contacting non-fatty foods except for infant formulae and follow-on formulae as defined by Directive 2006/141/EC or processed cereal-based foods and baby foods for infants and young children as defined by Directive 2006/125/EC; |
| | | | | | | | (c) | technical support |
| a | OJ L 302, 19.11.2005, p. 28. | | | | | | | |
| b | OJ L 330, 5.12.1998, p. 32. | | | | | | | |
| c | OJ L 253, 20.9.2008, p. 1. | | | | | | | |
| d | OJ L 226, 22.9.1995, p. 1. | | | | | | | |
| e | OJ L 158, 18.6.2008, p. 17. | | | | | | | |

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | |
|-----|-------|--------------------|--|-----|----|----|--------------|---------------------------------------|--|
| | | | | | | | | | agent in concentrations up to 0,1 % in the final product. |
| 729 | 75105 | 0068515 0026761 | Phthalic acid diesters with primary, saturated C ₉ -C ₁₁ alcohols more than 90 % C ₁₀ | yes | no | no | (26) (32) | Only to be used as: (a) (b) | (7) plasticiser in repeated use materials and articles; plasticiser in single-use materials and articles contacting non-fatty foods except for infant formulae and follow-on formulae as defined by Directive 2006/141/EC |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | | |
|-----|-------|---------|--------|-----|-----|-----|------|--|--|--|
| | | | | | | | | | | or processed cereal-based foods and baby foods for infants and young children as defined by Directive 2006/125/EC; technical support agent in concentrations up to 0,1 % in the final product. |
| 730 | 66930 | 0068554 | 470-11 | no | yes | no | | | | Residual monomer in methylsilsesquioxane: < 1 mg methyltrimethoxysilane/kg of methylsilsesquioxane |
| 731 | 18220 | 0068564 | 488-5 | no | yes | no | 0,05 | | | (2) |
| 732 | 45450 | 0068610 | 451-5 | yes | no | yes | 5 | | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | | |
|-----|----------|---------|--|-----|-----|-----|-----|------|--|-----|
| | | | isobutylene, copolymer | | | | | | | |
| 733 | 10599/92 | 0068783 | 4115, fatty, unsaturated (C ₁₈), dimers, hydrogenated, distilled and non-distilled | no | yes | no | | (18) | | (1) |
| | 10599/93 | | | | | | | | | |
| 734 | 46380 | 0068855 | 5409, magnes earth, soda ash flux-calcined | yes | no | no | | | | |
| 735 | 40120 | 0068951 | 5018, polyethylene glycol hydroxymethylphosphonate | yes | no | no | | | | |
| 736 | 50960 | 0069226 | 444, octyltin ethyleneglycol bis(mercaptoacetate) | yes | no | no | | (10) | | |
| 737 | 77370 | 0070142 | 2316, ethyleneglycol dipolyhydroxystearate | yes | no | no | | | | |
| 738 | 60320 | 0070321 | 2857, hydroxy-3,5-bis(1,1-dimethylbenzyl)phenyl]benzotriazole | yes | no | yes | 1,5 | | | |
| 739 | 70000 | 0070331 | 2921, oxamidobis[ethyl-3-(3,5-di-tert-butyl-4-hydroxyphenyl)-propionate] | yes | no | no | | | | |
| 740 | 81200 | 0071878 | 1086, [(1,1,3,3-tetramethylbutyl)amino]-1,3,5-triazine-2,4-diyl]-[(2,2,6,6- | yes | no | yes | 3 | | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | | |
|-----|----------------|----------------|--|-----|-----|-----|---|--|--|--|
| | | | tetramethyl-4-piperidyl)-imino]hexamethylene[(2,2,6,6-tetramethyl-4-piperidyl)imino] | | | | | | | |
| 741 | 24070 83610 | 0073138-83610 | acids and rosin acids | yes | yes | no | | | | |
| 742 | 92700 | 0078301242,44- | tetramethyl-20-(2,3-epoxypropyl)-7-oxa-3,20-diazadispiro-[5.1.11.2]-heneicosan-21-one, polymer | yes | no | yes | 5 | | | |
| 743 | 38950 | 00790725964- | ethylbenzylidene)sorbitol | yes | no | no | | | | |
| 744 | 18888 | 0080181331-3 | hydroxybutanoic acid-3-hydroxypentanoic acid, copolymer | no | yes | no | | | | The substance is used as product obtained by bacterial fermentation. In compliance with the specifications mentioned in the Table 4 of Annex I |
| 745 | 68145 | 0080410232,9'- | nitrilo(triethyl | yes | no | yes | 5 | | | SML expressed |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | |
|-----|-------|-----------------------|---|-----|-----|-----|------|------|---|
| | | | tris(3,3',5,5'-tetra-tert-butyl-1,1'-bi-phenyl-2,2'-diyl)phosphite) | | | | | | as sum of phosphite and phosphate |
| 746 | 38810 | 008069350026 | di-tert-butyl-4-methylphenyl)pentaerythritol diphosphite | yes | no | yes | 5 | | SML expressed as sum of phosphite and phosphate |
| 747 | 47600 | 0084030615 | dodecyltin bis(isooctyl mercaptoacetate) | yes | no | yes | | (25) | |
| 748 | 12765 | 0084434128 | N-(2-aminoethyl)-β-alanine, sodium salt | no | yes | no | 0,05 | | |
| 749 | 66360 | 0085209221 | 2-methylene bis(4,6-di-tert-butylphenyl) sodium phosphate | yes | no | yes | 5 | | |
| 750 | 66350 | 0085209224 | 4-methylenebis(4,6-di-tert-butylphenyl) lithium phosphate | yes | no | no | 5 | | |
| 751 | 81515 | 0087189251 | 2,5-bis(zinc glycerolate) | yes | no | no | | | |
| 752 | 39890 | 008782641-30069158-41 | 4-(methylbenzylidene)sorbitol | yes | no | no | | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | |
|-----|-------|---|-----|-----|-----|------|------|---|--|
| | | 40054686-97 — 40081541-12-0 | | | | | | | |
| 753 | 62800 | 00927044011- kabin, yes calcined | no | no | | | | | |
| 754 | 56020 | 00998806465- polyester yes dibehenate | no | no | | | | | |
| 755 | 21765 | 0106246434-7 methylenebis(3- chloro-2,6- diethylaniline) | no | yes | no | 0,05 | | (1) | |
| 756 | 40020 | 0110553224-0 bis(octylthiomethyl)-6- methylphenol | yes | no | yes | | (24) | | |
| 757 | 95725 | 01106387216- zinculites reaction product with citric acid, lithium salt | no | no | | | | | |
| 758 | 38940 | 0110675224-8 bis(dodecylthiomethyl)-6- methylphenol | yes | no | yes | | (24) | | |
| 759 | 54300 | 0118337209-0 ethylidenebis(4,6- di-tert- butylphenyl) fluorophosphonite | yes | no | yes | 6 | | | |
| 760 | 83595 | 01193451506-0 Reaction product of di- tert- butylphosphonite with biphenyl, obtained by condensation of 2,4- di-tert- | yes | no | no | 18 | | Composition: — 4,4'- biphenylene- bis[0,0- bis(2,4- di- tert- butylphenyl)phosphonite] (CAS No 0038613-77-3) (36-46 % w/ | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | |
|----------|------------------------------|---|--|--|--|--|---|---|
| | | butylphenol with Friedel Craft reaction product of phosphorous trichloride and biphenyl | | | | | — | w (*), 4,3'- biphenylene- bis[0,0- bis(2,4- di- tert- butylphenyl)phosphonite] (CAS No 0118421-00-4) (17-23 % w/ w (*), 3,3'- biphenylene- bis[0,0- bis(2,4- di- tert- butylphenyl)phosphonite] (CAS No 0118421-01-5) (1-5 % w/ w (*), 4- biphenylene-0,0- bis(2,4- di- tert- butylphenyl)phosphonite (CAS No 0091362-37-7) (11-19 % w/ w (*), tris(2,4- di- tert- butylphenyl)phosphite (CAS No 0031570-04-4) |
| a | OJ L 302, 19.11.2005, p. 28. | | | | | | | |
| b | OJ L 330, 5.12.1998, p. 32. | | | | | | | |
| c | OJ L 253, 20.9.2008, p. 1. | | | | | | | |
| d | OJ L 226, 22.9.1995, p. 1. | | | | | | | |
| e | OJ L 158, 18.6.2008, p. 17. | | | | | | | |

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | | — | Melt range of 85–110 °C, |
|-----|-------|---------|--|-----|-----|-----|------|--|--|---|--------------------------|
| 761 | 92930 | 0120218 | Bis[4-(methoxycarbonyl-2,6-dimethyl-1,4-dihydropyridine-3-carboxylate)] | no | no | yes | 6 | | | | |
| 762 | 31530 | 0123968 | 2,5-Di-tert-pentyl-6-(1-(3,5-di-tert-pentyl-2-hydroxyphenyl)ethyl)phenyl ester | yes | no | yes | 5 | | | | |
| 763 | 39925 | 0129228 | 2,3-bis(methoxymethyl)-2,5-dimethylhexane | yes | no | yes | 0,05 | | | | |
| 764 | 13317 | 0132459 | 4,4'-bis[4-(ethoxycarbonyl)phenyl]-1,4,5,8-naphthalenetetracarboxydiimide | no | yes | no | 0,05 | | | Purity > 98,1 % (w/w). Only to be used as co-monomer (max 4 %) for polyesters (PET, PBT). | |
| 765 | 49485 | 0134701 | 2,6-dimethyl-6-(1-methylpentadecyl)phenol | yes | no | yes | 1 | | | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | |
|-----|-------|--------------|---|-----|----|----|---|--|-----|
| 766 | 38879 | 013586156-24 | bis(2,4-dimethylbenzylidene)sorbitol | yes | no | no | | | |
| 767 | 38510 | 013650419-6 | bis(3-aminopropyl)ethylenediamine, polymer with N-butyl-2,2,6,6-tetramethyl-4-piperidinamine and 2,4,6-trichloro-1,3,5-triazine | yes | no | no | 5 | | |
| 768 | 34850 | 014392590-2 | bis(hydrogenated tallow alkyl) oxidised amines | yes | no | no | | Not to be used for articles in contact with fatty foods for which simulant D is laid down. Only to be used in: | (1) |

(a) polyolefins at 0,1 % (w/w) concentration and in PET at

(b)

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | | |
|-----|-------|---------|--|-----|----|-----|------|--|--|--|
| | | | | | | | | | | 0,25 % (w/ w) concentration. |
| 769 | 74010 | 0145650 | Phosphoric acid, bis(2,4-di-tert-butyl-6-methylphenyl) ethyl ester | yes | no | yes | 5 | | | SML expressed as sum of phosphite and phosphate |
| 770 | 51700 | 0147315 | 2,4,6-tris(diphenyl-1,3,5-triazin-2-yl)-5-(hexyloxy)phenol | yes | no | no | 0,05 | | | |
| 771 | 34650 | 0151841 | 6-hydroxybis[2,2'-methylenebis(4,6-di-tert-butylphenyl) phosphate] | yes | no | no | 5 | | | |
| 772 | 47500 | 0153250 | 2,3-dicyclohexyl-2,6-naphthalene dicarboxamide | yes | no | no | 5 | | | |
| 773 | 38840 | 0154862 | bis(2,4-dicumylphenyl) phosphite | yes | no | yes | 5 | | | SML expressed as sum of the substance itself, its oxidised form bis(2,4-dicumylphenyl)pentaerythritol-phosphate and its hydrolysis product |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | |
|-----|-------|--------------|--|-----|----|-----|---|------|---|
| | | | | | | | | | (2,4-dicumylphenol) |
| 774 | 95270 | 016171723264 | 23264 tris(tert-butyl)phenyl-2-butyl-2-ethyl-1,3-propanediol phosphite | yes | no | yes | 2 | | SML expressed as sum of phosphite, phosphate and the hydrolysis product = TTBP |
| 775 | 45705 | 0166412178 | 12178 cyclohexanedicarboxylic acid, diisononyl ester | yes | no | no | | (32) | |
| 776 | 76723 | 0167883651 | 3651 polydimethylsiloxane, 3-aminopropyl terminated, polymer with dicyclohexylmethane-4,4'-diisocyanate | yes | no | no | | | The fraction with molecular weight below 1 000 Da should not exceed 1,5 % (w/w) |
| 777 | 31542 | 0174254a2b | 4a2b adipic acid, methyl ester, telomer with 1-dodecanethiol, C ₁₆ -C ₁₈ alkyl esters | yes | no | no | | | 0,5 % (1) in final product |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | |
|-----|-------|---------|---|-----|-----|------|------|--|-----|
| 778 | 71670 | 0178671 | polyethylene tetrakis (2-cyano-3,3-diphenylacrylate) | no | yes | 0,05 | | | |
| 779 | 39815 | 0182121 | bis(methoxymethyl)fluorene | yes | no | yes | 0,05 | | (1) |
| 780 | 81220 | 0192268 | [[6-[N-(2,2,6,6-tetramethyl-4-piperidinyl)-n-butylamino]-1,3,5-triazine-2,4-diyl][(2,2,6,6-tetramethyl-4-piperidinyl)imino]-1,6-hexanediyl[(2,2,6,6-tetramethyl-4-piperidinyl)imino]]-α-[N,N,N',N'-tetrabutyl-N''-(2,2,6,6-tetramethyl-4-piperidinyl)-N''-[6-(2,2,6,6-tetramethyl-4-piperidinylamino)-hexyl]-[1,3,5-triazine-2,4,6-triamine]-ω-N,N,N',N'-tetrabutyl-1,3,5-triazine-2,4-diamine] | yes | no | no | 5 | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | | |
|-----|-------|---------------|---|-----|-----|----|------|------|--|---|
| 781 | 95265 | 0227099160-57 | tris(4-benzoylphenyl)benzene | yes | no | no | 0,05 | | | |
| 782 | 76725 | 06614760-1 | polydimethylsiloxane, 3-aminopropyl terminated, polymer with 1-isocyanato-3-isocyanatomethyl-3,5,5-trimethylcyclohexane | | | no | | | | The fraction with molecular weight below 1 000 Da should not exceed 1 % (w/w) |
| 783 | 55910 | 07361506-3 | castor-oil mono-, hydrogenated, acetates | yes | no | no | | (32) | | |
| 784 | 95420 | 0745070161-5 | tris(2,2-dimethylpropanamido)benzene | yes | no | no | 0,05 | | | |
| 785 | 24910 | 00001000-1 | terephthalic acid | yes | no | | | (28) | | |
| 786 | 14627 | 0000117321-5 | 3-chlorophthalic anhydride | no | yes | no | 0,05 | | | SML expressed as 3-chlorophthalic acid |
| 787 | 14628 | 0000118445-6 | 4-chlorophthalic anhydride | no | yes | no | 0,05 | | | SML expressed as 4-chlorophthalic acid |
| 788 | 21498 | 0002530135-0 | (methacryloxy)propyltrimethoxysilane | no | yes | no | 0,05 | | | Only to be used (1) (11) |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | |
|-----|-------|------------------|--|-----|----|----|---|--|--|
| | | | | | | | | | as a surface treatment agent of inorganic fillers |
| 789 | 60027 | — | hydrogenated homopolymers and/or copolymers made of 1-hexene and/or 1-octene and/or 1-decene and/or 1-dodecene and/or 1-tetradecene (Mw: 440–12 000) | yes | no | no | | | Average (2) molecular weight not less than 440 Da. Viscosity at 100 °C not less than 3,8 cSt (3,8 × 10 ⁻⁶ m ² /s). |
| 790 | 80480 | 009075 008245 | poly(1,3,5-triazine-2,4-diyl)-[(2,2,6,6-tetramethyl-4-piperidyl)imino] hexamethylene-[(2,2,6,6-tetramethyl-4-piperidyl)imino] | yes | no | no | 5 | | Average (16) molecular weight not less than 2 400 Da. Residual content of morpholine ≤ 30 mg/kg, of N,N'- |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | |
|-----|-------|---------|---|-----|----|-----|------|--|--|
| | | | | | | | | | bis(2,2,6,6-tetramethylpiperidin-4-yl)hexane-1,6-diamine < 15 000 mg/kg, and of 2,4-dichloro-6-morpholino-1,3,5-triazine ≤ 20 mg/kg. |
| 791 | 92470 | 0106990 | N,N',N,N'-tetrakis(4,6-bis(N-butyl-(N-methyl-2,2,6,6-tetramethylpiperidin-4-yl)amino)triazin-2-yl)-4,7-diazadecane-1,10-diamine | yes | no | no | 0,05 | | |
| 792 | 92475 | 0203255 | 3,3',5,5'-tetrakis(tert-butyl)-2,2'-dihydroxybiphenyl, cyclic ester with [3-(3-tert-butyl-4-hydroxy-5-methylphenyl)propyl]oxyphosphonous acid | yes | no | yes | 5 | | SML expressed as the sum of phosphite and phosphate form of the substance and the hydrolysis products |
| 793 | 94000 | 0000102 | 7-ethanoylamine | yes | no | no | 0,05 | | SML expressed as the sum of |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | | |
|-----|-------|---------|---|-----|-----|-----|------|--------------|---|-------------|
| | | | | | | | | | triethanolamine and the hydrochloride adduct expressed as triethanolamine | |
| 794 | 18117 | 0000079 | glycolic acid | no | yes | no | | | For indirect food contact only, behind a PET layer | |
| 795 | 40155 | 0124172 | N,N-bis(2,2,6,6-tetramethyl-4-piperidyl)-N,N'-diformylhexamethylenediamine | yes | no | no | 0,05 | | | (2) (12) |
| 796 | 72141 | 0018602 | (1,4-phenylene)bis[4H-3,1-benzoxazin-4-one] | yes | no | yes | 0,05 | | SML including the sum of its hydrolysis products | |
| 797 | 76807 | 0007328 | polyester of adipic acid with 1,3-butanediol, 1,2-propanediol and 2-ethyl-1-hexanol | yes | no | yes | | (31) (32) | | |
| 798 | 92200 | 0006422 | terephthalic acid, | yes | no | no | 60 | (32) | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | | |
|-----|-------|-------------|--|-----|----|----|-----|--|--|---|
| | | | bis(2-ethylhexyl)ester | | | | | | | |
| 799 | 77708 | — | polyethyleneglycol (EO = 1-50) ethers of linear and branched primary (C ₈ -C ₂₂) alcohols | yes | no | no | 1,8 | | | In compliance with the purity criteria for ethylene oxide as laid down in Directive 2008/84/EC laying down specific purity criteria on food additives other than colours and sweeteners (OJ L 253, 20.9.2008, p. 1) |
| 800 | 94425 | 00008671110 | tributyl phosphonoacetate | yes | no | no | | | | Only for use in PET |
| 801 | 30607 | — | acids, C ₂ -C ₂₄ , aliphatic, linear, monocarboxylic, from natural oils | yes | no | no | | | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | |
|-----|-------|---------|---|-----|----|----|---|---|------|
| | | | and fats, lithium salt | | | | | | |
| 802 | 33105 | 0146340 | alcohols C ₁₂ - C ₁₄ secondary, β-(2- hydroxyethoxy), ethoxylated | yes | no | no | 5 | | (12) |
| 803 | 33535 | 0152261 | 33-1 alkenes(C ₂₀ - C ₂₄) copolymer with maleic anhydride, reaction product with 4- amino-2,2,6,6- tetramethylpiperidine | yes | no | no | | Not to be used for articles in contact with fatty foods for which simulant D is laid down. Not to be used in contact with alcoholic foods. | (13) |
| 804 | 80510 | 1010121 | 8073- nonyl-1,1- dioxo-1- thiopropene-1,3- diyl)- block- poly(x- oleyl-7- hydroxy-1,5- diiminoctane-1,8- | yes | no | no | | Only to be used as polymer production aid in polyethylene (PE), polypropylene | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | |
|-----|-------|--------------|--|-----|-----|----|---|--|--|
| | | | diyl), process mixture with x = 1 and/or 5, neutralised with dodecylbenzenesulfonic acid | | | | | | (PP) and polystyrene (PS) |
| 805 | 93450 | — | titanium dioxide, coated with a copolymer of n-octyltrichlorosilane and [aminotris(methylenephosphonic acid), penta sodium salt] | yes | no | no | | | The content of the surface treatment copolymer of the coated titanium dioxide is less than 1 % w/w |
| 806 | 14876 | 0001076197-7 | cyclohexanedicarboxylic acid | no | yes | no | 5 | | Only to be used for manufacture of polyesters |
| 807 | 93485 | — | titanium nitride, nanoparticles | yes | no | no | | | No migration of titanium nitride nanoparticles. Only to be used in PET bottles up to |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | |
|-----|-------|---------------|---|-----|----|-----|------|------|--|
| | | | | | | | | | 20 mg/kg. In the PET, the agglomerates have a diameter of 100 – 500 nm consisting of primary titanium nitride nanoparticles; primary particles have a diameter of approximately 20 nm. |
| 808 | 38550 | 0882073b14(4) | propylbenzylidene)propylsorbitol | yes | no | no | 5 | | SML including the sum of its hydrolysis products |
| 809 | 49080 | 0852282N89-4 | (2,6-diisopropylphenyl)-6-[4-(1,1,3,3-tetramethylbutyl)phenoxy]-1H-benzo[de]isoquinolin-1,3(2H)-dione | yes | no | yes | 0,05 | | Only (6) for use (14) in PET (15) |
| 810 | 68119 | | neopentyl glycol, diesters and monoesters with | yes | no | no | 5 | (32) | Not to be used for articles in |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | |
|-----|-------|---------|--|----|----|----|--|--|--|
| | | | benzoic acid and 2-ethylhexanoic acid | | | | | | contact with fatty foods for which simulant D is laid down. |
| 811 | 80077 | 006844 | polyethylene waxes, oxidised | no | no | 60 | | | |
| 812 | 80350 | 0124578 | poly(12-hydroxystearic acid)-polyethyleneimine copolymer | no | no | | | | Only to be used in polyethylene terephthalate (PET), polystyrene (PS), high impact polystyrene (HIPS) and polyamide (PA) up to 0,1 % w/w. Prepared by the reaction of poly(12-hydroxystearic acid) with polyethyleneimine. |
| 813 | 91530 | — | sulphosuccinic acid alkyl (C ₄ - | no | no | 5 | | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | |
|-----|-------|---|--|-----|----|----|---|------|---|
| | | | C ₂₀) or cyclohexyl diesters, salts | | | | | | |
| 814 | 91815 | — | sulphosuccinic acid monoalkyl (C ₁₀ -C ₁₆) polyethyleneglycol esters, salts | yes | no | no | 2 | | |
| 815 | 94985 | — | trimethylpropyl mixed triesters and diesters with benzoic acid and 2-ethylhexanoic acid | no | no | no | 5 | (32) | Not to be used for articles in contact with fatty foods for which simulant D is laid down |
| 816 | 45704 | — | cis-1,2-cyclohexanedicarboxylic acid, salts | yes | no | no | 5 | | |
| 817 | 38507 | — | cis-endo-bicyclo[2.2.1]heptane-2,3-dicarboxylic acid, salts | yes | no | no | 5 | | Not to be used with polyethylene in contact with acidic foods. Purity ≥ 96 %. |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | | |
|-----|-------|---|---------------------------------------|-----|----|----|------|--|--|-----|
| 818 | 21530 | — | methallyl acid, salts | yes | no | no | 5 | | | |
| 819 | 68110 | — | neodecanoic acid, salts | yes | no | no | 0,05 | | Not to be used in polymers contacting fatty foods. Not to be used for articles in contact with fatty foods for which simulant D is laid down. SML expressed as neodecanoic acid. | |
| 820 | 76420 | — | pimelic acid, salts | yes | no | no | | | | |
| 821 | 90810 | — | stearoyl- lactic acid, salts | yes | no | no | | | | |
| 822 | 71938 | — | perchloric acid, salts | yes | no | no | 0,05 | | | (4) |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | | |
|-----|-------|---------|--|-----|-----|----|---|--|--|---|
| 823 | 24889 | — | 5-Sulphoisophthalic acid, salts | no | yes | no | 5 | | | |
| 854 | 71943 | 0329238 | perfluoroacetic acid, α -substituted with the copolymer of perfluoro-1,2-propylene glycol and perfluoro-1,1-ethylene glycol, terminated with chlorohexafluoropropoxy groups | yes | no | no | | | | Only to be used in concentrations up to 0,5 % w/w in the polymerisation of fluoropolymers that are processed at temperatures at or above 340 °C and are intended for use in repeated use articles |
| 860 | 71980 | 0051798 | perfluoro[2-(poly(n-propoxy))propanoic acid] | yes | no | no | | | | Only to be used in the polymerisation of fluoropolymers that are processed at temperatures at or |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | |
|-----|-------|---------|------------------------|----|-----|----|------|--|---|
| | | | | | | | | | above 265 °C and are intended for use in repeated use articles |
| 861 | 71990 | 0013252 | 2-ethylhexanoic acid | no | no | | | | Only to be used in the polymerisation of fluoropolymers that are processed at temperatures at or above 265 °C and are intended for use in repeated use articles |
| 862 | 15180 | 0018085 | 3,4-diacetoxy-1-butene | no | yes | no | 0,05 | | SML including the hydrolysis product 3,4-dihydroxy-1-butene. Only for use as a co- |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | |
|-----|-------|---------------|--|-----|----|----|---|--|--|
| | | | | | | | | | monomer for ethyl vinyl alcohol copolymers. |
| 864 | 46330 | 0000056206-4 | 206-4 diamino-6- hydroxypyrimidine | yes | no | no | 5 | | Only to be used in rigid poly(vinyl chloride) (PVC) in contact with non- acidic and non- alcoholic aqueous food |
| 865 | 40619 | 0025322(00-01 | 00-01 acrylate, methyl methacrylate, butyl methacrylate) copolymer | yes | no | no | | | Only to be used in rigid poly(vinyl chloride) (PVC) at a maximum level of 1 % |
| 866 | 40620 | — | (butyl acrylate, methyl methacrylate) copolymer, cross- linked with | yes | no | no | | | Only to be used in rigid poly(vinyl chloride) (PVC) at a |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | |
|-----|-------|---------|--|-----|----|----|---|--|---|
| | | | allyl methacrylate | | | | | | maximum level of 7 % |
| 867 | 40815 | 0040471 | (00-21) yes methacrylate, ethyl acrylate, methyl methacrylate) copolymer | no | no | | | | Only to be used in rigid poly(vinyl chloride) (PVC) at a maximum level of 2 % |
| 868 | 53245 | 0009010 | (00-21) yes acrylate, methyl methacrylate) copolymer | no | no | | | | Only to be used in rigid poly(vinyl chloride) (PVC) at a maximum level of 2 % |
| 869 | 66763 | 0027136 | (00-21) yes acrylate, methyl methacrylate, styrene) copolymer | no | no | | | | Only to be used in rigid poly(vinyl chloride) (PVC) at a maximum level of 3 % |
| 870 | 95500 | 0160535 | N,N'-tris(2-methylcyclohexyl)-1,2,3- | yes | no | no | 5 | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | | |
|-----|-------|----------------------|---|-----|----|-----|---|--|--|--|
| | | | propane- tricarboxamide | | | | | | | |
| 875 | 80345 | 0058128 ^a | poly(12-hydroxystearic acid) stearate | yes | no | yes | 5 | | | |
| 878 | 31335 | — | acids, fatty (C ₈ -C ₂₂) from animal or vegetable fats and oils, esters with branched alcohols, aliphatic, monohydric, saturated, primary (C ₃ -C ₂₂) | yes | no | no | | | | |
| 879 | 31336 | — | acids, fatty (C ₈ -C ₂₂) from animal or vegetable fats and oils, esters with alcohols, linear, aliphatic, monohydric, | yes | no | no | | | | |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

| | | | | | | | | | |
|-----|-------|---------|---|-----|-----|----|------|--|---|
| | | | saturated, primary (C ₁ -C ₂₂) | | | | | | |
| 880 | 31348 | 0085116 | 0034, fatty (C ₈ -C ₂₂), esters with pentaerythritol | yes | no | no | | | |
| 881 | 25187 | 0003010 | 295,4-tetramethylcyclobutane-1,3-diol | no | yes | no | 5 | | Only for repeated use articles for long term storage at room temperature or below and hotfill |
| 882 | 25872 | 0002416 | 293,6-trimethylphenol | no | yes | no | 0,05 | | |
| 883 | 22074 | 0004457 | 371-0 methyl-1,5-pentanediol | no | yes | no | 0,05 | | Only to be used in materials in contact with food at a surface to mass ratio up to |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | | | | | | | |
|-----|-------|---------|---|-----|----|----|------|--|---|
| | | | | | | | | | 0,5 dm ² / kg |
| 884 | 34240 | 0091082 | alkyl C ₁₀ -C ₂₁ sulphonic acid, esters with phenol | yes | no | no | 0,05 | | Not to be used for articles in contact with fatty foods for which simulant D is laid down. |
| 885 | 45676 | 0263244 | oligomers of (butylene terephthalate) | yes | no | no | | | Only to be used in poly(ethylene terephthalate) (PET), poly(butylene terephthalate) (PBT), polycarbonate (PC), polystyrene (PS) and rigid poly(vinyl chloride) (PVC) plastics in concentrations up to 1 % w/w, in contact |

a OJ L 302, 19.11.2005, p. 28.

b OJ L 330, 5.12.1998, p. 32.

c OJ L 253, 20.9.2008, p. 1.

d OJ L 226, 22.9.1995, p. 1.

e OJ L 158, 18.6.2008, p. 17.

Status: This is the original version (as it was originally adopted).

| | | | |
|----|--|-------|--|
| 4 | 212 435 | 15 | expressed as caprolactam |
| 5 | 137 472 | 3 | expressed as the sum of the substances |
| 6 | 412 512 513 588 | 1 | expressed as iodine |
| 7 | 19 20 | 1,2 | expressed as tertiary amine |
| 8 | 317 318 319 359 431 464 | 6 | expressed as the sum of the substances |
| 9 | 650 695 697 698 726 | 0,18 | expressed as tin |
| 10 | 28 29 30 31 32 33 466 582 618 619 620 646 676 736 | 0,006 | expressed as tin |
| 11 | 66 645 657 | 1,2 | expressed as tin |
| 12 | 444 469 470 | 30 | expressed as the sum of the substances |
| 13 | 163 285 | 1,5 | expressed as the sum of the substances |
| 14 | 294 368 | 5 | expressed as the sum of the substances |

Status: This is the original version (as it was originally adopted).

| | | | |
|----|---|------|---|
| 15 | 98 196 | 15 | expressed as formaldehyde |
| 16 | 407 583 584 599 | 6 | expressed as boron Without prejudice to the provisions of Directive 98/83/EC |
| 17 | 4 167 169 198 274 354 372 460 461 475 476 485 490 653 | ND | expressed as isocyanate moiety |
| 18 | 705 733 | 0,05 | expressed as the sum of the substances |
| 19 | 505 516 519 | 10 | expressed as SO ₂ |
| 20 | 290 386 390 | 30 | expressed as the sum of the substances |
| 21 | 347 349 | 5 | expressed as trimellitic acid |
| 22 | 70 147 176 218 323 325 365 371 380 425 446 448 456 636 | 6 | expressed as acrylic acid |
| 23 | 150 156 181 183 | 6 | expressed as methacrylic acid |

Status: This is the original version (as it was originally adopted).

| | | | |
|----|---|------|--|
| | 184 355 370 374 439 440 447 457 482 | | |
| 24 | 756 758 | 5 | expressed as the sum of the substances |
| 25 | 720 747 | 0,05 | sum of mono-n-dodecyltin tris(isooctylmercaptoacetate), di-n-dodecyltin bis(isooctylmercaptoacetate), mono-dodecyltin trichloride and di-dodecyltin dichloride) expressed as the sum of mono- and di-dodecyltin chloride |
| 26 | 728 729 | 9 | expressed as the sum of the substances |
| 27 | 188 291 | 5 | expressed as isophthalic acid |
| 28 | 191 192 785 | 7,5 | expressed as terephthalic acid |
| 29 | 342 672 | 0,05 | expressed as the sum of 6-hydroxyhexanoic acid and caprolactone |
| 30 | 254 672 | 5 | expressed as 1,4-butanediol |
| 31 | 73 797 | 30 | expressed as the sum of the substances |
| 32 | 8 72 73 138 140 157 159 207 242 283 532 | 60 | expressed as the sum of the substances |

| | | |
|-----|--|--|
| 670 | | |
| 728 | | |
| 729 | | |
| 775 | | |
| 783 | | |
| 797 | | |
| 798 | | |
| 810 | | |
| 815 | | |

3. Notes on verification of compliance

Table 3 on notes on verification of compliance contains the following information:

Column 1 (Note No): contains the identification number of the Note. It is the number referred to in Column 11 in Table 1 of this Annex.

Column 2 (Notes on verification of compliance): contains rules that shall be respected when testing for compliance of the substance with specific migration limits or other restrictions or it contains remarks on situations where there is a risk of non-compliance.

TABLE 3

| (1) Note No | (2) Notes on verification of compliance |
|------------------------------|--|
| (1) | Verification of compliance by residual content per food contact surface area (QMA) pending the availability of an analytical method. |
| (2) | There is a risk that the SML or OML could be exceeded in fatty food simulants. |
| (3) | There is a risk that the migration of the substance deteriorates the organoleptic characteristics of the food in contact and then, that the final product does not comply with Article 3(1) c of the Framework Regulation (EC) No 1935/2004. |
| (4) | Compliance testing when there is a fat contact should be performed using saturated fatty food simulants as simulant D. |
| (5) | Compliance testing when there is a fat contact should be performed using isooctane as substitute of simulant D2 (unstable). |
| (6) | Migration limit might be exceeded at very high temperature. |
| (7) | If testing in food is performed, Annex V 1.4 shall be taken into account. |

Status: This is the original version (as it was originally adopted).

| | |
|------|---|
| (8) | Verification of compliance by residual content per food contact surface area (QMA); QMA = 0,005 mg/6 dm ² . |
| (9) | Verification of compliance by residual content per food contact surface area (QMA) pending the availability of analytical method for migration testing. The ratio surface to quantity of food shall be lower than 2dm ² /kg. |
| (10) | Verification of compliance by residual content per food contact surface area (QMA) in case of reaction with food or simulant. |
| (11) | Only a method of analysis for the determination of the residual monomer in the treated filler is available. |
| (12) | There is a risk that the SML could be exceeded from polyolefins. |
| (13) | Only a method for determination of the content in polymer and a method for determination of the starting substances in food simulants are available. |
| (14) | There is a risk that the SML could be exceeded from plastics containing more than 0,5 % w/w of the substance. |
| (15) | There is a risk that the SML could be exceeded in contact with foods with high alcoholic content. |
| (16) | There is a risk that the SML could be exceeded from low-density polyethylene (LDPE) containing more than 0,3 % w/w of the substance when in contact with fatty foods |
| (17) | Only a method for determination of the residual content of the substance in the polymer is available |

4. Detailed specification on substances


Table 4 on detailed specifications on substances contains the following information

Column 1 (FCM substance No): contains the unique identification number of the substances referred to in Column 1 in Table 1 of Annex I to which the specification applies.

Column 2 (Detailed specification on the substance): contains the specification on the substance.

TABLE 4

| (1) | (2) |
|-----|-----|
|-----|-----|

| FCM substance No | Detailed specification on the substance | |
|------------------|---|---|
| 744 | Definition | <p>The copolymers are produced by the controlled fermentation of <i>Alcaligenes eutrophus</i> using mixtures of glucose and propanoic acid as carbon sources. The organism used has not been genetically engineered and has been derived from a single wildtype organism <i>Alcaligenes eutrophus</i> strain H16 NCIMB 10442. Master stocks of the organism are stored as freeze-dried ampoules. A submaster/working stock is prepared from the master stock and stored in liquid nitrogen and used to prepare inocula for the fermenter. Fermenter samples will be examined daily both microscopically and for any changes in colonial morphology on a variety of agars at different temperatures. The copolymers are isolated from heat treatment bacteria by controlled digestion of the other cellular components, washing and drying. These copolymers are normally offered as formulated, melt formed granules containing additives such as nucleating agents, plasticisers, fillers, stabilisers and pigments which all conform to the general and individual specifications</p> |
| | Chemical name | Poly(3-D-hydroxybutanoate-co-3-D-hydroxypentanoate) |
| | CAS number | 0080181-31-3 |
| | Structural formula |  <p>where $n/(m + n)$ greater than 0 and less or equal to 0,25</p> |

Status: This is the original version (as it was originally adopted).

| | | |
|--|--------------------------|--|
| | Average molecular weight | Not less than 150 000 Daltons (measured by gel permeation chromatography) |
| | Assay | Not less than 98 % poly(3-D-hydroxybutanoate-co-3-D-hydroxy-pentanoate) analysed after hydrolysis as a mixture of 3-D-hydroxybutanoic and 3-D-hydroxypentanoic acids |
| | Description | White to off-white powder after isolation |
| | Characteristics | |
| | Identification tests: | |
| | Solubility | Soluble in chlorinated hydrocarbons such as chloroform or dichloromethane but practically insoluble in ethanol, aliphatic alkanes and water |
| | Restriction | QMA for crotonic acid is 0,05 mg/6 dm ² |
| | Purity | Prior to granulation the raw material copolymer powder must contain: |
| | — nitrogen, | Not more than 2 500 mg/kg of plastic |
| | — zinc, | Not more than 100 mg/kg of plastic |
| | — copper, | Not more than 5 mg/kg of plastic |
| | — lead, | Not more than 2 mg/kg of plastic |
| | — arsenic, | Not more than 1 mg/kg of plastic |
| | — chromium, | Not more than 1 mg/kg of plastic |