
Status: Point in time view as at 26/01/2017.

Changes to legislation: There are outstanding changes not yet made to Commission Delegated Regulation (EU) 2017/1475. Any changes that have already been made to the legislation appear in the content and are referenced with annotations. (See end of Document for details)

ANNEX

For products covered by standard EN 1304 ‘Clay roofing tiles and fittings — Product definitions and specifications’ and intended for external use, a new classification in relation to their essential characteristic ‘frost resistance’ is established as follows:

Class 1 (150 cycles): minimum 150 cycles. If after 150 cycles none of the tiles shows any of the damage described as unacceptable according to EN 539-2:2013, Table 1.

Class 2 (90 cycles): 90 – 149 cycles. If after 90 cycles none of the tiles shows any of the damage described as unacceptable according to EN 539-2:2013, Table 1.

Class 3 (30 cycles): 30 – 89 cycles. If after 30 cycles none of the tiles shows any of the damage described as unacceptable according to EN 539-2:2013, Table 1.

Status:

Point in time view as at 26/01/2017.

Changes to legislation:

There are outstanding changes not yet made to Commission Delegated Regulation (EU) 2017/1475. Any changes that have already been made to the legislation appear in the content and are referenced with annotations.