

SCHEDULE 2

METHODS OF ANALYSIS

PART II

17.

DETERMINATION OF FINENESS OF POTASSIC BASIC SLAG

Sieving

4.2 Weigh to the nearest 0.1 g, 20 g of the dry sample and transfer to the sieve with the lower receiver attached. Shake the sieve for five minutes, frequently tapping the sides. Disintegrate soft lumps that can be caused to crumble by the application of a soft brush, taking care that the hard part of the brush does not make contact with the sieve and that the brush is not used to brush particles through the sieve.

Transfer the finer portion from the container into a 500 ml beaker and add 200 ml of previously boiled water. Stir and then filter through a weighed glass sintered crucible. Thoroughly wash the residue with water, dry and re-weigh the crucible. Calculate the weight of slag in the mixture with a particle size of less than 0.5 mm (A).

Weigh to the nearest 0.01 g about 20 g of the dry sample and transfer to a 500 ml conical flask. Add 200 ml previously boiled water and shake for 30 minutes. Filter through a weighed, sintered glass crucible, wash the residue thoroughly with water, dry and re-weigh the crucible. Calculate the total weight of slag in the mixture (B).