

## SCHEDULE 1

### PART I

4. The foam under test, cut to the specified dimensions is placed on the test rig, covered with the fabric specified in paragraph 2 above and tensioned with clips as set out in BS 5852: Part 2. An ignition source 5 crib is placed in position. The mass of the complete assembly is determined (“initial mass”). The test shall be carried out in accordance with BS 5852: Part 2. In particular flaming or smouldering failure shall be determined against the criteria of clause 4 of BS 5852: Part 2.

After flaming and smouldering has ceased, any debris which has become detached from the specimen shall be removed. The remaining mass of the assembly (“final mass”) is then recorded.