

## SCHEDULE 5

[<sup>F1</sup>Regulation 8 and 9]

### THE MATCH TEST

#### Textual Amendments

- F1** Sch. 5 shoulder note substituted (1.3.1990) by The Furniture and Furnishings (Fire) (Safety) (Amendment) Regulations 1989 (S.I. 1989/2358), regs. 1(2), **10(a)**

#### Commencement Information

- I1** Sch. 5 in force at 1.11.1988, see **reg. 1(2)(a)**

## PART I

1. All braids and other trimmings shall be removed from material upon which a test is to be conducted.

2. Any covering fabric which has been treated with a fire-retardant chemical to reduce the ignitability of the upholstery shall, before it is conditioned in accordance with clause 7.1 of B.S. 5852: Part 1 be subjected to the water-soaking procedure set out in clauses 4.2 to 4.5 of B.S. 5651, save that for the second subclause of clause 4.5 there shall be substituted the following:

“After 30 minutes, remove the specimen, rinse in water (4.2.1) using a liquor ratio of 1:20 for 2 minutes, and then dry the specimen by any method suitable for the fabric type.”

3. The test shall be carried out in accordance with those provisions of BS 5852: Part 1 which relate to butane flame ignition source 1. The filling material for this test shall be non-fire retardant polyurethane foam corresponding to the specification set out in BS 3379 Type B Hardness grade 130 and of a density of 20–22 kg per m<sup>3</sup>.

4. The criteria of failure shall be those specified in clause [<sup>F2</sup>9] of BS 5852: Part 1.

#### Textual Amendments

- F2** Word in Sch. 5 Pt. 1 para. 4 substituted (1.3.1990) by The Furniture and Furnishings (Fire) (Safety) (Amendment) Regulations 1989 (S.I. 1989/2358), regs. 1(2), **10(b)**

## PART II

### THE MATCH TEST FOR STRETCH COVERS

The test for stretch covers shall be conducted in the same way as for other cover materials except that the filling material over which the fabric is tested shall be a foam which passes the ignitability test in Part I of Schedule 1 and which has a density of 24–26 kg per m<sup>3</sup>.

**Changes to legislation:** *There are currently no known outstanding effects for the The Furniture and Furnishings (Fire) (Safety) Regulations 1988, SCHEDULE 5. (See end of Document for details)*

## [<sup>F3</sup>PART III

### THE MATCH TEST FOR INVISIBLE PARTS OF COVERS

---

#### **Textual Amendments**

**F3** Sch. 5 Pt. 3 inserted (1.3.1990) by [The Furniture and Furnishings \(Fire\) \(Safety\) \(Amendment\) Regulations 1989 \(S.I. 1989/2358\)](#), regs. 1(2), **10(c)**

1. The test shall be carried out in accordance with those provisions of BS 5852: Part 1 which relate to butane flame ignition source 1. The filling material for this test shall be a foam which passes the ignitability test in Part 1 of Schedule 1 and which has a density of 24—26 kg per m<sup>3</sup>.
2. The criteria of failure shall be those specified in clause 9 of BS 5852: Part 1.]

**Changes to legislation:**

There are currently no known outstanding effects for the The Furniture and Furnishings (Fire) (Safety) Regulations 1988, SCHEDULE 5.