

## SCHEDULE 5

### THE MATCH TEST

---

#### Commencement Information

**II** Sch. 5 in force at 1.11.1988, see **reg. 1(2)(a)**

### PART I

**3.** The test shall be carried out in accordance with those provisions of BS 5852: Part 1 which relate to butane flame ignition source 1. The filling material for this test shall be non-fire retardant polyurethane foam corresponding to the specification set out in BS 3379 Type B Hardness grade 130 and of a density of 20–22 kg per m<sup>3</sup>.

**Changes to legislation:**

There are currently no known outstanding effects for the The Furniture and Furnishings (Fire) (Safety) Regulations 1988, Paragraph 3.