

Status: This version of this schedule contains provisions that are prospective.

Changes to legislation: There are outstanding changes not yet made by the legislation.gov.uk editorial team to The Plastic Materials and Articles in Contact with Food (England) (No.2) Regulations 2006. Any changes that have already been made by the team appear in the content and are referenced with annotations. (See end of Document for details) View outstanding changes

PROSPECTIVE

SCHEDULE 2

Regulations 9 and 11

Provisions Applicable when Testing Compliance with the Migration Limits

General Provisions

1. When the results of the migration tests specified in this Schedule and, where appropriate Schedule 3, are analytically determined, the specific gravity of any simulants used shall be assumed to be 1, so that milligrams of any substance released per litre of simulant will correspond numerically to milligrams of that substance released per kilogram of that simulant.

Commencement Information

I1 Sch. 2 para. 1 in force at 19.11.2006, see [reg. 1](#)

2. Where any migration test specified in this Schedule and, where appropriate, Schedule 3 is carried out on any sample taken from any plastic material or article and the quantities of food or simulant placed in contact with the sample differ from those employed in the actual conditions under which the plastic material or article is used or is to be used, the results obtained should be corrected by applying the formula $M = ((m \cdot a_2 / a_1 \cdot q) \cdot 1000)$ where —

- (a) M is the migration in mg/kg;
- (b) m is the mass in the mg of substance released by the sample as determined by the migration test;
- (c) a_1 is the surface area in square decimetres of the sample in contact with the food or simulant during the migration test;
- (d) a_2 is the surface area in square decimetres of the plastic material or article in actual conditions of use; and
- (e) q is the quantity in grams of food in contact with the plastic material or article in actual conditions of use.

Commencement Information

I2 Sch. 2 para. 2 in force at 19.11.2006, see [reg. 1](#)

3.—(1) Subject to sub-paragraph (2), any testing of migration from any plastic material or article shall be carried out on that plastic material or article.

(2) In any case where determination in accordance with sub-paragraph (1) above is impracticable, such testing shall be carried out, using either specimens taken from that plastic material or article, or where appropriate, specimens representative of that plastic material or article.

(3) Any sample used for such testing shall be placed in contact with the simulant or food, as the case may be, in a manner representing the contact conditions in actual use, and for this purpose the testing shall be carried out in such a way that only those parts of the sample intended to come into contact with food in actual use will be in contact with the simulant or food.

Status: This version of this schedule contains provisions that are prospective.

Changes to legislation: There are outstanding changes not yet made by the legislation.gov.uk editorial team to The Plastic Materials and Articles in Contact with Food (England) (No.2) Regulations 2006. Any changes that have already been made by the team appear in the content and are referenced with annotations. (See end of Document for details) View outstanding changes

(4) Any migration testing of caps, gaskets, stoppers or similar devices for sealing shall be carried out on these articles by applying them to the containers for which they are intended in a manner which corresponds to the conditions of closing in normal or foreseeable use.

Commencement Information

I3 Sch. 2 para. 3 in force at 19.11.2006, see [reg. 1](#)

4.—(1) Any sample of plastic material or article shall be placed in contact with the appropriate simulant or the food for a period and at a temperature which are chosen by reference to the contact conditions in actual use in accordance with the provisions of this Schedule and, where appropriate, Schedule 3.

(2) At the end of the period referred to in sub-paragraph (1), analytical determination of the total quantity of substances (overall migration), each specific quantity of a substance (specific migration) or, as the case may be, both that total and that specific quantity released by the sample shall be carried out on the simulant or food, as the case may be.

(3) Verification that migration into food complies with a migration limit specified in regulation 9 or in Annex II, III or IV (for the purposes of this Schedule and Schedule 3 referred to together as “the Annexes”) shall be carried out under the most extreme conditions of time and temperature foreseeable in actual use in accordance with the provisions of this Schedule.

(4) Verification that migration into food simulants complies with a migration limit specified in regulation 9 or the Annexes shall be carried out in accordance with the provisions of this Schedule and using conventional migration tests, the basic rules for which are set out in Schedule 3.

Commencement Information

I4 Sch. 2 para. 4 in force at 19.11.2006, see [reg. 1](#)

5. Where a plastic material or article is intended to come into repeated contact with food, any migration test shall (subject to paragraph 7 below) be carried out three times on a single sample in accordance with the conditions laid down in this Schedule and, where appropriate, Schedule 3 using separate samples of the simulant or, as the case may be food, on each occasion, and the level of the migration found in the third test shall be treated as the level relevant to that test.

Commencement Information

I5 Sch. 2 para. 5 in force at 19.11.2006, see [reg. 1](#)

Commencement Information

- I1** Sch. 2 para. 1 in force at 19.11.2006, see [reg. 1](#)
- I2** Sch. 2 para. 2 in force at 19.11.2006, see [reg. 1](#)
- I3** Sch. 2 para. 3 in force at 19.11.2006, see [reg. 1](#)
- I4** Sch. 2 para. 4 in force at 19.11.2006, see [reg. 1](#)
- I5** Sch. 2 para. 5 in force at 19.11.2006, see [reg. 1](#)

Status: This version of this schedule contains provisions that are prospective.

Changes to legislation: There are outstanding changes not yet made by the [legislation.gov.uk](https://www.legislation.gov.uk) editorial team to The Plastic Materials and Articles in Contact with Food (England) (No.2) Regulations 2006. Any changes that have already been made by the team appear in the content and are referenced with annotations. (See end of Document for details) [View outstanding changes](#)

Special provisions relating to overall migration

6.—(1) Subject to sub-paragraph (2), any method of analytical determination may be used to prove excess of an overall migration limit in relation to a plastic material or article.

(2) In any proceedings for an offence under these Regulations where it is alleged that a plastic material or article does not comply with regulation 9 it shall be a defence for the person charged to prove that—

- (a) if an aqueous simulant specified in Schedule 3 had been used, and the analytical determination of the total quantity of substances released by a sample of the plastic material or article tested had been carried out by evaporation of the simulant and weighing of the residue; or
- (b) if rectified olive oil or any of its substitutes had been used as a simulant and—
 - (i) a sample of the plastic material or article had been weighed before and after contact with the simulant;
 - (ii) the simulant absorbed by the sample had been extracted and determined quantitatively;
 - (iii) the quantity of simulant so found had been subtracted from the weight of the sample measured after contact with the simulant; and
 - (iv) the difference between the initial and corrected final weights had been determined to represent the overall migration of the sample examined,

there would have been no such excess so determined.

Commencement Information

I6 Sch. 2 para. 6 in force at 19.11.2006, see [reg. 1](#)

7.—(1) Where a plastic material or article is intended to come into repeated contact with food and it is technically impossible to carry out the test described in paragraph 5, the test shall be modified in accordance with sub-paragraph (2) or in such other way so as to enable the level of migration occurring during the third such test to be determined, and such a determination may be used as evidence of the overall migration in relation to a plastic material or article.

(2) Three identical samples of the plastic material or article are to be procured, following which—

- (a) the first sample is to be subjected to the appropriate test according with paragraph 4 and the overall migration determined (M_1);
- (b) the second and third samples are to be subjected to the same conditions of temperature but the period of contact is to be respectively two and three times that specified and the overall migration determined in each case (M_2 and M_3).

(3) Where a modified test has been carried out in accordance with sub-paragraph (2), provided that either M_1 or $M_3 - M_2$ did not exceed the overall migration limit, the plastic material or article subjected to the test shall be deemed to be in compliance with that limit.

Commencement Information

I7 Sch. 2 para. 7 in force at 19.11.2006, see [reg. 1](#)

Status: This version of this schedule contains provisions that are prospective.

Changes to legislation: There are outstanding changes not yet made by the legislation.gov.uk editorial team to The Plastic Materials and Articles in Contact with Food (England) (No.2) Regulations 2006. Any changes that have already been made by the team appear in the content and are referenced with annotations. (See end of Document for details) View outstanding changes

8.—(1) Any plastic material or article which exceeds its overall migration limit by an amount not exceeding the analytical tolerance specified in sub-paragraph (2) shall be deemed for the purposes of these Regulations not to exceed its overall migration limit.

(2) The following analytical tolerances shall be applied for limits of overall migration—

- (a) 20 mg/kg or, as the case may be, 3 milligrams per square decimetre in migration tests using as a simulant rectified olive oil or substitutes;
- (b) 12mg/kg or, as the case may be, 2 milligrams per square decimetre in migration tests using other simulants referred to in Schedule 3.

Commencement Information

18 Sch. 2 para. 8 in force at 19.11.2006, see [reg. 1](#)

Commencement Information

16 Sch. 2 para. 6 in force at 19.11.2006, see [reg. 1](#)

17 Sch. 2 para. 7 in force at 19.11.2006, see [reg. 1](#)

18 Sch. 2 para. 8 in force at 19.11.2006, see [reg. 1](#)

Status:

This version of this schedule contains provisions that are prospective.

Changes to legislation:

There are outstanding changes not yet made by the legislation.gov.uk editorial team to The Plastic Materials and Articles in Contact with Food (England) (No.2) Regulations 2006. Any changes that have already been made by the team appear in the content and are referenced with annotations.

[View outstanding changes](#)

Changes and effects yet to be applied to :

- Sch. 2 para. 1 coming into force by [S.I. 2006/2687 reg. 1](#)
- Sch. 2 para. 2 coming into force by [S.I. 2006/2687 reg. 1](#)
- Sch. 2 para. 3 coming into force by [S.I. 2006/2687 reg. 1](#)
- Sch. 2 para. 4 coming into force by [S.I. 2006/2687 reg. 1](#)
- Sch. 2 para. 5 coming into force by [S.I. 2006/2687 reg. 1](#)
- Sch. 2 para. 6 coming into force by [S.I. 2006/2687 reg. 1](#)
- Sch. 2 para. 7 coming into force by [S.I. 2006/2687 reg. 1](#)
- Sch. 2 para. 8 coming into force by [S.I. 2006/2687 reg. 1](#)
- Regulations revoked by [S.I. 2008/916 reg. 29\(a\)](#)