

## SCHEDULE 3

### Overall and Specific Migration Testing Using Food Simulants

## PART 5

### Migration Test Conditions (Times and Temperatures)

#### **General criteria**

2. Where the plastic material or article being tested is intended for a food contact application covered by a combination of two or more times and temperatures specified in column 2 of the Table to this Part, the migration test shall be carried out by subjecting the test specimen successively to all the applicable worst foreseeable conditions appropriate to the sample, using the same portion of food simulant.