

SCHEDULE 3

Overall and Specific Migration Testing Using Food Simulants

PART 2

Food Simulants to be used in Migration Testing

5. Where a fatty food simulant specified in paragraph 4 is used in migration testing and the result of that test shows that a plastic material or article does not comply with any migration limit specified in regulation 9 or the Annexes, verification that the plastic material or article does not comply with the specified migration must be carried out by testing that material or article using olive oil if such testing is technically feasible, and if such testing is not technically feasible the plastic material or article is deemed not to comply with the specified migration limit.